An integrated scheme for crystal plasticity analysis: Virtual grain structure generation

P Zhang, D Balint and J Lin*

Department of Mechanical Engineering, Imperial College, London SW7 2AZ, UK

ABSTRACT

An integrated scheme is developed based on the controlled Poisson Voronoi tessellation (CPVT) model to generate the polycrystalline grain structure for micromechanics simulations. The proposed model of CPVT involves a single control parameter that is used to produce the grain structure with regularity control, by which the yielded tessellation varies from the purely random Voronoi tessellation to the regular hexagonal tessellation. The system extends the standard CPVT model by the addition of two features: a one-parameter gamma distribution and a mapping from a set of quantitative metallographic measurements to the distribution parameter. Based on this scheme, a grain structure can be constructed such that the virtual tessellation is statistically equivalent to the expected grain size distribution. To validate the modules that utilise the physical parameters that dictate the regularity, a series of theoretical investigations is performed. Efforts are devoted to proving the uniqueness of the mapping from the physical parameters to the distribution parameter and the regularity parameter. An efficient numerical algorithm is provided to facilitate the mapping solution process. A software system (VGRAIN) is developed implementing the proposed CPVT model to generate the grain structure for crystal plasticity finite element (CPFE) analysis. To demonstrate the proposed scheme and the VGRAIN system, a plane strain CPFE analysis is conducted. Two microstructures are generated with different regularities, and the deformation under uniaxial tension is simulated.

Keywords: Voronoi tessellation; grain structure; grain size distribution; crystal plasticity finite element (CPFE) analysis; micromechanics

* The corresponding author. E-mail address: d.balint@imperial.ac.uk

1. Introduction

Computational studies (e.g. CPFE) employing crystal plasticity theory are currently being used to gain valuable insights into mechanical deformation of polycrystalline materials [1, 2]. Since stress-strain distributions are related to grain size, shape, orientation and their distributions, FE micromechanics simulations must be based upon a grain structure modelled within a FE/CAE computational environment, as shown in **Error! Reference source not found.** Explicit modelling of the grain structure is essential to capture a range of size-dependent features of micromechanical deformation [3-5].

Grain structures for micromechanical simulations can be obtained by various metallographic techniques relying on two-dimensional images. Images may be captured using optical microscopy [6-9] or electron back-scatter diffraction (EBSD) maps [10-15]; combined with manual or automatic sketching methods, grain structures can then be constructed and input to a FE model. However, these experimental approaches are extremely time-consuming and expensive for practical applications, and the achieved grain structures are also difficult to extrapolate to large specimens. Recently, a novel X-Ray diffraction method has also been proposed for structural characterisation of polycrystalline materials [16,17], although this approach requires high-energy synchrotron radiation sources. In contrast, geometrical models provide a solution to quickly generate large virtual grain structures. In early research, simplified geometrical units such as cubes, rhombic dodecahedra, and truncated octahedrons were employed to represent the grain aggregates, e.g. [18-21]; the study in [22] examined the influence of grain shape on the aggregate mechanical behaviour. The reported results have shown that the inter-granular and intra-granular stress variations depended consistently on the grain shape. However, in reality most grain structures exhibit large variations in grain shape and size. Hence, such uniform discretisations fail to account for the natural variations in grain morphology. Alternatively, efforts have been made to simulate realistic grain structures by means of e.g., the Monte-Carlo (Potts) model [23], the ellipsoid packing algorithm combined with the cellular automata (CA) method [24], the phase field model [25] and level-set methods [26,27], the latter of which has been implemented in a microstructure generation software system.

Traditionally, Voronoi tessellation (VT) models have been widely used for metallurgical applications [28, 29], as they provide a natural solution to represent microstructures with non-uniform grain shapes. Formation of a Voronoi tessellation can be generally interpreted as the result of a grain aggregate growth process, where grains are spatially distributed and completely

determined by initial nuclei and growth velocities [28]. However, as the Voronoi tessellation is disordered, there are still no clear rules for interpreting the organisation and geometrical constraints of the grains produced by the tessellation. One key issue in generating the virtual grain structure is evaluating the degree of uniformity [30], and also using the degree of uniformity to generate the tessellation with control of the grain size distribution.

To evaluate the degree of grain size uniformity or regularity for Voronoi tessellations, Zhu et al. [31] introduced a regularity parameter evaluating the degree of uniformity of a Voronoi tessellation with reference to a regular hexagonal tessellation (RHT). The value of the regularity parameter ranges from 0 to 1, corresponding to a Poisson Voronoi tessellation (PVT) and a regular hexagonal tessellation, respectively. Ho et al. [32] and Cao et al. [33] adopted this regularity parameter as a control parameter and proposed a scheme to produce Voronoi tessellations with specified regularity. However, the correlation between regularity and the grain structure is generally too obscure for engineers, so efforts have been devoted to replacing the regularity parameter by a set of physical parameters obtained from the quantitative metallographic measurements. In [32], a set of four parameters is used to quantify the grain size distribution, including a mean grain size, a large grain size and a small grain size, as well as the percentage of grains within that range. The numerical procedure to derive the regularity value implemented a direct enumerative method which has a very low efficiency. Cao et al. [33] attempted to improve the efficiency by devising a statistical method to derive the grain size distribution based on the mean grain size and two sampled grain sizes. However, their statistical estimation failed to provide a sufficient level of precision.

To support the scheme of generating the grain structure by means of the VT model with regularity control, two critical issues remain to be solved: 1) First and foremost, the theoretical relation between the regularity value and the set of physical parameters characterizing the grain structure needs to be addressed and derived. This scheme works under the assumption that the physical parameters can uniquely define the grain size distribution and the regularity value, but the exact relation between them must be revealed. 2) Secondly, if the regularity parameter can be determined by the physical parameters, an effective algorithm is essential to calculate the control parameter from the physical parameters.

In the first part of this work, a controlled Poisson Voronoi tessellation model (CPVT) is proposed, which involves a control parameter to monitor the generation of the grain structure with a prescribed regularity. This CPVT model will then be embedded into an integrated scheme to generate

the virtual grain structure. The integrated scheme starts with the input of the four measurements including the mean grain size, large and small grain sizes, and the percentage of grains within that range. Then the regularity and control parameter of the CPVT can be derived in sequence.

In the second part, a series of theoretical results will be provided to validate the uniqueness of the determination of the tessellation's regularity based on the physical parameters. Further, an efficient numerical procedure is proposed to facilitate determination of the distribution parameter. Finally, two micro-mechanics FE simulations are performed to demonstrate the application of the integrated grain structure modelling system. Note that, for simplicity and without loss of generality, all examples and discussions are based on two-dimensional¹ tessellations, and the grain size is defined in terms of grain area.

2. CPVT model and integrated grain structure generation scheme

Polycrystalline materials are originally formed by the nucleation and growth of grains. The initial nucleation site for each grain is referred to as its seed; a final grain structure depends on the seed pattern and individual grain growth velocities, which describe the speed of progressive addition of atoms until impinge upon adjacent grains. Voronoi tessellations are naturally analogous to the material solidification [28], wherein seeds of a Voronoi tessellation are spatially distributed, and grain boundaries are determined by the specified grain growth velocities for the given seed pattern.

Given a plane of area A_0 , and letting the seeds be produced in the area by sampling x and y coordinates independently from a uniform random generator, a corresponding tessellation can be achieved after a growth process. The resulting tessellation is generally referred to as a Poisson Voronoi tessellation (PVT). Note that the seeds are represented by points in a PVT. In contrast, assuming that each initial seed is a circle with diameter $\delta > 0$, and no seeds overlap each other in the seed lattice, then an alternative Voronoi tessellation can be produced by uniformly generating and growing the circular seeds. This random VT is called a *controlled Poisson Voronoi tessellation* (CPVT), where the circle diameter of a seed is used as a *control parameter* dictating the distances between it and its neighbours. The CPVT generation process proceeds as follows: After the first seed is produced, each subsequent seed i is only accepted if it is greater than a minimum allowable distance δ_i from any existing seed, i.e., $d(i, k) \geq \delta_i$, where $k = 1, 2, \dots, i - 1$. Provided that all seeds have the same diameter δ , the distance between a newly generated seed i and an existing seed k

¹ The present framework has been extended to three-dimensional tessellations; this will be presented in a forthcoming publication.

satisfies the condition $d(i, k) \geq \delta, \forall k = 1, 2, \dots, i - 1$. For example, as illustrated in Fig. 2, the new seed g would be accepted because the distances between g and the other adjacent seeds are all equal to or larger than δ .

The CPVT model aims to fully control the tessellation's regularity and its corresponding grain size distribution, and the control parameter is the primary link between the user-expected grain structure and the realised virtual grain structure. Fig. 3 shows the integrated system that employs the CPVT model to generate the grain structure based on the user input. The overall procedure is:

- Workpiece related input includes the size of a workpiece and the mean grain size, which are used to obtain the implementation parameters including the tessellation's domain Ω and the number of grains N_{seed} ;
- Grain structure related input consists of four physical parameters, which describe a set of higher order grain size distribution features, to determine the control parameter δ ;
- In the process of deriving the regularity, two modules are involved: One maps from the physical parameters to a distribution parameter c , and the other maps from the distribution parameter to the regularity parameter α .

Now, the controlled Poisson Voronoi model can be denoted as $CPVT(\delta|\Omega, N_{seed})$, where under the evaluation of δ , the N_{seed} seeds are sequentially generated within the domain Ω . Details of the implementation will be discussed in the remainder of this section.

2.1 Regularity and the control parameter

To evaluate the regularity of the tessellation, Zhu *et al.* defined the regularity parameter α in [31] as

$$\alpha = \delta/d_{reg}, \quad (1)$$

where δ is the minimum distance among all neighbouring seeds in the tessellation, and d_{reg} is the distance between two adjacent seeds in the equivalent regular hexagonal tessellation (RHT). According to the seed lattice of the RHT, the standard seed distance d_{reg} is calculated as

$$d_{reg} = \left(\frac{2A_0}{3^{1/2}N} \right)^{1/2}, \quad (2)$$

where A_0 is the area of the equivalent RHT and N is the number of hexagons in the RHT.

2.2.1 Equivalent regular hexagonal tessellation

Here the term ‘equivalent’ means that a VT and its correlated RHT have an equal mean grain size D_{mean} and an equal domain area A_0 . It is important to note that the equivalent RHT consists of space-filling hexagons, which partition a domain of area A_0 without overlap, therefore the number of grains in the RHT can be directly determined from the domain area, according to

$$N = A_0/D_{mean} . \quad (3)$$

As a result, the number of grains in a VT can be determined by using the definition of its equivalent RHT, specified by user input.

In quantitative metallography, the number of grains is determined based on the heuristic rule that a grain cut by boundaries is counted as a half grain. However, in the proposed scheme, a VT is generated as follows: 1) A domain is defined; 2) the seeds are randomly created in the given area; 3) the grain structure is generated. Therefore, the final tessellation ignores the effect of seeds external to the domain, which exist in actual materials.

Fig. 4 shows tessellations with and without external seeds. Neglecting neighbouring seeds, the tessellation in (b) has lost approximately half of the grains cut by boundaries, presented in (a). However the total area of the grains cut by boundaries is correspondingly increased in (b) by a factor of ~ 2 . Therefore, based on the above VT scheme, the number of grains and seeds are approximately equivalent, i.e.,

$$N_{seed} \approx N. \quad (4)$$

Therefore, based on the heuristic rule given by Eq. (4), the equivalent RHT can be used to determine the number of seeds required for the VT, together with the result of Eq. (3).

2.2.2 Control parameter δ of the CPVT

The control parameter of a CPVT is defined by a minimum acceptable seed spacing (or seed distance). The minimum seed spacing of a VT was employed to compute the regularity value α of a VT in [31], whilst by prescribing an expected minimum seed spacing using the control parameter, a final VT has an approximate regularity α . This can be explained in that as randomly sampling a certain number of seeds, the minimum seed spacing would converge to the value of the control parameter. Also, when sampling a small number of seeds, the resultant VT tends to be more regular than the prescribed regularity, due to random error. However, the random error is small and allowable, when the number of grains is large (c.f. [34] for further details).

Thus, the expected minimum seed spacing is taken as the control parameter to monitor the seed generation process. From the definition of the tessellation's regularity in Eq. (1), the control parameter δ can be determined by

$$\delta = \alpha d_{reg}. \quad (5)$$

It can be seen that if $\alpha = 0$, then $\delta = 0$, and the resultant tessellation is a pure Poisson Voronoi Tessellation, whilst letting the regularity $\alpha = 1$ gives $\delta = d_{reg}$, and the yielded tessellation in that case is exactly a regular hexagonal tessellation. As the regularity α varies from 0 to 1, the tessellations become increasingly uniform. Fig. 5 shows a series of tessellations with varying regularity values.

In summary, implementation of the CPVT model $CPVT(\delta|\Omega, N_{seed})$ involves two parallel procedures: Determination of the implementation parameters $\{\Omega, N_{seed}\}$ and derivation of the control parameter δ . First of all, the number of seeds N_{seed} to be generated in a VT is determined by Eq. (4) and the standard seed distance d_{reg} is defined in Eq. (2). Secondly, with the assignment of a regularity value, a control parameter δ can be obtained from Eq. (5).

2.2 Regularity, grain size distribution and physical parameters

In a CPVT, the regularity parameter α is used directly to specify the control parameter δ . However, physical measurements from quantitative metallography, such as the mean grain size and percentage of grains between the small and large sizes, are well known and widely used by engineers and material scientists. In such a circumstance, the regularity parameter is not intuitive for practical use.

Two modules are to be developed to map the gap between the physical parameters and regularity parameter. The first module is the grain size distribution model linking the tessellation's regularity to its grain size distribution, and the other module is the mechanism to determine the distribution parameter from the given physical parameters.

Traditionally, the grain area distributions of Voronoi tessellations have been modelled by gamma distribution functions. Reported results include a three-parameter gamma distribution [35] and a two-parameter gamma distribution [36, 37]. If the experimental data is normalised by the mean grain area, then a one-parameter gamma distribution can also accurately fit the grain size distribution in term of grain area [30, 31, 38, 39]. The one-parameter gamma distribution function takes the form of,

$$P_{x,x+dx} = \frac{c^c}{\Gamma(c)} x^{c-1} e^{-cx} dx, \quad x > 0, \quad (6)$$

where the parameter $c > 1$, and $\Gamma(c)$ is the gamma function, defined as

$$\Gamma(c) = \int_0^\infty x^{c-1} e^{-cx} dx. \quad (7)$$

Note that the variance of the one-parameter gamma distribution is $1/c$. As the parameter c increases, the distribution becomes narrower, which is more suitable for modelling the tessellations having approximately similar grain sizes. In addition, there are two major advantages to using a one-parameter gamma distribution to describe the grain size distribution: Only one parameter c is involved in the relation for the tessellation's regularity, and the mean value of this distribution is one, which is the normalised mean grain size.

In [31], a series of statistical tests have been performed to summarise the relationship between the fitting parameter c and the regularity α , where α ranges from 0 to 0.8. In [32] and [33], a descriptive model was proposed based on the statistical data of [14], given by

$$\alpha = A(z(c) - z_0)^{k+nz(c)}, \quad c_0 \leq c \leq c_m \quad (8)$$

where $z(c) = c/c_m$, $z_0 = c_0/c_m$, $c_0 = 3.555$, $c_m = 47.524$, $A = 0.738895$, $k = 0.323911$ and $n = -0.414367$. Eq. (8) and Eq. (5) provide a mechanism to assign the control parameter by prescribing an intuitive grain-size distribution model with a distribution parameter c rather than the regularity parameter α .

The next step incorporates a set of traditional physical parameters to replace the distribution parameter for regularity assignment, by which all abstract parameters are avoided when assigning the input to the CPVT model. Considering a set of physical parameters $\{D_L, D_{mean}, D_R, P_r\}$ from the quantitative metallography, where D_{mean} is the mean grain size, defined as $D_{mean} = \frac{1}{N} \sum D_i$, D_L and D_R are two specific grain size values and P_r is the percentage of the grains with size in the range of $[D_L, D_R]$ over the total number of the grains N , i.e.,

$$P_r = \frac{1}{N} \sum m_i, \text{ where } m_i = \begin{cases} 1, & \text{if } D_i \in [D_L, D_R] \\ 0, & \text{otherwise} \end{cases}.$$

It should be noted that grain size D henceforth represents an area in two-dimension as in this study, and a volume in three-dimension.

When modelling grain distributions by a one-parameter gamma distribution, the set of parameters conform to the following equation:

$$P_r = \int_{x_1}^{x_2} \frac{c^c}{\Gamma(c)} x^{c-1} e^{-cx} dx, \quad (9)$$

where $x_1 = D_L/D_{mean}$, $x_2 = D_R/D_{mean}$ and $\Gamma(c)$ is a gamma function as in Eq. (7). Fig. 6 presents an example of a one-parameter gamma distribution with $c = 20$, where the area of the shaded part between the lower limit $x_1 = D_L/D_{mean}$ and upper limit $x_2 = D_R/D_{mean}$ equals the percentage $P_r = 0.635$.

It can be observed that by designating the set of physical parameters, the parameter c is correspondingly found by solving Eq. (9). However, there are still two major issues to be solved in order to utilise this scheme, which are: Conditions for which the parameter c is uniquely determined by Eq. (9), and an efficient numerical algorithm to solve Eq. (9).

3. Physical parameters

This section consists of two parts: First is the presentation of the condition for existence of a unique solution to Eq. (9), followed by an efficient algorithm for solving Eq. (9).

3.1 Uniqueness

Here *uniqueness* implies the uniqueness of the value of c obtained by solving Eq. (9). That is, given a set of physical parameters $\{D_L, D_{mean}, D_R, P_r\}$, there correspondingly exists a unique value of c characterising the one-parameter gamma distribution, describing the grain size distribution. Let,

$$\begin{cases} x_1 = 1 - \Delta_1, & 0 < \Delta_1 < 1 \\ x_2 = 1 + \Delta_2, & 0 < \Delta_2 < 1 \end{cases} \quad (10)$$

where x_1 and x_2 are the integral limits of Eq. (9). For the symmetric case where $\Delta_1 = \Delta_2 = \Delta$, $\bar{x} = (x_1 + x_2)/2 = 1$, which is also the mean value of a one-parameter gamma distribution.

Lemma 1. *There exists an interval $S^* = (x_1^*, x_2^*)$, such that for any interval $S = (x_1, x_2)$, where $x_1 < 1 < x_2$, if $S \subseteq S^*$, the implicit function*

$$P_r(c) = \int_{x_1}^{x_2} \frac{c^c}{\Gamma(c)} x^{c-1} e^{-cx} dx \quad (11)$$

is strictly monotonically increasing, as the parameter c increases for any $c \geq 1$. Moreover, the interval $S^ = (x_1^*, x_2^*)$ can be estimated by*

$$\begin{cases} x_1^* \approx 1 - \frac{1}{\sqrt{c}} + \mathcal{O}(\Delta^{3/2}) \\ x_2^* \approx 1 + \frac{1}{\sqrt{c}} \end{cases}, \quad (12)$$

where the term $\mathcal{O}(\Delta^{3/2}) > 0$.

Theorem 1. *Given the constants x_1, x_2 and the percentage value $P_r(x_1, x_2)|_c$, where $x_1 < 1 < x_2$, if the interval $S = [x_1, x_2] \subset S^* = (x_1^*, x_2^*)$, where x_1^* and x_2^* are determined from Eq. (12), the implicit function $P_r(c)$ in Eq.(11), defined over the domain $D(P_r) \subseteq [1, \infty)$ and range $R(P_r) \subseteq (0, 1)$, has the properties that:*

- $P_r(c)$ is a bijection;
- $P_r(c)$ has a continuous inverse $P_r^{-1}(c)$ on the range $R(P_r)$.

Lemma 1 and Theorem 1 explain the existence of a valid range of physical parameters, where uniqueness is satisfied. Proofs of Lemma 1 and Theorem 1 are given in the Appendix. This is realised by choosing a small grain size D_L , a large grain size D_R and a mean grain size D_{mean} , such that $S = [x_1, x_2] \subset S^* = (x_1^*, x_2^*)$. Then, the parameter c is uniquely determined by the percentage value P_r . Although the existence of such an interval of physical parameters that uniquely defines the c values has been proved, this interval, estimated by Eq. (12), is not large enough for all practical applications. In the following, efforts are made to extend the effective interval S^* .

3.1.1 Estimation of S^*

To estimate the interval S^* means to find a valid interval $S^* = (x_1^*, x_2^*)$ as large as possible such that $\frac{\partial P_r}{\partial c} > 0$. Since $S^* = (x_1^*, x_2^*) = (1 - \Delta_1^*, 1 + \Delta_2^*)$, to estimate the valid interval S^* is equivalent to finding possible large values of both Δ_1^* and Δ_2^* . For simplicity and without loss of generality, only a symmetrical situation is considered, where $\Delta_1 = \Delta_2 = \Delta$. Let the function $\varphi(\Delta)$ be

$$\varphi(c, \Delta) = \frac{\partial P_r(c, \Delta)}{\partial c} = \frac{c^c}{\Gamma(c)} \int_{1-\Delta}^{1+\Delta} x^{c-1} e^{-cx} [1 + \ln c - \psi(c) + \ln x - x] dx. \quad (13)$$

Furthermore, for any $c > 1$, let

$$\begin{cases} g_1(\Delta) = 1 + \ln c - \psi(c) + \ln(1 - \Delta) - (1 - \Delta) \\ g_2(\Delta) = 1 + \ln c - \psi(c) + \ln(1 + \Delta) - (1 + \Delta) \end{cases}, \quad (14)$$

and there exist $\tilde{\Delta}_1, \tilde{\Delta}_2 \in (0, 1)$ such that

$$\begin{cases} g_1(\tilde{\Delta}_1) = 0 \\ g_2(\tilde{\Delta}_2) = 0 \end{cases}. \quad (15)$$

Due to $0 < \tilde{\Delta}_1 < \tilde{\Delta}_2 < 1$, the property of $\varphi(c, \Delta)$ is studied with respect to three sub-intervals:

$$I_1 \cup I_2 \cup I_3 = (0, \tilde{\Delta}_1] \cup (\tilde{\Delta}_1, \tilde{\Delta}_2) \cup [\tilde{\Delta}_2, 1).$$

Lemma 2. *There exists a point $\Delta^* \in (\tilde{\Delta}_1, \tilde{\Delta}_2)$, where $\tilde{\Delta}_1$ and $\tilde{\Delta}_2$ are given by Eq. (15), such that for any $\Delta \in (0, \Delta^*]$, $\varphi(c, \Delta) > 0$. Moreover, the function $\varphi(c, \Delta)$ is strictly monotonically increasing for $\Delta \in (0, \Delta^*]$ and strictly monotonically decreasing for $\Delta \in [\Delta^*, 1)$.*

(Proof of Lemma 2 is given in the Appendix.) The shape of the function $\varphi(c, \Delta)$ is schematically illustrated in Fig. 7, where it can be observed that as Δ increases from 0 to Δ^* , $\varphi(\Delta)$ increases, starting from a positive value. But after Δ^* , as the variable Δ increases, the function value $\varphi|_{\Delta > \Delta^*}$ decreases correspondingly. Then

$$\min_{\Delta^* < \Delta < 1} \varphi(\Delta) = \lim_{\Delta \rightarrow 1} \varphi(\Delta). \quad (16)$$

In this situation, the asymptotic value of $\lim_{\Delta \rightarrow 1} \varphi(\Delta)$ is critical, that is, if $\lim_{\Delta \rightarrow 1} \varphi(\Delta) > 0$, then the interval S^* is such that $S^* = (0, 2)$.

Table 1 was calculated by means of the Gaussian quadrature method using the arbitrary precision package ARPREC [40]. From the numerical results, it can be verified that for any $\Delta \in [0, 0.999)$ and $c \in [1, 90]$, $\varphi(c, \Delta) > 0$ is satisfied. From the descriptive model of Eq. (8), the c value only ranges from c_0 to c_m , therefore this numerical result is sufficient for practical use. Hence the estimation of $S^* = [0.001, 1.999]$ is achieved, where the mapping from the percentage value P_r to the distribution function parameter c is one to one.

3.1.2 Lower bound on P_r

The preceding discussion shows that given $x_1 = D_L/D_{mean}$ and $x_2 = D_R/D_{mean}$ within the interval given by Eq. (12), the function value $P_r(c, x_1, x_2)$ is monotonically increasing as c increases. On the other hand, the P_r value cannot be arbitrarily small due to the requirement of modelling grain size distributions, that is, a relaxation condition to determine the lower bound of P_r is derived based on $c \geq 1$. Therefore, the lower bound for the percentage $P_r(c, x_1, x_2)$ is given by,

$$P_r(1, x_1, x_2) = e^{-x_1} - e^{-x_2}. \quad (17)$$

For the symmetrical case, i.e., $x_1 = 1 - \Delta$ and $x_2 = 1 + \Delta$, the lower bound is determined by

$$P_r(1, \Delta) = e^{\Delta-1} - e^{-\Delta-1}, \quad (18)$$

where, $\Delta \in [0, 0.999)$.

3.2 Algorithm to solve the c value

In [32], [33] and [41], the c value is determined by means of exhaustive enumeration starting from 1 with a prescribed incremental step, such as 0.001. Since each iterative step involves a series of computations including one numerical integration, this searching scheme is fairly inefficient. To improve the solution procedure, an efficient gradient search method is proposed as follows. Given the four input parameters, D_L , D_{mean} , D_R and P_r , the following equation must be solved for c ,

$$P_r = \int_{D_L/D_{mean}}^{D_R/D_{mean}} \frac{c^c}{\Gamma(c)} x^{c-1} e^{-cx} dx \triangleq F(c), \quad (19)$$

where the constant $\Gamma(c)$ is calculated by Eq. (7). A Newton-Raphson method can be used to obtain the c value as follows. Let

$$f(c) = \int_{D_L/D_{mean}}^{D_R/D_{mean}} \frac{c^c}{\Gamma(c)} x^{c-1} e^{-cx} dx - P_r, \quad (20)$$

then,

$$f'(c) = \int_{D_L/D_{mean}}^{D_R/D_{mean}} \frac{c^c}{\Gamma(c)} x^{c-1} e^{-cx} [1 + \ln(c) - \psi(c) + \ln(x) - x] dx, \quad (21)$$

and the iterative root finding procedure is

$$c_{i+1} = c_i - \frac{f(c)}{f'(c)}, \quad (22)$$

where $i = 1, 2, \dots$. Based on the preceding discussion, the denominator is always non-zero. Since all the distributions are described by $c \geq c_0$, the searching process starts at $c = c_0$. This process continues until the prescribed tolerance, ε , is achieved, where the termination condition is formulated in terms of the successive change as

$$|c_{i+1} - c_i| \leq \varepsilon. \quad (23)$$

4. VGRAIN system and micromechanics simulation

To facilitate grain structure generation and micro-mechanics modelling, an integrated system called VGRAIN has been developed to build materials microstructures, where the proposed CPVT model has been implemented to define the grain structures. The integrated process of defining the microstructure of the material is illustrated in Fig. 8. Two more modules have also been developed to include grain orientation and material properties assignment. The orientation of each grain can be assigned based on a fixed texture, or be set by a random value from a random number generator based on a uniform distribution or a normal distribution. Grain orientations can also be defined according to measurements, such as EBSD. In the VGRAIN system, the generated grain structure

together with the grain orientations can be directly imported into commercially available FE codes, e.g., ABAQUS/CAE, for further pre-processing operations, such as meshing, boundary and loading conditions defined based on the simulation requirements. Crystal plasticity constitutive equations as in Wang et al. [5] were implemented in the commercial FE code ABAQUS/EXPLICIT through the user defined material subroutine VUMAT. The detailed implementation and CPFE analysis procedures are presented in [5].

To demonstrate the proposed CPVT model and material properties definition procedure in the VGRAIN system, 2D plane strain CPFE analyses of uniaxial tension have been performed. It is worth noting that singly-, doubly- or triply-periodic boundary conditions can be prescribed for representative volume elements with grain structures generated by VGRAIN, although this has not been automated in the present version to maintain generality. The crystal plasticity calibration of [2] for 316L stainless steel is used here. The crystal plasticity is not the focus of this study; details of the calculations can be found in [5]. The overall dimensions of the microfilm workpiece are $100\text{ }\mu\text{m} \times 30\text{ }\mu\text{m}$ and a displacement of $U = 80\text{ }\mu\text{m}$ is applied at the right edge of the model and the lateral faces are free of constraint. The overall setup is shown in Fig. 9.

Two specimens were generated with different regularities: One was much more regular than the other. The physical parameters and the corresponding distribution parameters from the CPVT model are given in Table 2. Both microstructures have the same mean grain size of $50\text{ }\mu\text{m}^2$, in terms of area, i.e., the equivalent grain diameter is approximately $8\text{ }\mu\text{m}$ assuming a circular grain shape. By assigning different physical parameters, different regularities were achieved using the CPVT model. The simulated irregular and regular grain structures are presented in (a) and (d) of Fig. 10, respectively. It should be noted that repeated application of the same physical parameters using the CPVT model will result in slightly different grain structures, but all the simulated grain structures have the feature that the grain sizes are statistically conformal with the specified physical parameters.

Fig. 10 shows CPFE simulations for both microstructures, where (a) – (c) show the irregular grain structure and (d) – (f) show the regular grain-structure. Every simulation involves three major steps: definition of the grain structure as shown in (a) and (d), assignment of material properties, mesh and boundary conditions, as illustrated in (b) and (e), and post-processing and analysis as in (c) and (f). The deformed models are presented in (c) and (f) of Fig. 10, where contours of accumulated plastic strain (ε_p) are shown and the necking features of both models can be observed.

Fig. 11 correlates the necking regions with the original microstructures. It was found in [5] that necking caused by strain localization is increasingly prohibited by a greater number of grains through the specimen width. Although strain localization necking is delayed until greater applied strain when the number of grains through the specimen width is greater, the onset of necking in that case was demonstrated to be sudden with rapid progression towards a high level of thinning. The grain structures shown in Figs. 10 and 11 have the same average grain size. However, the regular grain structure has approximately the same number of grains through the specimen width at any location along the length, whereas the irregular grain structure has between two and seven grains through the width. Although necking by strain localization was shown in [5] to occur in locations with fewer grains through the width, the situation shown here is distinctly different in that only regular grain patterns were simulated in [5]. In the case of an irregular grain pattern, although there may be a location with relatively few grains through the specimen width, strain localization necking also requires that those grains have crystallographic orientations favorable to slip, i.e. there must be at least one slip system available having a relatively high Schmid factor under the applied loading. For a specimen with a regular grain pattern having, e.g., an average of two grains through the specimen width, there is statistically a much higher (depending on the specimen aspect ratio) likelihood there will be a location along the length with grains oriented such that they are favorable to slip, compared to a specimen with an irregular grain pattern having a higher mean grain size but also one or more locations along the length with two grains through the specimen width. Hence, there is a greater statistical variation in the necking response for the film shown in Fig. 11 (c) and (d) than for that in (a) and (b). The necking zones (NZ) shown in Fig. 11 indicate that, for the strain shown which is quite extreme, the NZ with more grains through the width, given by (a) and (b), actually necked more than the NZ give by (c) and (d). However, this can be understood by the previous discussion in that either the grains in the NZ of the irregular grain pattern were oriented in a way not favorable to crystallographic slip, compared to those in the NZ of the regular grain pattern, or, the level of applied strain was sufficient for the sudden onset of necking and rapid thinning demonstrated in [5] to occur in the regular grain pattern such that it overcame the more gradual necking in the irregular grain pattern (in the latter case, the degree of necking in the irregular grain pattern would have been greater than that in the regular grain pattern for some smaller value of applied strain).

5. Conclusion

In this work, a controlled Poisson Voronoi tessellation model, $CPVT(\delta|\Omega, N_{seed})$, has been proposed to generate virtual polycrystalline grain structures with emphasis on regularity control. The model

extends the traditional Poisson Voronoi tessellation by substitution of point seeds with circular seeds having a given diameter δ . Under the condition of no circles overlapping, the regularity of the resultant tessellation can be varied from a purely random PVT to its equivalent regular hexagonal tessellation. The CPVT model first takes the workpiece-related parameters to derive an equivalent RHT. By specifying a regularity value, the control parameter δ is determined, which is employed by the CPVT model to generate the grain structure. Utility of the CPVT model in materials modelling application relies on correlating physical measurements of real microstructures obtained by quantitative metallography to the otherwise abstract regularity value. By discovery of an integrated scheme for identifying the regularity value from the physical parameters input, the CPVT model can now be fully operated based upon real microstructures data.

Two essential relationships have been established: 1) The one-parameter gamma distribution model linking the regularity α , with the distribution parameter c , and 2) the correlation of a set of four physical parameters with the distribution parameter c . This integration allows the CPVT model to directly generate a tessellation that is statistically analogous to a grain distribution defined by user input.

Mathematical proof of uniqueness of the solution was performed by identifying a small valid interval, which was then extended into a larger region that fully satisfies the application requirements. Further, a series of computational results were presented to validate the uniqueness assumption of the proposed scheme. Meanwhile, to facilitate the CPVT model definition, a numerical algorithm was proposed to efficiently solve Eq. (9).

The VGRAIN software system has been developed to implement the proposed CPVT model and solution scheme to generate microstructures for crystal plasticity finite element analyses particularly using ABAQUS. By assigning different physical parameters, corresponding grain structures were obtained. To demonstrate applications of the proposed CPVT model and integrated grain structure generation scheme, two plane strain CPFE analyses have been performed. Simulation results showed the influence of grain regularity on the mechanical behaviour, and strain localisation on the necking behaviour.

Reference

- [1] R. Asaro, J. Rice, Strain localization in ductile single crystals, *Journal of the Mechanics and Physics of Solids* 25 (5) (1977) 309–338.
- [2] F. Harewood, P. McHugh, Investigation of finite element mesh independence in rate dependent materials, *Computational Materials Science* 37 (4) (2006) 442–453.
- [3] D. Balint, V. Deshpande, A. Needleman, E. Van der Giessen, Discrete dislocation plasticity analysis of the grain size dependence of the flow strength of polycrystals, *International Journal of Plasticity* 24 (12) (2008) 2149–2172.
- [4] D. Balint, V. Deshpande, A. Needleman, E. Giessen, Size effects in uniaxial deformation of single and polycrystals: a discrete dislocation plasticity analysis, *Modelling and Simulation in Materials Science and Engineering* 14 (2006) 409–422.
- [5] S. Wang, W. Zhuang, D. Balint, J. Lin, A crystal plasticity study of the necking of micro-films under tension, *Journal of Multiscale Modelling* 3 (4) (2009) 331–345.
- [6] J. Spowart, H. Mullens, B. Puchala, Collecting and analyzing microstructures in three dimensions: A fully automated approach, *JOM* 55 (10) (2003) 35–37.
- [7] R. S. Sidhu, N. Chawla, Three-dimensional microstructure characterization of Ag₃Sn intermetallics in Sn-rich solder by serial sectioning, *Materials Characterization* 52 (3) (2004) 225–230.
- [8] J. E. Spowart, Automated serial sectioning for 3-D analysis of microstructures, *Scripta Materialia* 55 (1) (2006) 5–10.
- [9] L. Rauch, L. Madej, Application of the automatic image processing in modelling of the deformation mechanisms based on the digital representation of microstructure, *International Journal for Multiscale Computational Engineering* 8 (3) (2010) 343–356.
- [10] D. Raabe, M. Sachtleber, Z. Zhao, F. Roters, S. Zaefferer, Micromechanical and macromechanical effects in grain scale polycrystal plasticity experimentation and simulation, *Acta Materialia* 49 (17) (2001) 3433–3441.
- [11] J. Den Toonder, J. Van Dommelen, F. Baaijens, Relation between single crystal elasticity and the effective elastic behaviour of polycrystalline materials: Theory, measurement and computation, *Modelling and Simulation in Materials Science and Engineering* 7 (6) (1999) 909–928.
- [12] A. Lewis, A. Geltmacher, Image-based modeling of the response of experimental 3D microstructures to mechanical loading, *Scripta materialia* 55 (1) (2006) 81–85.
- [13] Y. Bhandari, S. Sarkar, M. Groeber, M. Uchic, D. Dimiduk, S. Ghosh, 3D polycrystalline microstructure reconstruction from FIB generated serial sections for FE analysis, *Computational Materials Science* 41 (2) (2007) 222–235.

- [14] M. Groeber, S. Ghosh, M. Uchic, D. Dimiduk, A framework for automated analysis and simulation of 3D polycrystalline microstructures. part 1: Statistical characterization, *Acta Materialia* 56 (6) (2008) 1257–1273.
- [15] A. D. Rollett, S.-B. Lee, R. Campman, G. Rohrer, Three-dimensional characterization of microstructure by electron back-scatter diffraction, *Annual Review of Materials Research* 37 (1) (2007) 627–658.
- [16] H. Poulsen, S. Nielsen, E. Lauridsen, S. Schmidt, R. Suter, U. Lienert, L. Margulies, T. Lorentzen, J. Jensen, Three-dimensional maps of grain boundaries and the stress state of individual grains in polycrystals and powders, *Journal of applied crystallography* 34 (6) (2001) 751–756.
- [17] H. Poulsen, 3DXRD - a new probe for materials science, Ph.D. thesis, Risø National Laboratory, Roskilde, Denmark (2004).
- [18] S. Kalidindi, C. Bronkhorst, L. Anand, Crystallographic texture evolution in bulk deformation processing of FCC metals, *Journal of Mechanics and Physics of Solids* 40 (1992) 537–569.
- [19] G. Sarma, P. Dawson, Effects of interactions among crystals on the inhomogeneous deformations of polycrystals, *Acta Materialia* 44 (5) (1996) 1937–1953.
- [20] D. Mika, P. Dawson, Effects of grain interaction on deformation in polycrystals, *Materials Science and Engineering A* 257 (1) (1998) 62–76.
- [21] L. Delannay, P. J. Jacques, S. R. Kalidindi, Finite element modeling of crystal plasticity with grains shaped as truncated octahedrons, *International Journal of Plasticity* 22 (10) (2006) 1879–1898.
- [22] H. Ritz, P. R. Dawson, Sensitivity to grain discretization of the simulated crystal stress distributions in FCC polycrystals, *Modelling and Simulation in Materials Science and Engineering* 17 (1) (2009) 1–21.
- [23] O. Ivasishin, S. Shevchenko, S. Semiatin, Implementation of exact grain-boundary geometry into a 3-D Monte-Carlo (potts) model for microstructure evolution, *Acta Materialia* 57 (9) (2009) 2834–2844.
- [24] A. Brahme, M. Alvi, D. Saylor, J. Fridy, A. Rollett, 3D reconstruction of microstructure in a commercial purity aluminum, *Scripta Materialia* 55 (1) (2006) 75–80.
- [25] L. Chen, Novel computer simulation technique for modeling grain growth, *Scripta Metallurgica et Materialia* 32 (1995) 115–120.
- [26] R. Logé, M. Bernacki, H. Resk, L. Delannay, H. Dignonnet, Y. Chastel, T. Coupez, Linking plastic deformation to recrystallization in metals using digital microstructures, *Philosophical Magazine* 88 (30) (2008) 3691–3712.
- [27] M. Bernacki, H. Resk, T. Coupez, R. E. Logé, Finite element model of primary recrystallization in polycrystalline aggregates using a level set framework, *Modelling and Simulation in Materials Science and Engineering* 17 (6) (2009) 064006.

- [28] B. Boots, The arrangement of cells in random networks, *Metallography* 15 (1) (1982) 53–62.
- [29] D. Aboav, The arrangement of grains in a polycrystal, *Metallography* 3 (4) (1970) 383–390.
- [30] J. Lemaitre, A. Gervois, J. Troadec, N. Rivier, M. Ammi, L. Oger, D. Bideau, Arrangement of cells in Voronoi tessellations of monosize packing of discs, *Philosophical Magazine B* 67 (3) (1993) 347–362.
- [31] H. X. Zhu, S. M. Thorpe, A. H. Windle, The geometrical properties of irregular two-dimensional Voronoi tessellations, *Philosophical Magazine A* 81 (12) (2001) 2765–2783.
- [32] K. C. Ho, N. Zhang, J. Lin, T. A. Dean, An integrated approach for virtual microstructure generation and micromechanics modelling for micro-forming simulation, in: *Proceedings of ASME MNC2007*, 2007.
- [33] J. Cao, W. Zhuang, S. Wang, K. Ho, N. Zhang, J. Lin, T. Dean, An integrated crystal plasticity FE system for microforming simulation, *Journal of Multiscale Modelling* 1 (2009) 107–124.
- [34] P. Zhang, J. Lin, D. Balint, An integrated scheme for CPFE simulation: Implementation and case studies, Submitted to *philosophical magazine*.
- [35] A. Hinde, R. Miles, Monte Carlo estimates of the distributions of the random polygons of the Voronoi tessellation with respect to a Poisson process, *Journal of Statistical Computation and Simulation* 10 (3) (1980) 205–223.
- [36] S. Kumar, S. K. Kurtz, Properties of a two-dimensional Poisson-Voronoi tessellation: A Monte-Carlo study, *Materials Characterization* 31 (1) (1993) 55–68.
- [37] S. Kumar, S. Kurtz, J. Banavar, M. Sharma, Properties of a three-dimensional Poisson-Voronoi tessellation: A Monte Carlo study, *Journal of statistical physics* 67 (3) (1992) 523–551.
- [38] D. Weaire, J. Kermode, J. Wejchert, On the distribution of cell areas in a Voronoi network, *Philosophical Magazine B* 53 (5) (1986) 101–105.
- [39] J. Wejchert, D. Weaire, J. P. Kermode, Monte Carlo simulation of the evolution of a two-dimensional soap froth, *Philosophical Magazine B* 53 (1) (1986) 15–24.
- [40] D. Bailey, H. Yozo, X. Li, B. Thompson, ARPREC: An arbitrary precision computation package, Tech. rep., Lawrence Berkeley National Laboratory (2002).
- [41] J. Cao, W. Zhuang, S. Wang, J. Lin, Development of a VGRAIN system for CPFE analysis in micro-forming applications, *The International Journal of Advanced Manufacturing Technology* 47 (2010) 981–991.
- [42] H. Alzer, On some inequalities for the gamma and psi functions, *Mathematics of Computation* 66 (217) (1997) 373–389.

Appendix

Proof of Lemma 1

Consider a function $P_r(c, x_1, x_2)$, where $c \geq 1$ and $0 < x_1 < 1 < x_2$. The partial derivate of P_r with respect to the parameter c is computed as,

$$\frac{\partial P_r}{\partial c} = \frac{\partial}{\partial c} \left(\frac{c^c}{\Gamma(c)} \right) \int_{x_1}^{x_2} x^{c-1} e^{-cx} dx + \frac{c^c}{\Gamma(c)} \frac{\partial}{\partial c} \left(\int_{x_1}^{x_2} x^{c-1} e^{-cx} dx \right).$$

Since $(c^c)' = c^c(1 + \ln c)$ and

$$\psi(c) = \frac{\Gamma'(c)}{\Gamma(c)},$$

where $\psi(c)$ is the digamma function defined as the logarithmic derivative of the gamma function, then

$$\frac{\partial P_r}{\partial c} = \frac{c^c}{\Gamma(c)} \int_{x_1}^{x_2} x^{c-1} e^{-cx} [1 + \ln c - \psi(c) + \ln x - x] dx. \quad (24)$$

Let $g(x) = 1 + \ln c - \psi(c) + \ln x - x$. Note that $x^{c-1} e^{-cx} > 0$ is always satisfied for any $x \in S$.

Then there is a sufficient condition that if $g(x) > 0$, then $\frac{\partial P_r}{\partial c} > 0$.

For the term $\ln c - \psi(c)$, the inequality of

$$\frac{1}{2c} < \ln c - \psi(c) < \frac{1}{c} \quad (25)$$

holds (see [42]). Thus, $g(x) > 1 + \frac{1}{2c} + \ln x - x$. To find a valid interval $S^* = (x_1^*, x_2^*)$ such that $g(x) > 0$, two subintervals $S_1^* = (x_1^*, 1]$ and $S_2^* = (1, x_2^*)$ are to be calculated respectively, where $x_1^* = 1 - \Delta_1^*$ and $x_2^* = 1 + \Delta_2^*$.

Note that, $\ln(1 + \Delta) = \Delta - \frac{\Delta^2}{2} + \frac{\Delta^3}{3} - \frac{\Delta^4}{4} + \dots > \Delta - \frac{\Delta^2}{2}$, where $1 > \Delta > 0$. Thus, for $x_2 = 1 + \Delta \in S_2^*$,

$$\begin{aligned} g(x) &= 1 + \ln c - \psi(c) + \ln(1 + \Delta) - (1 + \Delta) \\ &> 1 + \frac{1}{2c} + \left(\Delta - \frac{\Delta^2}{2} \right) - (1 + \Delta) = \frac{1}{2c} - \frac{\Delta^2}{2}. \end{aligned}$$

So, $\Delta_2^* = c^{-1/2}$ and $S_2^* = (1, 1 + c^{-1/2})$ such that $g(x) > 0$, for $x \in S_2^*$.

Next for the interval S_1^* , the function $g(x)$ is differentiable. Based on Eq. (25), $g(1) > \ln c - \psi(c) > 0$, and hence there exists $\Delta > 0$, such that $g(x) > 0$, where $x \in (1 - \Delta, 1]$. Since $\ln(1 - \Delta) = -\Delta - \frac{\Delta^2}{2} - \frac{\Delta^3}{3} - \frac{\Delta^4}{4} - \dots$,

$$\begin{aligned}
g(x) &= 1 + \ln c - \psi(c) + \ln(1 - \Delta) - (1 - \Delta) \\
&> 1 + \frac{1}{2c} + \left(-\Delta - \frac{\Delta^2}{2} - \mathcal{O}(\Delta^3) \right) - (1 - \Delta) \\
&= \frac{1}{2c} - \frac{\Delta^2}{2} - \mathcal{O}(\Delta^3).
\end{aligned}$$

Thus, for $\Delta \leq c^{-1/2} - \mathcal{O}(\Delta^{3/2})$, $g(x) > 0$ and then $\Delta_1^* = c^{-1/2} - \mathcal{O}(\Delta^{3/2})$

In summary, $\forall x \in S^* = (x_1^*, x_2^*) = S_1^* \cup S_2^*$, $g(x) > 0$, where

$$\begin{cases} x_1^* = 1 - \Delta_1^* \approx 1 - \frac{1}{\sqrt{c}} + \mathcal{O}(\Delta^{3/2}) \\ x_2^* = 1 + \Delta_2^* \approx 1 + \frac{1}{\sqrt{c}} \end{cases}. \quad (26)$$

A conclusion, from Eq. (24), is the result that for any $(x_1, x_2) \subset S^*$ and $x_1 < 1 < x_2$, $\frac{\partial P_r}{\partial c} > 0$, i.e., $P_r(c, x_1, x_2)$ monotonically increases as c increases.

Proof of Theorem 1

Lemma 1 shows that provided $x_1, x_2 \in S^*$ where $x_1 < 1 < x_2$ and $S^* = (x_1^*, x_2^*)$ defined by Eq. (12), $\frac{\partial P_r}{\partial c} > 0$, i.e., the percentage value $P_r(x_1, x_2)|_c$ monotonically increases as c increases. Thus, the function $P_r(c)$ is a one-to-one mapping with the domain $D(P_r) = S^*$. Also, $P_r(c)$ has a continuous inverse $P_r^{-1}(c)$ on the range $R(P_r)$.

Proof of Lemma 2

For functions $g_1(\Delta)$ and $g_2(\Delta)$ in Eq. (14), the derivatives,

$$\begin{cases} g_1'(\Delta) = \frac{-\Delta}{1 - \Delta} \\ g_2'(\Delta) = \frac{-\Delta}{1 + \Delta} \end{cases}, \quad (27)$$

are negative, i.e., they are decreasing on interval $(0,1)$. Moreover, let $\tilde{\Delta}_1, \tilde{\Delta}_2 > 0$ such that Eq. (15) is satisfied. Note that, for $c \geq c_0$ (Eq. (8)), there are always $\tilde{\Delta}_1, \tilde{\Delta}_2 \in (0,1)$.

In the following, the property of $\varphi(c, \Delta)$ is studied with three intervals, $I_1 \cup I_2 \cup I_3 = (0, \tilde{\Delta}_1] \cup (\tilde{\Delta}_1, \tilde{\Delta}_2) \cup [\tilde{\Delta}_2, 1)$, respectively. The derivative $\varphi(\Delta)$ with respect to Δ is computed as

$$\begin{aligned}
\frac{\partial \varphi(c, \Delta)}{\partial \Delta} &= \frac{c^c}{\Gamma(c)} \{ (1 - \Delta)^{c-1} e^{-c(1-\Delta)} \cdot [1 + \ln c - \psi(c) + \ln(1 - \Delta) - (1 - \Delta)] \\
&\quad + (1 + \Delta)^{c-1} e^{-c(1+\Delta)} \cdot [1 + \ln c - \psi(c) + \ln(1 + \Delta) - (1 + \Delta)] \}, \quad (28)
\end{aligned}$$

and let

$$\begin{cases} m_1(\Delta) = (1 - \Delta)^{c-1} e^{-c(1-\Delta)} \\ m_2(\Delta) = (1 + \Delta)^{c-1} e^{-c(1+\Delta)} \end{cases} \quad (29)$$

where $m_1(\Delta) > 0$ and $m_2(\Delta) > 0$ for all $\Delta \in (0,1)$. Together with the notation in Eq. (14), it has

$$\frac{\partial \varphi(c, \Delta)}{\partial \Delta} = \frac{c^c}{\Gamma(c)} (m_1(\Delta) g_1(\Delta) + m_2(\Delta) g_2(\Delta)). \quad (30)$$

Obviously, for $\Delta \in I_1 = (0, \tilde{\Delta}_1]$, $g_1(\Delta) \geq 0$ and $g_2(\Delta) > 0$, and hence $\frac{\partial \varphi(c, \Delta)}{\partial \Delta} > 0$. Therefore, $\varphi(\Delta)$ is monotonically increasing on the interval $I_1 = (0, \tilde{\Delta}_1]$. In contrast, for $\Delta \in I_3 = [\tilde{\Delta}_2, 1)$, $g_1(\Delta) < 0$ and $g_2(\Delta) \leq 0$, and thus, $\frac{\partial \varphi(c, \Delta)}{\partial \Delta} < 0$. Thus, $\varphi(\Delta)$ is monotonically decreasing on the interval I_3 .

Consider the property of $\frac{\partial \varphi(c, \Delta)}{\partial \Delta}$ on $I_2 = (\tilde{\Delta}_1, \tilde{\Delta}_2)$, where $g_1(\Delta) < 0$ and $g_2(\Delta) > 0$. $m_1(\Delta)$ and $m_2(\Delta)$ in (29) have relation of $m_1(\Delta) > m_2(\Delta) > 0$, for $\Delta \in (0, \tilde{\Delta}_2)$. From Eq. (30), it can be derived that

$$\frac{\partial \varphi(c, \Delta)}{\partial \Delta} < \frac{c^c}{\Gamma(c)} m_1(\Delta) (g_1(\Delta) + g_2(\Delta)).$$

In addition, $g_1(\tilde{\Delta}_1) + g_2(\tilde{\Delta}_1) > 0$ and $g_1(\tilde{\Delta}_2) + g_2(\tilde{\Delta}_2) < 0$. There exists $\bar{\Delta} \in (\tilde{\Delta}_1, \tilde{\Delta}_2)$, such that $g_1(\bar{\Delta}) + g_2(\bar{\Delta}) = 0$. From Eq. (27), it has $g'_1(\Delta) < g'_2(\Delta) < 0$, for all $\Delta \in I_2$. Therefore, for $\bar{\Delta} < \Delta < \tilde{\Delta}_2$, $g_1(\Delta) + g_2(\Delta) < 0$, and hence $\frac{\partial \varphi(c, \Delta)}{\partial \Delta} < 0$.

For $\tilde{\Delta}_1 < \Delta \leq \bar{\Delta}$, the second derivative of $\varphi(c, \Delta)$ has

$$\frac{\partial^2 \varphi(c, \Delta)}{\partial \Delta^2} = \frac{c^c}{\Gamma(c)} \cdot (m'_1(\Delta) g_1(\Delta) + m_1(\Delta) g'_1(\Delta) + m'_2(\Delta) g_2(\Delta) + m_2(\Delta) g'_2(\Delta)). \quad (31)$$

Due to

$$m'_2(\Delta) = \frac{-1-c\Delta}{1+\Delta} m_2 < 0,$$

And hence the term

$$m'_2(\Delta) g_2(\Delta) + m_2(\Delta) g'_2(\Delta) < 0.$$

In addition, the term

$$m'_1(\Delta) g_1(\Delta) + m_1(\Delta) g'_1(\Delta) = m_1(\Delta) \left[\frac{1}{1-\Delta} ((1-c\Delta) g_1(\Delta) - \Delta) \right]$$

is negative if and only if

$$\rho(\Delta) = (1 - c\Delta)g_1(\Delta) - \Delta < 0.$$

Note that, for $\Delta = \bar{\Delta}$, it has $g_1(\bar{\Delta}) + g_2(\bar{\Delta}) = 0$. It can be derived that

$$\ln c - \psi(c) = \frac{\bar{\Delta}^2}{2} + \frac{\bar{\Delta}^4}{4} + \dots.$$

From Eq. (25),

$$\frac{1}{2c} < \frac{\bar{\Delta}^2}{2} + \frac{\bar{\Delta}^4}{4} + \dots < \frac{1}{c}.$$

Then,

$$\begin{aligned} \rho(\bar{\Delta}) &= (c\bar{\Delta} - 1) \left(\frac{\bar{\Delta}^3}{3} + \frac{\bar{\Delta}^5}{5} + \dots \right) - \bar{\Delta} \\ &< \left(\frac{2}{\bar{\Delta}} - 1 \right) \left(\frac{\bar{\Delta}^3}{3} + \frac{\bar{\Delta}^5}{5} + \dots \right) - \bar{\Delta} \\ &= -\bar{\Delta} + \frac{2\bar{\Delta}^2}{3} - \frac{\bar{\Delta}^3}{3} + \dots. \end{aligned}$$

Thus $\rho(\bar{\Delta}) < 0$. Moreover, since $\rho(\tilde{\Delta}_1) < 0$ and $\rho(\Delta)'' > 0$, it can be obtained that $\rho(\Delta) < 0$, for $\tilde{\Delta}_1 < \Delta \leq \bar{\Delta}$. Therefore, $\frac{\partial^2 \varphi(c, \Delta)}{\partial \Delta^2} < 0$, for $\tilde{\Delta}_1 < \Delta \leq \bar{\Delta}$, i.e., $\frac{\partial \varphi(c, \Delta)}{\partial \Delta}$ monotonically decreases on the interval $(\tilde{\Delta}_1, \bar{\Delta}]$. Additionally, $\frac{\partial \varphi(c, \Delta)}{\partial \Delta} > 0$ for $\Delta \in (0, \tilde{\Delta}_1]$ and $\frac{\partial \varphi(c, \Delta)}{\partial \Delta} < 0$ for $\Delta \in (\tilde{\Delta}_1, \bar{\Delta}]$, hence there exist $\Delta^* \in (\tilde{\Delta}_1, \bar{\Delta}] \subset (\tilde{\Delta}_1, \tilde{\Delta}_2)$ such that $\frac{\partial \varphi(c, \Delta^*)}{\partial \Delta} = 0$.

In conclusion, there exist $\Delta^* \in I_2$, such that

1. $\frac{\partial \varphi(c, \Delta^*)}{\partial \Delta} = 0$, $\Delta^* \in (\tilde{\Delta}_1, \tilde{\Delta}_2)$;
2. $\frac{\partial \varphi(c, \Delta)}{\partial \Delta} > 0$, for $0 < \Delta < \Delta^*$;
3. $\frac{\partial \varphi(c, \Delta)}{\partial \Delta} < 0$, for $\Delta^* < \Delta < 1$.

That is, the function $\varphi(c, \Delta)$ strictly monotonically increases for $\Delta \in (0, \Delta^*]$ and strictly monotonically decreases for $\Delta \in [\Delta^*, 1)$.

Table 1. Asymptotic behaviour of $\varphi(c, \Delta)|_{\Delta=0.999}$.

c	φ	c	φ	c	φ	c	φ	c	φ	c	φ
1	5.61E-02	100	2.89E-47	200	8.63E-91	300	2.23E-134	400	6.23E-178	500	1.86E-221
10	6.26E-08	110	1.34E-51	210	3.77E-95	310	9.79E-139	410	2.76E-182	510	8.26E-226
20	5.76E-13	120	6.10E-56	220	1.64E-99	320	4.31E-143	420	1.22E-186	520	3.68E-230
30	1.80E-17	130	2.74E-60	230	7.18E-104	330	1.90E-147	430	5.43E-191	530	1.64E-234
40	7.70E-22	140	1.22E-64	240	3.14E-108	340	8.37E-152	440	2.41E-195	540	7.30E-239
50	5.68E-26	150	5.38E-69	250	1.37E-112	350	3.69E-156	450	1.07E-199	550	3.25E-243
60	3.86E-30	160	2.36E-73	260	6.01E-117	360	1.63E-160	460	4.75E-204	560	1.45E-247
70	2.27E-34	170	1.04E-77	270	2.63E-121	370	7.20E-165	470	2.11E-208	570	6.47E-252
80	1.21E-38	180	4.53E-82	280	1.15E-125	380	3.18E-169	480	9.38E-213	580	2.89E-256
90	6.04E-43	190	1.98E-86	290	5.07E-130	390	1.41E-173	490	4.17E-217	590	1.29E-260

Table 2. Physical parameters and corresponding grain structure properties for the two microstructures.

Label	Physical parameters (μm^2)				Equivalent grain size [†] (μm)			CPVT model parameters			
	D_{mean}	D_L	D_R	P_r	d_{mean}	d_L	d_R	d_{reg} (μm)	α	δ (μm)	N
irregular	50	20	80	79%	7.6	4.8	9.6	7.6	0.156	1.18	60
regular	50	30	70	95%	7.6	5.9	9.0	7.6	0.666	5.06	60

[†] Assuming a hexagonal grain shape.

Fig. 1. Illustration of an integrated process for micromechanics FE simulations.

Fig. 2. Schematic pattern of a controlled Poisson Voronoi tessellation, where all seeds have identical diameter δ and the control parameter is equal to the diameter, and the seed distance $d(g, a) = \delta$ and $d(g, j) > \delta$, where $j = b, c, \dots, f$.

Fig. 3. The integrated scheme with CPVT model for grain structure generation.

Fig. 4. Illustration of the effect of external seeds on the number of grains. (a) A case accounting for external seeds; (b) a case neglecting external seeds.

$\alpha = 0.1$

$\alpha = 0.4$

$\alpha = 0.7$

$\alpha = 1$

Fig. 5. Controlled Poisson Voronoi tessellations with different regularity parameters.

Fig. 8. The virtual microstructure generation system (VGRAIN) for micro-mechanics modelling.

Fig. 9. Schematic diagram for the plane strain CPFE model.

Fig. 10. CPFE simulations for regular and irregular grain structures.

Fig. 11. Comparison of local deformation for both grain structures.