1 Polymer-assisted modification of metal-organic
2 framework MIL-96 (Al): influence of HPAM
3 concentration on particle size, crystal morphology and
4 removal of harmful environmental pollutant PFOA

5 *Luqman Hakim Mohd Azmi^{a,b,c}, Daryl Williams^c, Bradley P. Ladewig^{a,d,*}*

6 ^aBarrer Centre, Department of Chemical Engineering, Imperial College London, South
7 Kensington Campus, SW7 2AZ, London, United Kingdom.

8 ^bGrantham Institute – Climate Change and the Environment, Imperial College London, South
9 Kensington Campus, SW7 2AZ, London, United Kingdom.

10 ^cSurfaces and Particle Engineering Laboratory (SPEL), Department of Chemical Engineering,
11 Imperial College London, South Kensington Campus, SW7 2AZ, London, United Kingdom.

12 ^d Institute for Micro Process Engineering (IMVT), Karlsruhe Institute of Technology, Hermann-
13 von-Helmholtz-Platz 1, 76344 Eggenstein-Leopoldshafen, Germany.

14
15 * **Corresponding author details.** Dr. Bradley Ladewig, Institute for Micro Process Engineering
16 (IMVT), Karlsruhe Institute of Technology, Hermann-von-Helmholtz-Platz 1, 76344 Eggenstein-
17 Leopoldshafen, Germany. Email address: bradley.ladewig@kit.edu.

Highlights

- Addition of HPAM during MIL-96 synthesis facilitated particle size enlargement.
- HPAM also functions as a crystal shape modifying agent.
- HPAM-grafted MIL-96 showed improvement in PFOA uptake quantity.

Abstract

A new synthesis method was developed to prepare an aluminum-based metal organic framework (MIL-96) with a larger particle size and different crystal habits. A low cost and water-soluble polymer, hydrolyzed polyacrylamide (HPAM), was added in varying quantities into the synthesis reaction to achieve >200% particle size enlargement with controlled crystal morphology. The modified adsorbent, MIL-96-RHPAM2, was systematically characterized by SEM, XRD, FTIR, BET and TGA-MS. Using activated carbon (AC) as a reference adsorbent, the effectiveness of MIL-96-RHPAM2 for perfluorooctanoic acid (PFOA) removal from water was examined. The study confirms stable morphology of hydrated MIL-96-RHPAM2 particles as well as a superior PFOA adsorption capacity (340 mg/g) despite its lower surface area, relative to standard MIL-96. MIL-96-RHPAM2 suffers from slow adsorption kinetics as the modification significantly blocks pore access. The strong adsorption of PFOA by MIL-96-RHPAM2 was associated with the formation of electrostatic bonds between the anionic carboxylate of PFOA and the amine functionality present in the HPAM backbone. Thus, the strongly held PFOA molecules in the pores of MIL-96-RHPAM2 were not easily desorbed even after eluted with a high ionic strength solvent (500 mM NaCl). Nevertheless, this simple HPAM addition strategy can still chart promising

pathways to impart judicious control over adsorbent particle size and crystal shapes while the introduction of amine functionality onto the surface chemistry is simultaneously useful for enhanced PFOA removal from contaminated aqueous systems.

Keywords. HPAM, particle size, crystal morphology, metal-organic frameworks, perfluorooctanoic acid, adsorption.

1. Introduction

Adequate, clean and safe water supply is indispensable to healthy wellbeing of humans and living organisms (Tiedeken et al., 2017). Unfortunately, our surface and ground waters continue being polluted by industrial waste streams containing toxic and persistent chemicals including perfluorinated compounds (PFCs). PFCs have recently received much attention because they are ubiquitous contaminants in water, wildlife, and humans. The most commonly found PFCs in surface waters are perfluorooctanoic acid (PFOA) and perfluorooctane sulfonate (PFOS) (Rivera-Utrilla et al., 2013). Surprisingly, thus far, there is no mutually agreed international drinking water standard for PFOA and PFOS, but the United States Environmental Protection Agency have recommended a strict combined concentration limit of 70 ng/L (Cordner et al., 2019). Recent analysis of global water samples even revealed concentrations exceeding the provisional threshold (Andersson et al., 2019; Feng et al., 2020; Li et al., 2018; Lorenzo et al., 2019; Scher et al., 2018; Valsecchi et al., 2017).

Although most fluorochemical manufacturers have ceased their production of PFOA and PFOS in the early 2000s, this measure does not address the legacy pollution caused by these compounds (Wang et al., 2017). The ubiquitous presence and long-range mobility of PFCs is attributed to the high chemical stability of their C-F bonds (bond dissociation energy, $D^{\circ}_{298\text{ K}} = 485\text{ kJ/mol}$) (Richardson, 2008), rendering them suitable as ingredients to make fluoropolymers (McNamara et al., 2018), fire-fighting foams (Cordner et al., 2019), and stain-repellent products (Richardson, 2008). Typical contamination hot spots then include the vicinity of industrial areas, military training sites, airports and wastewater treatment plants (Hu et al., 2016). Moreover, exposures to PFCs adversely affect body immunity (Sunderland et al., 2019), neurological functions (Piekarski et al., 2020), reproductive systems (Rashtian et al., 2019), as well as giving strong correlations to coronary heart disease (Huang et al., 2018), and cancer (Mancini et al., 2020) among many others. As a result, there is an urgent need to investigate efficient materials for PFCs remediation from contaminated water.

Of the treatments available for PFCs removal from water (Ateia et al., 2019), adsorption is extensively used given its simplicity, relatively lower cost and high selectivity (Du et al., 2014). Studied adsorbents range from activated carbon (AC) (Du et al., 2015; Xu et al., 2020), minerals (Shih and Wang, 2013; Wang and Shih, 2011), magnetic nanoparticles (Badrudodoza et al., 2017), polymers (Xiao et al., 2017), resins (Yang et al., 2018), functionalized cellulose (Ateia et al., 2018), graphene oxide-silica hybrid (Ali et al., 2020), and metal-organic frameworks (MOFs) (Chen et al., 2016; Jun et al., 2019; K. Liu et al., 2015; Sini et al., 2018, 2019). However, except for MOFs, most adsorbents only exhibit between low and moderate PFOA uptake compared to the industrial AC standard (>90% removal, 3M Company, USA) (Vecitis et al., 2009).

MOFs refer to a novel class of porous materials made from organic bridging linkers and metal atoms. Distinguishing MOF features include their high surface areas, ready structure tunability and reusability via simple washing procedures which means that these materials are seen as a promising future substitute for AC (Xue et al., 2016). These features are befitting to resolve long-standing problems in PFOA removal by other conventional wastewater treatments especially given their dilute levels existence, low molecular weight, and high transportability (Chen et al., 2020; Gagliano et al., 2020). Further to that, in commercial water purification processes, adsorbents are generally deployed into a packed bed for continuous filtration. Fluids flowing through some packed beds may at times result in high pressure drops. This directly increases the energy requirement to pump the fluid through the bed and decreases the operational lifetime of the pumps, impacting on the economics of the process (Gebald et al., 2019). Although various factors are involved in optimal bed design, lowering the pressure drop can be easily achieved by increasing the adsorbent particle size (Mandić et al., 2017). Larger particles also facilitate easier recovery in between the washing cycles.

Size and crystal morphology of MOFs can be precisely controlled via the presence of additives (Seoane et al., 2016) such as initiation solvents (D. Liu et al., 2015; Long et al., 2011), coordination modulators or capping agents (Guo et al., 2018; Han et al., 2015; Wang et al., 2013), surfactants (Falcaro et al., 2011), and hard templates (Yan et al., 2015) or through synthetic techniques using pyrolysis (Lee and Kwak, 2017), ultrasound (Vaitsis et al., 2019), and microreactor (Watanabe et al., 2017). Some complexities regarding the respective methods are usage of harmful organic solvents, use of acidic or basic modulators that increase risk of safety hazards and difficulty in

isolating the hard templates after preparation. Whilst these three MOF synthetic techniques can only be carried out with specialized instrument, a common limitation of these approaches is the formation of predominantly nanoparticle products. The work reported here uses a surfactant-assisted method which serves as a multifaceted approach; functioning as a nanoreactor, a capping agent as well as a molecular template (Seoane et al., 2016).

The current study highlights a new one-pot surfactant-based synthesis method to control particle size and morphology of MOF crystals by utilizing a synthetic polymer, hydrolyzed polyacrylamide (HPAM). HPAM is a low cost and water-soluble polymer widely used for enhanced oil recovery in petroleum drilling processes, as well as being used as a flocculant for wastewater treatment (Rellegadla et al., 2017) where its benign effects on water quality are noted (Edomwonyi-Otu and Adelakun, 2018). Finally, a non-toxic and hydrothermally stable aluminum-based MOF, MIL-96 (Al) was chosen to be tested for liquid phase adsorption of PFOA. Given the positive surface charge for MIL-96 (Azhar et al., 2018), HPAM must be anionic to initiate particle aggregation. Such polymer-MOF composite strategy may also improve separation selectivity (Chang et al., 2020). In this case, the PFOA adsorption performance by the modified material was benchmarked with a commercial AC to understand the interaction mechanisms better.

2. Materials and Methods

2.1. Chemicals

Polyacrylamide (PAM) (FLOPAM FA 920 SH, non-ionic, molecular weight (M_w) = 10 – 12 MDa) and partially hydrolyzed polyacrylamide (HPAM) (FLOPAAM FP 3630 S, anionic, 25–35 mol% hydrolyzed, M_w = 18 MDa) were supplied by SNF Floerger (France). Polyacrylic acid sodium salt (PAA, average M_w ~2100), 2,2,2-trifluoroethanol (TFE, 99.5%), perfluorooctanoic acid (PFOA, 95%), ammonium acetate (AA, 99.0%), trimesic acid (TMA, 95%), sodium chloride (NaCl, 99%) were purchased from Sigma Aldrich. Deuterium oxide (D_2O , 99.9%) and aluminum nitrate nonahydrate ($Al(NO_3)_3 \cdot 9H_2O$, 98%) were purchased from Fluorochem and Alfa Aesar respectively. All other chemicals and solvents were reagent grade and used without further purification. Ultrapure water (H_2O) used throughout the study was obtained from PureLab Chorus ELGA unit. Granular activated carbon (AC) F400 was procured from Chemviron Carbon as a high-grade, steam-activated bituminous coal.

2.2. ^{19}F NMR analysis

Concentration for the internal standard (TFE) solution was set to 2.3 mM by transferring 0.42 mL TFE into 1 L H_2O . The NMR analyte consists of 0.25 mL D_2O , 0.25 mL filtrate and 0.2 mL TFE. Quantification was performed according to the literature (Sini et al., 2018). Integrated area under the characteristic peaks of the terminal CF_3 groups for PFOA (-80 ppm) was compared relative to the TFE peaks (-76 ppm). Residual PFOA concentration after adsorption was calculated from the linear calibration equation obtained.

2.3. Adsorption

Prior to adsorption, the adsorbents were activated overnight at 120 °C under vacuum. All sorption experiments were conducted at room temperature. A PFOA stock solution (1000 mg/L) was prepared using ultrapure H₂O. The adsorbent (20 mg) was added with 20 mL PFOA solution into a screw cap vial, stirred for 72 hours and then, the solution was filtered. The filtrate was collected for NMR analysis while the filtered solids were reused for desorption. The experiments were performed in duplicate and the average values are reported.

2.4. Desorption

Based on the result from the desorption solvent screening, the solvent composition was adjusted to get a mixed methanol/ water (3:1, v/v) stabilized with 10 mM AA buffer solution. To study the influence of NaCl on the desorption efficiency, four desorption solvents were prepared with varying NaCl concentrations namely: RS1 (no salt), RS2 (10 mM NaCl), RS3 (50 mM NaCl) and RS4 (500 mM NaCl). After 72 hours of adsorption, the adsorbent was recovered by filtration and placed respectively in 20 mL desorption solvent containing the above NaCl concentrations to be continuously stirred for another 72 hours at room temperature. The sample mass used for desorption was assumed the same with the initial mass. Sample preparation for NMR analysis followed the steps mentioned previously.

2.5. Hydrothermal Synthesis of MOF

MIL-96 was synthesized according to the original method described previously (Loiseau et al., 2006) whereas the protocol for polymer addition was adapted from another study (Nandiyanto et al., 2019). A typical hydrothermal synthesis solution contains Al(NO₃)₃·9H₂O (1.3 g, 3.5 mmol),

TMA (0.1 g, 0.5 mmol) and H₂O (5 mL, 278 mmol) in a 23 ml Teflon liner. Firstly, to induce particle aggregation, HPAM solution (1000 mg/L) was poured into the reacting solution containing only the dissolved linker in H₂O. The solution was later sonicated for 15 minutes prior to adding the metal precursor. The ratio between the volume of polymer solutions added to the volume of water (R) is defined in Eq. 1. The mixture was heated to 210 °C for 24 hours. After cooling to ambient conditions, the resulting solid product was recovered via filtration and consequently washed with copious amount of H₂O. The washed residue was dried at 120 °C in vacuo overnight. Similar steps were implemented when using other polymer solutions (PAM and PAA). Chemical structures for all the polymers are illustrated in Fig. S1 of the Supplementary Information (SI).

$$R = \frac{\text{Volume of polymer (mL)}}{\text{Volume of water used as solvent in the reaction (mL)}} \quad \text{Eq. 1}$$

3. Results and Discussion

3.1. SEM

For MIL-96, HPAM is proven effective in changing the MOF particle morphology as observed in Fig. 1a – 1d. Generally, starting from the normally reported small hexagonal bipyramidal shaped (HB) crystals (Benzaoui et al., 2017), higher HPAM concentrations facilitate incremental increases in the aspect ratio (length: diameter), transitioning from hexagonal spindles (HS) to elongated hexagonal rods (HR), particularly when 20 mL HPAM was used (MIL-96-RHPAM2). Upon closer inspection from out-of-plane PXRD measurements, the apparent HS morphology was revealed to be a hybrid form of two elongated hexagonal pyramids seamlessly connected at the long axis (Sindoro et al., 2013).

It was reported that the hydrothermal synthesis conditions for MIL-96 must be strictly controlled given the possibility of forming two larger pore Al trimesates, MIL-100 and MIL-110, in the same reaction system despite all having distinct crystal structures. MIL-100 is the kinetically stable product which forms at short reaction times and low pH condition whereas the thermodynamically favored MIL-96 can be obtained after longer reaction times. MIL-110, on the other hand, crystallizes in a much more acidic or basic medium (Haouas et al., 2009). Their corresponding crystal morphologies have also been solved with MIL-96, MIL-100 and MIL-110 presenting a flat hexagonal, an octahedral and a hexagonal needle-like habits respectively (Haouas et al., 2012). Therefore, the influence of HPAM on the crystal morphology agrees well with the stability order of these phases; MIL-96 > MIL-110 > MIL-100.

The addition of HPAM seems to play multiple roles in the crystal elongation phenomenon, firstly as a competing modulator. Since the pK_a value for HPAM (4.5) (Li et al., 2002) is similar to that of TMA ($pK_{a1} = 3.51$, $pK_{a2} = 3.89$, $pK_{a3} = 4.70$), there will be competition with the linker to form coordination bonds with available Al. As a result, nucleation rate slows down and permits slow growth of large MOF crystals (Morris et al., 2017). Secondly, the amine ($-NH_2$) groups in both HPAM and PAM increase the basicity of the reacting solution, providing ideal conditions for the formation of MIL-110 ascribed by the existence of HR crystals. HPAM is a copolymer composed of PAM and PAA. To identify the dominant functional groups responsible to the formation of HR, MIL-96 was synthesized using equivalent concentrations of PAM (Fig. 1e) and PAA (Fig. 1f) separately. Before the reaction, the solutions were very acidic upon addition of PAM ($pH = 2$), PAA ($pH = 2.4$) and HPAM ($pH = 2.2$). Such acidic environment increases the likelihood of $-NH_2$ groups protonating to form primary ammonium ions ($-NH_3^+$) in preference to the ionization of the $-COOH$ groups on the TMA due to higher pK_a values. It is therefore expected to see the $-NH_2$ groups contained in HPAM and PAM to govern the crystal elongation mechanism, transforming the HB shape into the HR habit more so than using PAA.

Following the addition of 20 mL PAA, it is unclear what drives the formation of new hexagonal lumps (HL) with some truncated and larger in dimension among the HR. What might have happened is, from the instant of mixing PAA in water, the dissociated Na^+ cations may end up competing with the Al^{3+} species to form bonds with the linker, causing deceleration in the crystal growth and altering the original template. Another factor that may have undermined PAA's influence is due to its low molecular weight (~ 2100 g/mol). By substituting higher molecular weight PAA for the synthesis, its influence toward crystal elongation may be amplified.

224

225 Finally, the successes in morphological change shown in the MIL-96 samples can be attributed
226 to the solubility of the linker (TMA) in water. Simultaneous dissolution of both TMA and HPAM
227 during the pre-mixing stage facilitates smooth integration of the latter species into the reacting
228 solution, which subsequently changes the MOF crystal morphology. On a side note, identical
229 experiments were performed involving similar modification of another MOF. Readers are referred
230 to Fig. S2 – S4 in the SI for further information.

231

Fig. 1. Modified MIL-96 crystals with (a) no polymer, (b) 2 mL HPAM ($R_{\text{HPAM}} = 0.2$), (c) 6 mL HPAM ($R_{\text{HPAM}} = 0.6$), (d) 20 mL HPAM ($R_{\text{HPAM}} = 2$), (e) 20 mL PAM ($R_{\text{PAM}} = 2$), and (f) 20 mL PAA ($R_{\text{PAA}} = 2$).

3.2.PXRD

As shown in Fig. 2, the PXRD patterns of every sample are slightly different compared to the simulated MIL-96 spectra. The peaks have also been shifted slightly to higher angle. The drift may be attributed to the presence of free TMA inside the pores of the samples (Abid et al., 2016). The aforementioned series of crystal shape changes can be defined using the Bravais, Frisdel, Donnay and Harker (BFDH) theory which describes the three main planes that make up the morphology

of MIL-96; they are (002), (100) and (101) at $2\theta = 5.7^\circ$, 7.1° and 7.7° respectively (D. Liu et al., 2015). Except for the subtly present (002), other key characteristic peaks including (102), match well with the simulated spectra, indicating the core crystalline structure is retained. Although by visual inspection, MIL-110 was mainly present at higher HPAM loading as evident by the HR formation, due to instrument limitation (minimum $2\theta \geq 5^\circ$), the characteristic XRD peaks of MIL-100 ($2\theta = 4^\circ$) and MIL-110 ((001) facet; $2\theta = 5^\circ$) (Lin et al., 2013) cannot be clearly detected and thus, have to be omitted from subsequent discussion.

Fig. 2. PXRD patterns of the simulated MIL-96 compared to the as-synthesized MIL-96 samples modified with different types and proportions of polymers.

With higher concentration of HPAM, the emerging (100) facet indicates it could enhance the growth rate of the (100), resulting in narrowed edge and the lengthening of the crystals. Furthermore, higher proportion of HPAM accentuates the growth of the (101) crystal plane as shown by the gradual peak increase in which alongside with (100), completes the formation of HR crystal morphology. This is consistent with the reported SEM images. The -NH_2 groups in HPAM function like OH^- ions, increasing solution basicity and speeding up the growth rate along the (101) facet, consequently forming the HR habit (Lin et al., 2013).

After the addition of PAA, the (002) facet that is responsible for the formation of HL is only weakly observed in the PXRD, as with the simulated MIL-96, which is probably affected by instrument background noise during scanning, impure phase with ill-defined morphology and powder size inconsistency. Although the BFDH theory also states that the growth rate of the (002) facet to be relatively unaffected, the number of products containing the (002) plane may be subservient compared to the bulk phase which is dominated with (100) and (101)-directed crystals. In short, the preferential crystal growth along the (100) and (101) planes, as a function of higher polymer concentrations, transformed the crystal anisotropy by promoting crystal elongation from its original HB shape. For a hexagonal lattice system, the impact of polymer presence in the reacting environment accelerated the growth along the c axis (Sindoro et al., 2013). Moreover, with a higher quantity of added polymers, the subtle width broadening of the strongest peak

corresponding to the (102) crystal face implies a slight decrease in particle size. In addition, the relative Bragg peaks of (200) and (201) also become broader and less intense compared to the original MIL-96, supporting the minor reduction in particle size and crystallinity.

3.3. FTIR

FTIR spectroscopy was used to understand PFOA adsorption mechanism onto MIL-96-RHPAM2 and the linker interaction with added polymer (Fig. S5). Detailed analysis of the IR peaks is displayed in Table S1. The collected spectra of spent MIL-96-RHPAM2 in Fig. 3 confirms that PFOA was adsorbed through electrostatic interaction with the MOF. A previous study also inferred the increased intensities of symmetric (ν_s) to asymmetric (ν_{as}) COO stretch after PFOA adsorption in relation to an inner-sphere complexation with the metal centers. In this case, the carboxylate head groups of PFOA may have formed electrostatic bonds to the surface of MIL-96-RHPAM2 (Gao and Chorover, 2012). The consistent N-H peak on both spectra of MIL-96-RHPAM2 after PFOA adsorption and desorption indicates minimal leaching of the HPAM functionality.

Fig. 3. FTIR spectra for the parent MIL-96 and MIL-96-RHPAM2 before and after PFOA adsorption.

3.4. BET

The use of PAM, PAA and HPAM for this particle size modification led to a significant reduction in the apparent surface area (SA_{BET}), see Fig. S6. The pore size distribution plot in Fig. S7 clearly proves complete pore blocking when HPAM was used, asserting its location inside the

pores. Interestingly, compared to the apparent surface area of AC ($SA_{\text{BET}} = 1179 \text{ m}^2/\text{g}$), MIL-96-RHPAM2 ($SA_{\text{BET}} = 75 \text{ m}^2/\text{g}$) has comparatively good PFOA adsorption capacity even though it possesses a lower surface area.

3.5. Adsorption Kinetics

Apart from knowing the equilibrium adsorption capacity of sorbents (Fig. S10), it is equally important to understand the adsorption kinetics involved in the PFOA removal by MIL-96-RHPAM2. Based on previous studies, the experimental data obtained herein is fitted using a pseudo second order (PSO) kinetic model. Fig. S12 highlights the severe diffusion limitation exhibited by MIL-96-RHPAM2 as the material's adsorptive capacity only reached its plateau after 186 hours of contact time. Concurrently, the PFOA adsorption data can also be described by the Elovich kinetic model. Non-linear plots using both models showed high regression coefficients with PSO ($R^2 = 0.983$) and Elovich ($R^2 = 0.996$), suggesting chemisorption is the rate limiting step as supported by the FTIR analysis. Since the Elovich equation gave superior approximation to the experimental data, it may be concluded that the adsorption proceeded in a highly heterogeneous system (Riahi et al., 2017). Earlier discussions have highlighted the abundance of chemical functional groups comprising of $-\text{NH}_2$, $-\text{OH}$, $-\text{COOH}$, $-\text{NH}_3^+$ and the Al^{3+} metal centers on MIL-96-RHPAM2 which may readily bind to PFOA.

To gain a detailed insight in the PFOA adsorption kinetics for MIL-96-RHPAM2, vapor phase adsorption experiments were conducted with a hydrocarbon analogue to PFOA; n-octane (C_8H_{18}) (Fig. S13 – S14). The fundamental differences in liquid-phase adsorption and vapor adsorption are acknowledged but, in both cases, the kinetic rate is nonetheless similar (denoted by the proximity

of $k_2 = 2 \times 10^{-4} \text{ g/mg.min}$). Vapor phase adsorption time of 1000 minutes is still insufficient to realize an equilibrium adsorption state. The BET result shows that although increasing the HPAM content increases the particle size (Fig. 4), it has compromised the material's porosity. In turn, there is an increase in the diffusion path length inside the adsorbent that hindered effective diffusion and prolonging the time required to reach equilibrium (Kumar et al., 2019). It may appear that the approach outlined here has created another problem but, there is a future opportunity to retain the beneficial effect provided by HPAM by tuning MIL-96 adsorption capacity with temperature, taking into account the high thermal stability of HPAM (Al-Hamairi and AlAmeri, 2020) and the MOF flexibility of changing and increasing its pore size (Barton et al., 2018).

Fig. 4. Measured hydrodynamic particle size distribution (mean volume equivalent sphere diameter in bracket) of polymer-modified MIL-96 in pure water by laser light diffraction ($n = 5$). The particle size ranges shown reflect the true size as particles were pre-sonicated prior to the laser light diffraction measurement. Addition of 20 mL HPAM effectively formed the largest MIL-96 particles with 225% diameter increase from 3.2 μm to 10.4 μm .

In comparison to the reported kinetic data for PFOA removal by several other adsorbents, MIL-96-RHPAM2 can adsorb PFOA at loading levels on a par with other adsorbents, but the extremely slow uptake would be a significant drawback for its practical use. Relative to other adsorption studies displayed in Table 1, the PFOA concentration used in this work is the highest.

341
342 **Table 1.** Comparison of the pseudo-second order kinetic parameters for PFOA adsorption by select
343 MOFs and AC.

Sorbent used	Tested PFOA concentration (mg/L)	Pseudo-second order model parameter			Equilibrium time (hr)	Reference
		q_e (mg/g)	k_2 (g/mg.min)	R^2		
Bamboo-derived AC	120	393	2.7×10^{-5}	0.91	33.5	(Du et al., 2015)
Fe ₃ O ₄ -modified AC	300	364	7.1×10^{-5}	0.998	29	(Xu et al., 2020)
Perfluorinated UiO-66-(F4)	500	381	2.6×10^{-3}	0.993	1	(Sini et al., 2018)
UiO-66		327	2.7×10^{-3}	0.996		
MIL-101 (Cr)	100	481	1.4×10^{-4}	0.967	1	(K. Liu et al., 2015)
Quaternized amine MIL-101 (Cr)-QDMEN		791	2.1×10^{-4}	0.985		

MIL-53 (Al)	1	100	7.3×10^{-2}	0.999	4	(Jun et al., 2019)
ZIF-7	-	22	7.1×10^{-5}	0.994	1	(Chen et al., 2016)
ZIF-8		177	2.0×10^{-5}	0.978		
ZIF-L		244	9.6×10^{-6}	0.985		
UiO-67	500	350	6.1×10^{-4}	0.999	1	(Sini et al., 2019)
MIL-96-RHPAM2	1000	340*	1.7×10^{-4}	0.983	186	This work

*Shows the increase in adsorption capacity after kinetic experiment was extended to 186 hours suggesting MIL-96-RHPAM2 has a very slow kinetic rate.

3.6. PFOA Adsorption and Desorption

Knowing that PFCs are hazardous chemicals, safe regeneration and economical reuse of the spent adsorbents is critically important. Although thermal regeneration is preferably used by carbon manufacturers, adsorbed PFCs are not easily removed from the carbon surfaces by decomposition as C-F is the strongest single bond in organic chemistry after B-F, Si-F and H-F. While the next best alternative is to use higher regeneration temperatures to break the C-F bond, this often results in high carbon losses (Ateia et al., 2019).

To develop an efficient PFOA regeneration method from spent MOF, the nature of adsorption processes must first be understood. An earlier report on PFOA adsorption by MOF had confirmed the electrostatic interaction between the cationic MOF species (Al^{3+}) with the anionic carboxylate groups (COO^-) of PFOA as the main binding mechanism, supplemented by H-bonding and hydrophobic interaction to a lesser extent (Jun et al., 2019). So, with electrostatic interaction being the most prevalent, it was decided to trial saline eluents to evaluate their destabilization effect on the electrostatic PFOA adsorption complex.

The positively charged Al^{3+} center of MIL-96 is surmised to have a strong interaction with the anionic carboxylate groups (COO^-) of PFOA. Contrary to expectations, increasing the eluent ionic strength has minimal effect on PFOA desorption by MIL-96-RHPAM2 (Shih and Wang, 2013; Wang and Shih, 2011) except for a slight drop at the highest tested salt concentration (500 mM NaCl). Such salt concentration may be sufficiently high enough to reduce the electrostatic forces between the Al^{3+} center and the negatively charged PFOA molecules resulting from the competitive PFOA adsorption with the background ions (Na^+ and Cl^-) (Gao and Chorover, 2012). However, due to the well-established acid-base and electrostatic bonds between the Al^{3+} , carboxylate (COO^-), hydroxyl (OH), NH_2 and NH_3^+ functional groups on the MOF, the driving force to establish new bonds with the incoming Na^+ and Cl^- ions is not as favorable, hence, not accommodating the desorption of adsorbed PFOA molecules into the eluent phase.

Apart from the Al^{3+} center being a major MOF binding site, it is probable that the NH_2 , which will also exist in a protonated form as a NH_3^+ , contained in HPAM also attaches to the anionic carboxylate of PFOA via strong electrostatic adsorption forces (Ali et al., 2020; Deng et al., 2013;

K. Liu et al., 2015). In addition, the van der Waals interaction between the carbon chain of PFOA (8 carbons on the PFOA) and the main skeleton $(CH_2-CH)_n$ of HPAM may also contribute to the adsorption process. Altogether, these explanations for the incomplete desorption of PFOA from aminated adsorbents such as MIL-96-RHPAM2 are in line with the obtained result from batch desorption studies. Fig. 5 illustrates the nuanced NaCl influence in the eluent to the PFOA desorption performance of MIL-96-RHPAM2. Across the tested salinity window, the highest PFOA fraction desorbed only reached 77% but not full recovery, providing future research opportunities to clarify the best solvent/ salt systems capable of complete PFOA desorption. Descriptions on the possible PFOA adsorption mechanisms onto MIL-96-RHPAM2 can be found in Fig. S16 (Scheme S1) and Fig. S17 (Scheme S2) for the pristine form.

Although PFOA desorption efficiency from AC is inferior to MIL-96-RHPAM2 at lower ionic strengths, AC's desorption efficiency is improved at the highest ionic strength tested here. Similar to MOF, PFOA adsorption onto AC shares similar adsorption mechanisms (Wang and Shih, 2011; Wang et al., 2019), confirming the importance of surface chemistry on AC. There is a clear correlation with a marked increase in PFCs sorption with more availability of basic groups in the adsorbents. Thus, to enhance the adsorption process, an abundance of hydroxyl and carboxyl oxygen-containing functional groups on the AC surface will then interact with the PFOA anions via acid-base/electrostatic interactions (Sun et al., 2016; Zhi and Liu, 2016). Along the same lines, the oxygen-containing basic and acidic surface groups on AC may form H-bond interactions with the amphoteric COOH functional groups within PFOA. An increase in the eluent ionic strength can potentially weaken these PFOA to AC H-bonding interactions by the Na^+ and the Cl^- ions shielding the electrostatic interactions whilst also directly competing for the H-bonding sites.

While these results show that NaCl was not an effective PFOA desorption facilitating agent, only catalytic degradation has so far offered superior performance (Du et al., 2014; Zhao et al., 2013).

Fig. 5. Percentage of PFOA desorbed from MIL-96-RHPAM2 and AC using eluents with various NaCl concentrations (temperature 25 °C, adsorbent dose = 2 mg/L, initial PFOA concentration = 1000 mg/L).

4. Conclusions

In summary, the addition of an anionic polymer (HPAM) to a cationic aluminum-based MOF (MIL-96) during the hydrothermal synthesis stage allowed the formation of larger MOF crystals

with well-defined crystal habits. Taking advantage of HPAM being a low cost and an environmentally friendly additive, a HPAM-modified MIL-96 (MIL-96-RHPAM2) showed promising particle size growth from 3.2 μm to 10.4 μm as well as the ability to control the crystal morphology using this simple modification procedure. Incorporating HPAM into the MIL-96 structure resulted in the introduction of amine functionality, which can form a primary ammonium species that in turn led to improved PFOA adsorption capacity relative to original pristine form, while also promoting higher PFOA affinity compared to AC. Higher concentrations of NaCl in the eluent solvents did not yield enhanced PFOA desorption from both spent adsorbents, MIL-96-RHPAM2 (maximum PFOA desorbed was 77%) and AC (74%), primarily due to the strong PFOA adsorption to both adsorbents.

Acknowledgments

Luqman Hakim Mohd Azmi gratefully acknowledges the financial support provided by the sovereign wealth fund of Malaysian Government, Yayasan Khazanah for his PhD studies. The authors also thank Prof. Paul D. Lickiss, Dr. Pavani Cherukupally and Elwin Hunter-Sellars for useful discussion on material design and characterization.

Appendix A. Supplementary Material

Characterization techniques, SEM images of HPAM-modified MIL-101 (Cr), IR spectra analysis of HPAM-treated linker, data pertaining to samples' N_2 adsorption and desorption isotherms together with their pore size distribution, TGA-MS, batch adsorption, n-octane vapor sorption

433 study, elemental analysis, and illustrations of PFOA adsorption mechanisms by MIL-96-RHPAM2
434 are included. The raw data presented in all figures, and high-resolution versions of the SEM
435 images, are available from the open repository: <https://doi.org/10.5281/zenodo.3813241>

References

- Abid, H.R., Rada, Z.H., Shang, J., Wang, S., 2016. Synthesis, characterization, and CO₂ adsorption of three metal-organic frameworks (MOFs): MIL-53, MIL-96, and amino-MIL-53. *Polyhedron* 120, 103–111.
- Al-Hamairi, A., AlAmeri, W., 2020. Development of a novel model to predict HPAM viscosity with the effects of concentration, salinity and divalent content. *J. Pet. Explor. Prod. Technol.* 1–15.
- Ali, M., Meaney, S.P., Giles, L.W., Holt, P., Majumder, M., Tabor, R.F., 2020. Capture of Perfluorooctanoic Acid Using Oil-Filled Graphene Oxide–Silica Hybrid Capsules. *Environ. Sci. Technol.* 54, 3549–3558.
- Andersson, E.M., Scott, K., Xu, Y., Li, Y., Olsson, D.S., Fletcher, T., Jakobsson, K., 2019. High exposure to perfluorinated compounds in drinking water and thyroid disease. A cohort study from Ronneby, Sweden. *Environ. Res.* 176, 108540.
- Ateia, M., Attia, M.F., Maroli, A., Tharayil, N., Alexis, F., Whitehead, D.C., Karanfil, T., 2018. Rapid removal of poly-and perfluorinated alkyl substances by poly (ethylenimine)-functionalized cellulose microcrystals at environmentally relevant conditions. *Environ. Sci. Technol. Lett.* 5, 764–769.
- Ateia, M., Maroli, A., Tharayil, N., Karanfil, T., 2019. The overlooked short-and ultrashort-chain poly-and perfluorinated substances: A review. *Chemosphere* 220, 866–882.
- Azhar, M.R., Abid, H.R., Tade, M.O., Periasamy, V., Sun, H., Wang, S., 2018. Cascade

456 applications of robust MIL-96 metal organic frameworks in environmental remediation:
 457 Proof of concept. Chem. Eng. J. 341, 262–271.

458 Badruddoza, A.Z.M., Bhattarai, B., Suri, R.P.S., 2017. Environmentally friendly β -cyclodextrin–
 459 ionic liquid polyurethane-modified magnetic sorbent for the removal of PFOA, PFOS, and
 460 Cr (VI) from water. ACS Sustain. Chem. Eng. 5, 9223–9232.

461 Barton, H.F., Davis, A.K., Lee, D.T., Parsons, G.N., 2018. Solvothermal Synthesis of MIL-96 and
 462 UiO-66-NH₂ on Atomic Layer Deposited Metal Oxide Coatings on Fiber Mats. J. Vis. Exp.
 463 e57734. <https://doi.org/doi:10.3791/57734>

464 Benzaqui, M., Pillai, R.S., Sabetghadam, A., Benoit, V., Normand, P., Marrot, J., Menguy, N.,
 465 Montero, D., Shepard, W., Tissot, A., 2017. Revisiting the aluminum trimesate-based MOF
 466 (MIL-96): from structure determination to the processing of mixed matrix membranes for
 467 CO₂ capture. Chem. Mater. 29, 10326–10338.

468 Chang, Y., Huang, H., Wang, L., Li, Y., Zhong, C., 2020. Synergistic Dual-Li⁺ Sites for CO₂
 469 Separation in Metal-Organic Framework Composites. Chem. Eng. J. 126201.

470 Chen, M.-J., Yang, A.-C., Wang, N.-H., Chiu, H.-C., Li, Y.-L., Kang, D.-Y., Lo, S.-L., 2016.
 471 Influence of crystal topology and interior surface functionality of metal-organic frameworks
 472 on PFOA sorption performance. Microporous Mesoporous Mater. 236, 202–210.

473 Chen, X., Vanangamudi, A., Wang, J., Jegatheesan, J., Mishra, V., Sharma, R., Gray, S.R.,
 474 Kujawa, J., Kujawski, W., Wicaksana, F., 2020. Direct contact membrane distillation for
 475 effective concentration of perfluoroalkyl substances–Impact of surface fouling and material
 476 stability. Water Res. 116010.

477 Cordner, A., Vanessa, Y., Schaidler, L.A., Rudel, R.A., Richter, L., Brown, P., 2019. Guideline
 478 levels for PFOA and PFOS in drinking water: the role of scientific uncertainty, risk
 479 assessment decisions, and social factors. *J. Expo. Sci. Environ. Epidemiol.* 29, 157.

480 Deng, S., Niu, L., Bei, Y., Wang, B., Huang, J., Yu, G., 2013. Adsorption of perfluorinated
 481 compounds on aminated rice husk prepared by atom transfer radical polymerization.
 482 *Chemosphere* 91, 124–130. <https://doi.org/10.1016/j.chemosphere.2012.11.015>

483 Du, Z., Deng, S., Bei, Y., Huang, Q., Wang, B., Huang, J., Yu, G., 2014. Adsorption behavior and
 484 mechanism of perfluorinated compounds on various adsorbents—a review. *J. Hazard. Mater.*
 485 274, 443–454.

486 Du, Z., Deng, S., Chen, Y., Wang, B., Huang, J., Wang, Y., Yu, G., 2015. Removal of
 487 perfluorinated carboxylates from washing wastewater of perfluorooctanesulfonyl fluoride
 488 using activated carbons and resins. *J. Hazard. Mater.* 286, 136–143.

489 Edomwonyi-Otu, L.C., Adelakun, D.O., 2018. Effect of heavy molecular weight polymer on
 490 quality of drinking water. *Mater. Today Commun.* 15, 337–343.

491 Falcaro, P., Hill, A.J., Nairn, K.M., Jasieniak, J., Mardel, J.I., Bastow, T.J., Mayo, S.C., Gimona,
 492 M., Gomez, D., Whitfield, H.J., 2011. A new method to position and functionalize metal-
 493 organic framework crystals. *Nat. Commun.* 2, 237.

494 Feng, X., Ye, M., Li, Y., Zhou, J., Sun, B., Zhu, Y., Zhu, L., 2020. Potential sources and sediment-
 495 pore water partitioning behaviors of emerging per/polyfluoroalkyl substances in the South
 496 Yellow Sea. *J. Hazard. Mater.* 389, 122124.

497 Gagliano, E., Sgroi, M., Falciglia, P.P., Vagliasindi, F.G.A., Roccaro, P., 2020. Removal of poly-
 498 and perfluoroalkyl substances (PFAS) from water by adsorption: Role of PFAS chain length,
 499 effect of organic matter and challenges in adsorbent regeneration. *Water Res.* 171, 115381.

500 Gao, X., Chorover, J., 2012. Adsorption of perfluorooctanoic acid and perfluorooctanesulfonic
 501 acid to iron oxide surfaces as studied by flow-through ATR-FTIR spectroscopy. *Environ.*
 502 *Chem.* 9, 148–157.

503 Gebald, C., Repond, N., Ruesch, T., Wurzbacher, J.A., 2019. Low-pressure drop structure of
 504 particle adsorbent bed for adsorption gas separation process. US10427086B2.

505 Guo, C., Zhang, Yonghong, Guo, Y., Zhang, L., Zhang, Yi, Wang, J., 2018. A general and efficient
 506 approach for tuning the crystal morphology of classical MOFs. *Chem. Commun.* 54, 252–
 507 255.

508 Han, Y., Liu, M., Li, K., Zuo, Y., Wei, Y., Xu, S., Zhang, G., Song, C., Zhang, Z., Guo, X., 2015.
 509 Facile synthesis of morphology and size-controlled zirconium metal–organic framework
 510 UiO-66: the role of hydrofluoric acid in crystallization. *CrystEngComm* 17, 6434–6440.

511 Haouas, M., Volkringer, C., Loiseau, T., Férey, G., Taulelle, F., 2009. The Extra-Framework Sub-
 512 Lattice of the Metal–Organic Framework MIL-110: A Solid-State NMR Investigation. *Chem.*
 513 *Eur. J.* 15, 3139–3146.

514 Haouas, M., Volkringer, C., Loiseau, T., Férey, G., Taulelle, F., 2012. In situ NMR, ex situ XRD
 515 and SEM study of the hydrothermal crystallization of nanoporous aluminum trimesates MIL-
 516 96, MIL-100, and MIL-110. *Chem. Mater.* 24, 2462–2471.
 517 <https://doi.org/10.1021/cm300439e>

518 Hu, X.C., Andrews, D.Q., Lindstrom, A.B., Bruton, T.A., Schaider, L.A., Grandjean, P., Lohmann,
 519 R., Carignan, C.C., Blum, A., Balan, S.A., 2016. Detection of poly-and perfluoroalkyl
 520 substances (PFASs) in US drinking water linked to industrial sites, military fire training areas,
 521 and wastewater treatment plants. *Environ. Sci. Technol. Lett.* 3, 344–350.

522 Huang, M., Jiao, J., Zhuang, P., Chen, X., Wang, J., Zhang, Y., 2018. Serum polyfluoroalkyl
 523 chemicals are associated with risk of cardiovascular diseases in national US population.
 524 *Environ. Int.* 119, 37–46.

525 Jun, B.-M., Hwang, H.S., Heo, J., Han, J., Jang, M., Sohn, J., Park, C.M., Yoon, Y., 2019. Removal
 526 of selected endocrine-disrupting compounds using Al-based metal organic framework:
 527 Performance and mechanism of competitive adsorption. *J. Ind. Eng. Chem.* 79, 345–352.

528 Kumar, P.S., Korving, L., Keesman, K.J., van Loosdrecht, M.C.M., Witkamp, G.-J., 2019. Effect
 529 of pore size distribution and particle size of porous metal oxides on phosphate adsorption
 530 capacity and kinetics. *Chem. Eng. J.* 358, 160–169.

531 Lee, J., Kwak, S.-Y., 2017. Tubular superstructures composed of α -Fe₂O₃ nanoparticles from
 532 pyrolysis of metal–organic frameworks in a confined space: effect on morphology, particle
 533 size, and magnetic properties. *Cryst. Growth Des.* 17, 4496–4500.

534 Li, L., Zheng, H., Wang, T., Cai, M., Wang, P., 2018. Perfluoroalkyl acids in surface seawater
 535 from the North Pacific to the Arctic Ocean: Contamination, distribution and transportation.
 536 *Environ. Pollut.* 238, 168–176.

537 Li, W., Zhao, H., Teasdale, P.R., John, R., Zhang, S., 2002. Synthesis and characterisation of a
 538 polyacrylamide–polyacrylic acid copolymer hydrogel for environmental analysis of Cu and

539 Cd. React. Funct. Polym. 52, 31–41.

540 Lin, Y., Kong, C., Chen, L., 2013. Facile synthesis of aluminum-based metal-organic frameworks
 541 with different morphologies and structures through an OH--assisted method. Chem. - An
 542 Asian J. 8, 1873–1878. <https://doi.org/10.1002/asia.201300135>

543 Liu, D., Liu, Y., Dai, F., Zhao, J., Yang, K., Liu, C., 2015. Size-and morphology-controllable
 544 synthesis of MIL-96 (Al) by hydrolysis and coordination modulation of dual aluminium
 545 source and ligand systems. Dalt. Trans. 44, 16421–16429.

546 Liu, K., Zhang, S., Hu, X., Zhang, K., Roy, A., Yu, G., 2015. Understanding the adsorption of
 547 PFOA on MIL-101 (Cr)-based anionic-exchange metal–organic frameworks: comparing DFT
 548 calculations with aqueous sorption experiments. Environ. Sci. Technol. 49, 8657–8665.

549 Loiseau, T., Lecroq, L., Volkringer, C., Marrot, J., Férey, G., Haouas, M., Taulelle, F., Bourrelly,
 550 S., Llewellyn, P.L., Latroche, M., 2006. MIL-96, a porous aluminum trimesate 3D structure
 551 constructed from a hexagonal network of 18-membered rings and μ_3 -oxo-centered trinuclear
 552 units. J. Am. Chem. Soc. 128, 10223–10230. <https://doi.org/10.1021/ja0621086>

553 Long, P., Wu, H., Zhao, Q., Wang, Y., Dong, J., Li, J., 2011. Solvent effect on the synthesis of
 554 MIL-96 (Cr) and MIL-100 (Cr). Microporous Mesoporous Mater. 142, 489–493.

555 Lorenzo, M., Campo, J., Suárez-Varela, M.M., Picó, Y., 2019. Occurrence, distribution and
 556 behavior of emerging persistent organic pollutants (POPs) in a Mediterranean wetland
 557 protected area. Sci. Total Environ. 646, 1009–1020.

558 Mancini, F.R., Cano-Sancho, G., Gambaretti, J., Marchand, P., Boutron-Ruault, M., Severi, G.,

559 Arveux, P., Antignac, J., Kvaskoff, M., 2020. Perfluorinated alkylated substances serum
 560 concentration and breast cancer risk: Evidence from a nested case-control study in the French
 561 E3N cohort. *Int. J. Cancer* 146, 917–928.

562 Mandić, M., Todić, B., Živanić, L., Nikačević, N., Bukur, D.B., 2017. Effects of catalyst activity,
 563 particle size and shape, and process conditions on catalyst effectiveness and methane
 564 selectivity for Fischer–Tropsch reaction: a modeling study. *Ind. Eng. Chem. Res.* 56, 2733–
 565 2745.

566 McNamara, J.D., Franco, R., Mimna, R., Zappa, L., 2018. Comparison of activated carbons for
 567 removal of perfluorinated compounds from drinking water. *Journal-American Water Work.*
 568 *Assoc.* 110, E2–E14.

569 Morris, W., Wang, S., Cho, D., Auyeung, E., Li, P., Farha, O.K., Mirkin, C.A., 2017. Role of
 570 Modulators in Controlling the Colloidal Stability and Polydispersity of the UiO-66 Metal–
 571 Organic Framework. *ACS Appl. Mater. Interfaces* 9, 33413–33418.

572 Nandiyanto, A.B.D., He, X., Wang, W.-N., 2019. Colloid-Assisted Growth of Metal-Organic
 573 Framework Nanoparticles. *CrystEngComm* 1, 2268–2272.
 574 <https://doi.org/10.1039/c9ce00033j>

575 Piekarski, D.J., Diaz, K.R., McNerney, M.W., 2020. Perfluoroalkyl chemicals in neurological
 576 health and disease: Human concerns and animal models. *Neurotoxicology*.

577 Rashtian, J., Chavkin, D.E., Merhi, Z., 2019. Water and soil pollution as determinant of water and
 578 food quality/contamination and its impact on female fertility. *Reprod. Biol. Endocrinol.* 17,
 579 5.

580 Rellegadla, S., Prajapat, G., Agrawal, A., 2017. Polymers for enhanced oil recovery: fundamentals
581 and selection criteria. *Appl. Microbiol. Biotechnol.* 101, 4387–4402.

582 Riahi, K., Chaabane, S., Thayer, B. Ben, 2017. A kinetic modeling study of phosphate adsorption
583 onto *Phoenix dactylifera* L. date palm fibers in batch mode. *J. Saudi Chem. Soc.* 21, S143–
584 S152.

585 Richardson, S.D., 2008. Environmental Mass Spectrometry: Emerging Contaminants and Current
586 Issues. *Anal. Chem.* 80, 4373–4402. <https://doi.org/10.1021/ac202903d>

587 Rivera-Utrilla, J., Sánchez-Polo, M., Ferro-García, M.Á., Prados-Joya, G., Ocampo-Pérez, R.,
588 2013. Pharmaceuticals as emerging contaminants and their removal from water. A review.
589 *Chemosphere* 93, 1268–1287. <https://doi.org/10.1016/j.chemosphere.2013.07.059>

590 Scher, D.P., Kelly, J.E., Huset, C.A., Barry, K.M., Hoffbeck, R.W., Yingling, V.L., Messing, R.B.,
591 2018. Occurrence of perfluoroalkyl substances (PFAS) in garden produce at homes with a
592 history of PFAS-contaminated drinking water. *Chemosphere* 196, 548–555.

593 Seoane, B., Castellanos, S., Dikhtiarenko, A., Kapteijn, F., Gascon, J., 2016. Multi-scale crystal
594 engineering of metal organic frameworks. *Coord. Chem. Rev.* 307, 147–187.

595 Shih, K., Wang, F., 2013. Adsorption behavior of perfluorochemicals (PFCs) on boehmite:
596 influence of solution chemistry. *Procedia Environ. Sci.* 18, 106–113.

597 Sindoro, M., Jee, A.Y., Granick, S., 2013. Shape-selected colloidal MOF crystals for aqueous use.
598 *Chem. Commun.* 49, 9576–9578. <https://doi.org/10.1039/c3cc45935g>

599 Sini, K., Bourgeois, D., Idouhar, M., Carboni, M., Meyer, D., 2019. Metal-organic frameworks

600 cavity size effect on the extraction of organic pollutants. *Mater. Lett.* 250, 92–95.

601 Sini, K., Bourgeois, D., Idouhar, M., Carboni, M., Meyer, D., 2018. Metal-organic framework
 602 sorbents for the removal of perfluorinated compounds in an aqueous environment. *New J.*
 603 *Chem.* 42, 17889–17894. <https://doi.org/10.1039/c8nj03312a>

604 Sun, B., Ma, J., Sedlak, D.L., 2016. Chemisorption of perfluorooctanoic acid on powdered
 605 activated carbon initiated by persulfate in aqueous solution. *Environ. Sci. Technol.* 50, 7618–
 606 7624.

607 Sunderland, E.M., Hu, X.C., Dassuncao, C., Tokranov, A.K., Wagner, C.C., Allen, J.G., 2019. A
 608 review of the pathways of human exposure to poly-and perfluoroalkyl substances (PFASs)
 609 and present understanding of health effects. *J. Expo. Sci. Environ. Epidemiol.* 29, 131–147.

610 Tiedeken, E.J., Tahar, A., McHugh, B., Rowan, N.J., 2017. Monitoring, sources, receptors, and
 611 control measures for three European Union watch list substances of emerging concern in
 612 receiving waters – A 20 year systematic review. *Sci. Total Environ.* 574, 1140–1163.
 613 <https://doi.org/10.1016/j.scitotenv.2016.09.084>

614 Vaitsis, C., Sourkouni, G., Argirusis, C., 2019. Metal organic frameworks (MOFs) and ultrasound:
 615 a review. *Ultrason. Sonochem.* 52, 106–119.

616 Valsecchi, S., Conti, D., Crebelli, R., Polesello, S., Rusconi, M., Mazzoni, M., Preziosi, E., Carere,
 617 M., Lucentini, L., Ferretti, E., 2017. Deriving environmental quality standards for
 618 perfluorooctanoic acid (PFOA) and related short chain perfluorinated alkyl acids. *J. Hazard.*
 619 *Mater.* 323, 84–98.

620 Vecitis, C.D., Park, H., Cheng, J., Mader, B.T., Hoffmann, M.R., 2009. Treatment technologies
 621 for aqueous perfluorooctanesulfonate (PFOS) and perfluorooctanoate (PFOA). *Front.*
 622 *Environ. Sci. Eng. China* 3, 129–151.

623 Wang, F., Guo, H., Chai, Y., Li, Y., Liu, C., 2013. The controlled regulation of morphology and
 624 size of HKUST-1 by “coordination modulation method.” *Microporous Mesoporous Mater.*
 625 173, 181–188.

626 Wang, F., Shih, K., 2011. Adsorption of perfluorooctanesulfonate (PFOS) and perfluorooctanoate
 627 (PFOA) on alumina: Influence of solution pH and cations. *Water Res.* 45, 2925–2930.

628 Wang, W., Mi, X., Shi, H., Zhang, X., Zhou, Z., Li, C., Zhu, D., 2019. Adsorption behaviour and
 629 mechanism of the PFOS substitute OBS (sodium p-perfluorooctanesulfonate)
 630 on activated carbon. *R. Soc. Open Sci.* 6, 191069.

631 Wang, Z., DeWitt, J.C., Higgins, C.P., Cousins, I.T., 2017. A never-ending story of per-and
 632 polyfluoroalkyl substances (PFASs)? *Environ. Sci. Technol.* 51, 2508–2518.

633 Watanabe, S., Ohsaki, S., Hanafusa, T., Takada, K., Tanaka, H., Mae, K., Miyahara, M.T., 2017.
 634 Synthesis of zeolitic imidazolate framework-8 particles of controlled sizes, shapes, and gate
 635 adsorption characteristics using a central collision-type microreactor. *Chem. Eng. J.* 313,
 636 724–733.

637 Xiao, L., Ling, Y., Alsbaiee, A., Li, C., Helbling, D.E., Dichtel, W.R., 2017. β -Cyclodextrin
 638 Polymer Network Sequesters Perfluorooctanoic Acid at Environmentally Relevant
 639 Concentrations. *J. Am. Chem. Soc.* 139, 7689–7692. <https://doi.org/10.1021/jacs.7b02381>

640 Xu, J., Liu, Z., Zhao, D., Gao, N., Fu, X., 2020. Enhanced adsorption of perfluorooctanoic acid
 641 (PFOA) from water by granular activated carbon supported magnetite nanoparticles. *Sci.*
 642 *Total Environ.* 137757.

643 Xue, H., Chen, Q., Jiang, F., Yuan, D., Lv, G., Liang, L., Liu, L., Hong, M., 2016. A regenerative
 644 metal–organic framework for reversible uptake of Cd (II): from effective adsorption to in situ
 645 detection. *Chem. Sci.* 7, 5983–5988.

646 Yan, X., Lu, N., Fan, B., Bao, J., Pan, D., Wang, M., Li, R., 2015. Synthesis of mesoporous and
 647 tetragonal zirconia with inherited morphology from metal–organic frameworks.
 648 *CrystEngComm* 17, 6426–6433.

649 Yang, Y., Ding, Q., Yang, M., Wang, Y., Liu, N., Zhang, X., 2018. Magnetic ion exchange resin
 650 for effective removal of perfluorooctanoate from water: study of a response surface
 651 methodology and adsorption performances. *Environ. Sci. Pollut. Res.* 25, 29267–29278.

652 Zhao, H., Gao, J., Zhao, G., Fan, J., Wang, Yanbin, Wang, Yujing, 2013. Fabrication of novel
 653 SnO₂-Sb/carbon aerogel electrode for ultrasonic electrochemical oxidation of
 654 perfluorooctanoate with high catalytic efficiency. *Appl. Catal. B Environ.* 136–137, 278–286.
 655 <https://doi.org/10.1016/j.apcatb.2013.02.013>

656 Zhi, Y., Liu, J., 2016. Surface modification of activated carbon for enhanced adsorption of
 657 perfluoroalkyl acids from aqueous solutions. *Chemosphere* 144, 1224–1232.
 658 <https://doi.org/10.1016/j.chemosphere.2015.09.097>

659