



The Future of Layer-by-Layer Assembly: A Tribute to ACS Nano Associate Editor Helmuth Möhwald

Shuang Zhao,[†] Frank Caruso,^{‡,§,¶} Lars Dähne,[§] Gero Decher,^{||,⊥} Bruno G. De Geest,[#] Jinchun Fan,[¶] Neus Feliu,[†] Yuri Gogotsi,[§] Paula T. Hammond,[□] Mark C. Hersam,[■] Ali Khademhosseini,[○] Nicholas Kotov,[¶] Stefano Leporatti,[△] Yan Li,[▲] Fred Lisdat,[▽] Luis M. Liz-Marzán,[▼] Sergio Moya,[▼] Paul Mulvaney,[●] Andrey L. Rogach,^{††} Sathi Roy,[†] Dmitry G. Shchukin,^{‡‡} Andre G. Skirtach,^{§§} Molly M. Stevens,[¶] Gleb B. Sukhorukov,^{⊥,⊥} Paul S. Weiss,^{○,¶} Zhao Yue,^β Dingcheng Zhu,[†] and Wolfgang J. Parak^{*,†,▽}

[†]Fachbereich Physik, CHyN, Universität Hamburg, 22607 Hamburg, Germany

[‡]ARC Centre of Excellence in Convergent Bio-Nano Science and Technology, and the Department of Chemical Engineering, The University of Melbourne, Parkville, Victoria 3010, Australia

[§]Surflay Nanotec GmbH, 12489 Berlin, Germany

^{||}CNRS Institut Charles Sadron, Faculté de Chimie, Université de Strasbourg, Int. Center for Frontier Research in Chemistry, Strasbourg F-67034, France

[⊥]Int. Center for Materials Nanoarchitectonics, Ibaraki 305-0044, Japan

[#]Department of Pharmaceutics, Ghent University, 9000 Ghent, Belgium

[¶]Department of Chemical Engineering and Biointerfaces Institute, University of Michigan, Ann Arbor, Michigan 48105, United States

[§]Department of Materials Science and Engineering and A. J. Drexel Nanomaterials Institute, Drexel University, Philadelphia, Pennsylvania 19104, United States

[□]Department of Chemical Engineering, Massachusetts Institute of Technology, Cambridge, Massachusetts 02459, United States

[■]Department of Materials Science and Engineering, Northwestern University, Evanston, Illinois 60208-3108, United States

[○]Department of Bioengineering, Center for Minimally Invasive Therapeutics (C-MIT), California NanoSystems Institute (CNSI), University of California, Los Angeles, Los Angeles, California 90095, United States

[●]Michigan Institute for Translational Nanotechnology, Ypsilanti, Michigan 48198, United States

[△]CNR Nanotec-Istituto di Nanotecnologia, Italian National Research Council, Lecce 73100, Italy

[▲]College of Chemistry and Molecular Engineering, Peking University, Beijing 100871, China

[▽]Biosystems Technology, Institute for Applied Life Sciences, Technical University, D-15745 Wildau, Germany

[▼]CIC biomaGUNE, San Sebastian 20009, Spain

[○]Ikerbasque, Basque Foundation for Science, Bilbao 48013, Spain

[●]ARC Centre of Excellence in Exciton Science, School of Chemistry, University of Melbourne, Parkville, Victoria 3010, Australia

^{††}Department of Materials Science and Engineering, and Centre for Functional Photonics (CFP), City University of Hong Kong, Kowloon Tong, Hong Kong SAR

^{‡‡}Stephenson Institute for Renewable Energy, Department of Chemistry, University of Liverpool, Liverpool L69 7ZF, United Kingdom

^{§§}Nano-BioTechnology group, Department of Biotechnology, Faculty of Bioscience Engineering, Ghent University, 9000 Ghent, Belgium


^{¶¶}Department of Materials, Department of Bioengineering and Institute for Biomedical Engineering, Imperial College London, London SW7 2AZ, United Kingdom

^{⊥,⊥}School of Engineering and Materials Science, Queen Mary University of London, London E1 4NS, United Kingdom

^{¶¶}Department of Chemistry and Biochemistry and Department of Materials Science and Engineering, University of California, Los Angeles, Los Angeles, California 90095, United States

^βDepartment of Microelectronics, Nankai University, Tianjin 300350, China

ABSTRACT: Layer-by-layer (LbL) assembly is a widely used tool for engineering materials and coatings. In this Perspective, dedicated to the memory of ACS Nano associate editor Prof. Dr. Helmuth Möhwald, we discuss the developments and applications that are to come in LbL assembly, focusing on coatings, bulk materials, membranes, nanocomposites, and delivery vehicles.



The classic realization of layer-by-layer (LbL) assembly was introduced three decades ago,^{1–7} with significant contributions from our colleague, the late ACS Nano associate editor Helmuth Möhwald.^{8–33} Research on Langmuir–Blodgett deposition and later LbL assembly carried out by Helmuth Möhwald³⁴ created a critically important foundation for development of multilayer composites based on hybrid organic–inorganic nanostructures and numerous related technologies. Early studies in this area involved self-assembly of multilayers from graphite oxide,³⁵ clay sheets,³⁶ nanoparticles,^{8,37–42} and other materials, serving as conceptual growth points for the evolution of the fields of biomimetic composites, energy materials, and self-assembly. Numerous studies inspired and authored by Helmuth Möhwald not only paved the way for rapid expansion of nanoparticle-based design of nanocomposites, but also led to understanding biomineralization processes in Nature and their utilization in diverse areas of technology.⁴³ This field has since undergone massive expansion that continues to this day, and LbL is now an established and widely used technique for coating and encapsulation. With several publications per day, LbL assembly has matured from a scientific oddity to an accessible and useful tool for the preparation of nanoscale functional films. It continues to be used to create new commercial products, making it as interesting for various industries now as chemical vapor deposition (CVD) and physical vapor deposition (PVD) were in the 1960s. Whereas the past and the present of LbL have been extensively reviewed,^{11,44–50} in this Perspective, we focus on future opportunities using this exciting technique.

The classic realization of layer-by-layer assembly as a dip-and-rinse process has several conceptual advantages over other methods of materials preparation that predicated its wide use in science and technology. First, compared to other techniques,

Numerous studies authored and inspired by Helmuth Möhwald not only paved the way for rapid expansion of nanoparticle-based design of nanocomposites, but also led to understanding biomineralization processes in Nature and their utilization in diverse areas of technology.

for instance, sequential spin-coating, it enables preparation of nearly ideal conformal coatings on surfaces of any topography. Thus, it has been applied to planar surfaces, spherical particles, inside pores, and onto other more complex geometries.

Second, LbL is universal and flexible. It is compatible with other chemistries, meaning that a wide variety of different surfaces can be coated, not only charged substrates. The sequential assembly of the layers involves a washing step after the addition of each layer, which reduces the excess non-assembled materials or molecules. Because of the large variety of materials out of which layers can be formed, LbL enables convenient surface chemistry tailoring. Another important characteristic of LbL technology is the broad and independent variability of each double layer, which, in contrast to many other coating and encapsulation technologies, enables the modular construction of multifunctional devices like a box of bricks that have different properties and can be combined in different ways. These properties, combined with the availability of various stimuli^{51–55} to control responsiveness of polyelectrolyte assemblies, make LbL an extremely versatile technology platform. Third, the LbL method replicates the essential aspects of physics and chemistry of materials engineering in living organisms, and therefore, it leads to the amazing spectrum of biomimetic materials. Importantly, they may or may not be based on biomacromolecules pertaining to a specific biological process. Replicating the molecular-scale adaptation of the different structural components at the interfaces taking place in, for instance, biomineralization, one can attain structures and properties equal to or better than those of materials found in biology.⁵⁶ Note, however, that as with biology, many LbL processes require time for atomistic relaxation at the interfaces. Although the formation of multilayers approaching thermodynamic equilibrium is a rather time-consuming process, many future technologies will require such highly complex structures. This complexity will be illustrated below for some especially promising developments in this field. Of note are several successful reports of accelerating LbL processes using automated procedures on both planar and colloidal templates.^{57–61} In parallel, endeavors have also been undertaken to produce coatings with properties similar to those of LbL films but using single-step approaches.^{62–64}

In this Perspective, we highlight future directions with a focus on three areas: (1) functional **coatings** on planar and highly curved surfaces, (2) free-standing **membranes** and **bulk materials**, and (3) delivery vehicles based on **encapsulation** for biomedical applications.

LAYER-BY-LAYER-BASED FUNCTIONAL SURFACE COATINGS

Versatility of Coatings. Layer-by-layer coatings are extremely versatile. They enable variability in (1) composition, *i.e.*, the integration of different materials; (2) vertical structuring normal to the surface, *i.e.*, the possibility to create defined

sequences of layers;⁶⁵ and (3) anisotropic alignment, *i.e.*, to orient anisotropic materials within layers.

(1) **Toward Multinanocomposites.** Among all methods for functionalizing surfaces, LbL assembly arguably has the largest choice of deployable components (inorganic salts, organic molecules, polymers, DNA,^{66,67} graphene oxide, biomolecules, lipids, nanoparticles, or biological objects including cells⁶⁸). In polyelectrolyte multilayers, one can bring tens (if not hundreds) of materials together in ordered ways, whereas the number of components in most current nanocomposites is less than ~ 20 . The precision of LbL in controlling the structures of materials bridging the molecular, nano-, meso-, and micro-scales^{69–72} makes it possible to create conformal coatings with exceptionally high curvatures, including functionalized particles,^{73–76} and to design self-assembled nanocomposites with previously unexpected combinations of macroscale properties.^{36,69,77} Along these lines, LbL makes it possible to demonstrate the transition between nano- and macroscale optical effects in gold films experimentally by precisely tuning interparticle distances in multilayers of silica-coated gold nanoparticles,^{78,79} leading to extremely efficient substrates for surface-enhanced Raman scattering (SERS) detection.⁸⁰ The fundamental findings regarding rare combinations of properties made using LbL-based composites were confirmed using other techniques, such as vacuum-assisted filtration^{81–83} and spin-coating.⁸⁴ Layer-by-layer assembly enables the design and preparation of materials with adjustable multifunctionality, which is difficult, if not impossible, using other formulation technologies. Thus, LbL offers the tools to fabricate advanced materials by combining heterogeneous components with potential applications in optoelectronic devices, smart surfaces, solar cells, *etc.*

(2) **Toward Three-Dimensional (3D) Coatings.** The LbL technique also offers multiple approaches for the fabrication of composite materials from heterogeneous components, where the compositions of the materials are varied in the direction normal to the substrate. In addition to gradients in chemical composition, one can also vary the mechanical, optical, and electronic properties of composites in the vertical direction. The LbL concept can also be integrated with other nano- and microfabrication techniques. In particular, the use of printing strategies and combinations with other 3D coatings with variable vertical composition are possible. Combining LbL assembly with other modern strategies (*e.g.*, roll-to-roll, lithography, and 3D printing, *etc.*) as well as high-throughput production methods^{57,58,85–88} is beneficial for the preparation of novel functional LbL composites. Note that multilayer nanocomposites, made by LbL and Langmuir–Blodgett deposition, are extensively used in industry already, albeit produced using closely related, derivative methods. Some representative examples of these multilayer composites are those based on various forms of nanocarbons (graphene, graphene oxides, graphene, nanotubes, nanoribbons, graphene carbon quantum dots, *etc.*^{81,82,89–91}) and those based on various forms of ceramic nanoplatelets (clay, metal oxides, MXenes, *etc.*^{89,92–94}). The former are employed in energy technologies, whereas the latter are used in membrane and coating technologies. In each case, the composite multilayer production is reliable, scalable, and low cost due to self-assembly of anisotropic colloids. Future directions in multilayer biomimetic composites are likely to include computational design of the multilayers starting from molecular dynamics^{95–97} and coarse-grained models of the multilayers.⁹²

(3) **Toward Materials with Complex Anisotropies.** Most of the current materials are isotropic. Materials with anisotropic properties are, in general, more difficult to prepare and to characterize. For example, grazing incidence spraying⁹⁸ enables alignment of nanowires, nanorods, and nanofibers in plane^{99,100} during the deposition of individual layers in LbL films. With unidirectionally oriented multilayers, one can fabricate films containing ultrathin polarizers.¹⁰⁰ This approach, however, is capable of producing more complex anisotropies, even over large surface areas, by changing the direction of alignment in each individual layer of a multilayer film. We are just starting to realize materials with crisscross and even helical superstructures. Materials with such anisotropies are likely to be interesting for various applications in mechanics, photonics, and other areas.

Protective Coatings. Layer-by-layer assembly provides a convenient coating strategy for the protection of consumer products, such as paints for corrosion protection or antigraffiti coatings.^{101–104} Here, among the spectrum of technological advances based on LbL materials, one should mention anticorrosion coatings investigated by Möhwald and co-workers. Andreeva *et al.* deposited oppositely charged (PEI/PSS)_n polyelectrolyte (PE) multilayers on aluminum surfaces.¹⁰² The corrosion processes on the aluminum surfaces were blocked due to the pH-buffering ability of polyelectrolyte-based LbL coatings (Figure 1a). Another representative advance in this area is halloysite nanocontainers for anticorrosion coatings. Shchukin *et al.* first deposited LbL-assembled polyelectrolyte multilayers of (PAH/PSS)_n on the surfaces of inhibitor-loaded halloysite nanotubes.¹⁰⁵ After the halloysite nanocontainers were embedded, the sol–gel SiO₂/ZrO₂ active composite coatings with the nanocontainers showed long-term anticorrosion performance. The LbL composite multilayers provide effective storage and prolonged release of the inhibitor. Similarly, SiO₂ particles coated with LbL multilayers entrapping inhibitors were used as nanocontainers to achieve self-healing and anticorrosion composite coating simultaneously.^{18,103} Li *et al.* also designed a silica/polymer double-walled hybrid nanotube loaded with active molecules for metal corrosion protection.¹⁰⁶ A new generation of anticorrosion coatings that possess passive matrix functionality and that actively respond to changes in the local environment has been introduced.¹⁰⁷ Active corrosion protection aims to *restore* the properties of the material when the passive coating matrix is broken and corrosion of the substrate has started. The main component of the self-healing anticorrosion coatings are capsules in flat layers, which provide controlled release of the corrosion inhibitor on demand and only inside the corroded area (see Figure 1a). This release acts as a local trigger for the mechanism that heals the defects. The LbL assembly approach is an effective tool for the fabrication of the capsule shells, controlling release of the corrosion inhibitor on demand. Layer-by-layer assembly enables the use of various materials as shell components, utilizing weak, mostly electrostatic forces for their assembly. Depending on the nature of the “smart” materials (*e.g.*, polymers, nanoparticles) introduced into the container shell, different stimuli can induce reversible and irreversible shell modifications: pH, ionic strength, temperature, ultrasonic treatment, and electromagnetic fields. The different responses that can be observed vary from fine effects, such as tunable permeability, to more profound ones, such as total rupture of the container shell. These different behaviors depend on the composition of the polyelectrolyte multilayers (*e.g.*, weak polyanion–weak polycation or strong polyanion–weak polycation-based interactions).




Figure 1. (a) Layer-by-layer assembly can be used in protective coatings in several ways, *e.g.*, as nanoreservoirs of corrosion inhibitors and in multicomponent coatings. (b) Layer-by-layer assembly can be used for biomolecule immobilization in sensing devices and biofuel cells. (c) Layer-by-layer assembly can be used in photoelectrochemical devices to create 3D structures; in medical devices, different biological materials can be assembled in each layer independently. (d) Tailored coatings for better control of cell–surface interactions. (e) Layer-by-layer assembly can be used in antibacterial coatings of implants.

Coatings for Photonics and Energy-Related Applications. There are numerous energy applications that can take advantage of the tunable mechanical, electrical, and chemical properties of LbL composites.¹⁰⁸ In fact, the first implementation of graphene composites on electrodes currently used in a variety of batteries, supercapacitors, conductive inks, and fuel cells was demonstrated in LbL composites referring to these materials as graphite oxide in 1996.³⁵ The excellent laminar organization of the films also afforded demonstration of the

transition from the nonconductive state of graphite oxide to reduced graphene and their utilization in lithium batteries.¹⁰⁹ Composite materials with identical layered design were later produced by other techniques, such as vacuum-assisted filtration, are widely used in the technology.⁸¹ There are also many other energy-conversion devices that employ LbL multilayers from electroconductive materials which include batteries, supercapacitors, catalysts, solar cells, and fuel cells, and these modern applications frequently place higher demands on the performance

of the composites.¹¹⁰ Layer-by-layer multilayers can integrate the properties of different constituent materials, and judicious design enables them to take on multiple roles and functionalities, for instance, as battery anodes or ion-transporting membranes.^{111–113} Layer-by-layer assembly also facilitates the creation of controlled assemblies to study photonic properties of materials. Layer-by-layer assembly enables composite functional materials that combine polymers with oppositely charged nanoparticles. Such structures can easily be created on planar substrates^{114–117} and on colloidal microspheres.^{23,118–120} The organized superstructures from semiconductor nanoparticles (NPs), also known as quantum dots (QDs), can also be made using LbL as was demonstrated for CdS, PbS, and TiO₂.¹²¹ The advantage of QDs compared to graphite/graphene oxide is that they are capable of emitting in the visible^{114,122} and near-infrared¹²² parts of the spectrum; this property has been used to fabricate luminescent self-assembled films and to study energy transfer in such composites.¹¹⁵ Directed energy transfer from specific layers of QDs toward an interface or electrode was made possible exactly due to the possibility of arranging the LbL layer in the order of decreasing or increasing band gaps in graded semiconductor nanostructures.¹²³ Excitation recycling in LbL-grown graded band gap QD structures has been demonstrated¹¹⁶ and ascribed to superefficient exciton funneling to the layer containing the largest QDs.¹¹⁷ Besides graphene, layer-by-layer assembly is also compatible with other emerging two-dimensional (2D) materials such as hexagonal boron nitride whose LbL coatings yield exceptional performance as gate dielectrics in graphene field-effect transistors.¹²⁴ Last but not least, LbL has been used to build coatings for electromagnetic shielding. Flexible and electrically conductive thin films are required for electromagnetic interference (EMI) shielding of portable and wearable electronic devices.⁹³ The LbL technique enables combinations of nanoparticles and polymers, providing a platform for developing hierarchical architectures with a combination of properties including mechanical strength, transparency, and conductivity.⁸⁹ Spin-spray LbL enables rapid assembly of 2D Ti₃C₂ MXene–carbon nanotube (CNT) composite films for EMI shielding. These semitransparent LbL MXene–CNT composite films showed high conductivities and high specific shielding effectiveness, which are among the highest reported values for flexible and semitransparent composite thin films.

Biomolecule Immobilization for Sensing and Biofuel Cells. The LbL technique has found widespread applications in the fixation of biomolecules to surfaces^{49,125} because it enables (1) engineering of man-made materials with structural analogy to biomaterials; (2) the controlled deposition of biomolecules because deposition can be governed not only by the number of layers but also by adjusting pH, ion concentration, temperature, and polyelectrolyte and biomolecule concentrations in each layer; (3) the defined integration of different biomolecules in different layers and, thus, the creation of sequential signal chains; and (4) the incorporation of other functional components, such as mediators, which can facilitate electron transfer between immobilized molecules and electrodes or lipids, which, in turn, facilitates integration of more hydrophobic membrane proteins.¹²⁶ Furthermore, additional layers on top of the biomolecular assembly enhance the stability of the coatings and ensure efficient discrimination against unwanted species when the multilayer structure is used for sensing purposes. Interestingly, biomolecules cannot simply be passively incorporated into LbL architectures, but because they

often carry charges, they can be used as separate building blocks in the assembly process. In this context, alternating polymer/biomolecule or NP/biomolecule structures can be formed,^{127,128} as well as pure biomolecular LbL assemblies, such as DNA/protein or protein/protein multilayers.¹²⁹ The beauty of the technique can also be demonstrated by immobilizing different biomolecules in different layers on the sensing surface. This localization enables the construction of defined signal pathways by exploiting sequential reaction schemes. Here, reaction products formed in one layer can be further converted in a subsequent layer, as shown in Figure 1b.¹³ These artificial architectures can mimic biological functions, such as sequential electron transfer reactions or switchable pathways.¹³⁰ This capability enabled, for instance, the first implementation of tissue-adapted neuroprosthetic implants from conductive composites¹³¹ and light-induced excitation of neurons.¹³² Further steps in this directions can be based on direct electron transfer between the immobilized protein molecules. The LbL technique enables the artificial arrangement of redox centers, while keeping them in or close to their natural states. Here, developments are still at early stages—more advanced structures appear to be feasible though, such as the arrangement of enzymes into complex cascades to create artificial metabolome structures with high efficiency.^{133–135}

Switchable Coatings for Photoelectrochemistry. Electrochemical devices can be controlled by light based on photosensitive switches, such as QDs.^{136–139} Light-generated charge carriers can create photo currents, which enables both control and monitoring of electrochemical reactions (see Figure 1c).¹⁴⁰ Inorganic, photoactive materials such as QDs are commonly used in such applications, but light-sensitive

The layer-by-layer technique enables combinations of nanoparticles and polymers, providing a platform for developing hierarchical architectures with a combination of properties including mechanical strength, transparency, and conductivity.

biomolecules have also gained considerable interest for the conversion of light into electrical or chemical energy.¹⁴¹ An example is the protein supercomplex photosystem I, which can be assembled with the help of negatively charged DNA and the positively charged redox-protein cytochrome *c*. This system generates well-defined photocurrents, the magnitude of which depends on the number of deposited layers.¹⁴² Charge transfer in LbL structures has been well-studied by numerous groups.^{14,17,127,143–145} Layer-by-layer assembly can be used to increase the coverage of redox active molecules by assembling 3D structures, thereby dramatically increasing the analytical signal, but also improving the signal-to-noise ratio (SNR).^{146,147} The response from multilayer structures is significantly enhanced compared to the response from single monolayer-based structures. In addition, different kinds of biological modifications can be introduced to the LbL structures of the photoelectrochemical devices. For example, LbL offers the convenient possibility to immobilize enzymes, thereby controlling redox reactions close to the light switches as fixed on the surface of the electrodes. The porous structures of LbL films enable sub-

strates to reach the enzymes and cosubstrates or reaction products, such as O_2 or H_2O_2 , to reach the light switches.^{148–150} In the future, we expect antibodies and DNA to be incorporated as recognition elements into LbL-based structures. Creating defined sequences of antibodies or oligonucleotides within the 3D assemblies is also an important goal.^{151,152} There is great potential for photoelectrochemical devices to be developed that can sense multiple analytes in parallel. Layer-by-layer structures can also introduce good biocompatibility by modifying working electrodes in such a way that applications in cell-based detection become possible. The detection of several metabolites will enable more specific studies of cellular activities.¹⁵² Moreover, the biocompatibility and the ease of preparation of LbL-based systems will enable the fabrication of miniature sensors for human uses such as wearable health monitors and portable environmental monitoring devices. In addition, electrochromic coatings can be produced by self-assembly of 2D titanium carbide ($Ti_3C_2T_x$) MXene and gel electrolyte with a visible absorption peak shift from 770 to 670 nm and a 12% reversible change in transmittance with a switching rate of <1 s when cycled in an acidic electrolyte under applied potentials of less than 1 V.¹⁵³ The LbL film can act as both transparent conductive coating and active material in an electrochromic device, opening avenues for a number of optoelectronic, sensing, and photonic applications. Hybrid systems prepared by LbL assembly of polyoxometalate clusters and poly(4-vinylpyridine) also show reversible electro- and photochromic behavior.^{154,155}

Tailored Coatings for Better Control of Cell–Surface Interactions. For many applications, detailed understanding of the interface between cells and underlying substrates is critical.^{156,157} It is well established that LbL assembly offers a means to immobilize different biomolecules on surfaces using mild deposition conditions (see Figure 1d).¹⁵⁸ Layer-by-layer assemblies can integrate plasmids,¹⁵⁹ growth factors,¹⁶⁰ proteins, genetic material, antibodies, and antibiotics directly into the layers or the components can be precomplexed with polyelectrolytes and then assembled as complexes.¹⁶¹ For such biological components, e.g., for growth factors, their action can be extended in time¹⁶² or triggered by external stimuli, whereas their controlled release can be regulated by barrier layers. Multilayers can be prepared from biocompatible polyelectrolytes and their mechanical properties; wettability, and interactions with proteins and cells, can be fine-tuned by chemical cross-linking, thermal annealing,¹⁶³ or the addition of nanoparticles into the assembly (see Figure 2).¹⁶⁴ This strategy enables the availability of biomolecules on surfaces to be controlled.^{162,165,166} Imagine chemically identical surfaces (composition, roughness, etc.), below which nanoreinforced strata are hidden (i.e., deposited) that enable control of the tensile strength of the interface. Other combinations of surface properties can be deposited on top of cell-culture gels. Such surface engineering would be extremely useful for implants and scaffolds as a means to enhance cell adhesion, mobility, and differentiation. In the long term, there are numerous different ways for the LbL technique to be implemented. For example, they can be used to modify scaffolds and implants to create customized environments and interfaces in tissue engineering. Layer-by-layer assembled surfaces can also be laterally patterned as substrates for the growth of cells. Micropatterned deposition of LbL films has been used to generate architecturally organized cellular structures that better mimic the complex microstructures of tissues in the body. For example, patterned cocultures were generated by sequentially




Figure 2. Scheme of the protein adhesion mechanism and the effects on cell adhesion for non-annealed poly(L-lysine/alginate) (PLL/Alg) and annealed-PLL/Alg.¹⁵⁷ Results from the exchangeability assays are schematically described. On annealed PLL/Alg layer-by-layer (LbL) surfaces, proteins exhibit augmented interactions with the substrate, the exchangeability is reduced, and fibronectin (FN), either alone or in cooperation with bovine serum albumin (BSA), has stronger interactions with the LbL surface coating. The effect on cell adhesion is also illustrated.¹⁶⁹ The objects depicted in the scheme are not to scale, and for FN, only the FN III fragment is represented. Adapted with permission from ref 150. Copyright 2019 John Wiley & Sons, Inc.

depositing micropatterned LbL films made of hyaluronic acid and polylysine or collagen that could be used to render regions of a surface adhesive to cells.^{167,168} In such cultures, patterned cocultures of liver cells and fibroblasts showed increased functionality compared to various controls.

This strategy ultimately results in a multitude biomimetic composites including those made in bulk form. The diverse composite structures replicated using LbL assembly^{170–173} made possible *ex vivo* replication of nacre,³⁶ enamel,¹⁷⁰ extracellular matrix,^{174,175} and models of cellular organelles.^{176–178} By combining LbL assembly with other fabrication techniques at the micrometer and millimeter scale, tissue replicas with

Micropatterned deposition of layer-by-layer films has been used to generate architecturally organized cellular structures that better mimic the complex microstructures of tissues in the body.

complex geometries have been obtained, such as for bone marrow.^{179,180} The exceptional materials properties of the multilayer composites and the generality of the approach have also made possible the design, fabrication, and implementation of implantable devices,^{132,181,182} sensors,^{53,183,184} drug-delivery vehicles,^{185,186} and optical devices,^{187,188} exceeding the performance of existing technologies.

Antibacterial Surface Coatings. The advent of LbL films has led to several new strategies for the development of antibacterial coatings, from the fabrication of multilayers with




Figure 3. Changes in cell adhesion and in the physicochemical properties of layer-by-layer (LbL) multilayer coatings induced by thermal annealing.¹⁵⁷ (a) Scheme of the assembly and annealing protocols. (b) Phase contrast images of C2C12 cells adhered on glass, poly-L-lysine/alginate (n-PLL/Alg, a-PLL/Alg), n-chitosan/hyaluronic acid (n-Chi/HA), or a-Chi/HA as indicated. (c) Average cell adhesion spreading area from cells seeded on glass, n-PLL/Alg, a-PLL/Alg, n-Chi/HA, or a-Chi/HA polyelectrolyte multilayers. (d) Changes in physicochemical properties of polyelectrolyte multilayers upon annealing. Adapted with permission from ref 150. Copyright 2019 John Wiley & Sons, Inc.

cationic polymers that disrupt bacterial membranes,¹⁸⁹ to the assembly of antibacterial nanomaterials such as silver nanoparticles or graphene oxide,¹⁹⁰ to the encapsulation of antibiotics in the multilayers, to combinations of all these elements.¹⁹¹ The LbL assembly can include several layers of nanomaterials, combine layers of different nanomaterials in a film, or facilitate inclusion of antibiotics in the films by complexing with the polymers (see Figure 1e). Many antibiotics have charged groups that can be used to form complexes with polyelectrolytes in the LbL films or assembled in films replacing polyelectrolyte layers. The LbL technique has the advantage that it can be applied straightforwardly on almost any charged surface, and antibacterial coatings could be developed for medical devices as well as for implants. In particular, the LbL technique has significant potential in the design of antibacterial coatings that can inhibit nosocomial infections during implant surgery. An optimal antibacterial coating for bone implants based on release of an antibiotic should involve an initial burst release at the time of surgery, followed by prolonged release over the weeks following the surgical intervention to ensure bone tissue regeneration.¹⁹² The LbL technique can be used to design films capable of fully or partially degrading and releasing antibiotics at different times and rates. Examples in the literature show that aminoglycans, such as gentamicin, can be released from LbL films, combining burst and steady releases that would be particularly suitable for implant surgery.¹⁹³ Moreover, the LbL technique enables the additional assembly of growth factors on the coating that can counteract negative effects on cell growth and differentiation caused by a high localized dose of anti-

biotics.¹⁹⁴ These combinations can result in films with enhanced antibacterial properties and in the design of coatings suitable for different environments in multiple medical settings or for antifouling applications.

LAYER-BY-LAYER-BASED MEMBRANES

Purification Technologies. Another future for LbL coatings lies in separation technologies, such as liquid or gas permeation membranes (see Figure 4).^{69,195,196} Significant pioneering work has already been carried out,^{197–201} starting with gas separation membranes,⁶⁹ but recently, LbL membrane modification for fresh water production has been explored further. Nanofiltration membranes for the removal of particles down to virus sizes of ~35 nm are not able to retain dissolved materials, such as ions, leading to issues with water hardness, low molecular weight pharmaceutical agents, *etc.*, which become increasingly problematic in fresh water preparation. However, reverse osmosis (RO) membranes consume a great deal of energy and retain all salts, which is not useful for drinking water. In contrast, a few LbL-assembled layers of poly(diallyldimethylammonium chloride) (PDADMAC)/PSS on top of tubular filtration membranes of pore size 20 nm are able to increase the retention of magnesium sulfate from 5% to over 90% and for several endocrines above 50–90% depending on the endocrine type (see Figure 5).²⁰² In contrast to RO membranes, these LbL membranes allow permeation of sodium chloride, maintain high fluxes, and require much less pressure and energy. Up to now, the LbL coating of membranes has been evaluated only for films based on the




Figure 4. Layer-by-layer (LbL) assembly can be used for membranes for gases and liquids.

combination of one polycation with one polyanion. However, one can imagine that a multifunctional coating could improve the membranes further. The first layer on the membrane has to ensure a good connection of the LbL film to the membrane in order to resist sufficiently high-pressure back-flushing cycles. Furthermore, the first polyelectrolyte has to be assembled exclusively on top of the pores and should not penetrate into the pores, as otherwise these would be blocked. The intermediate layers should utilize a design in which the mesh size controls the retention of the analyte and also ensures the removal of specific pollutants.⁹¹ Finally, the outermost layer should reduce the fouling behavior of the membranes by controlling its hydrophilic properties and electrostatic repulsion.^{203–205}

Introducing Channels in Biological Membranes.

Biomimetic nature of LbL materials opens the possibility to replicate biological membranes. Cell membranes comprise not only lipids but also high protein content,²⁰⁶ for example, trans-membrane proteins that form channels for molecular transport into/out of cells. Lateral inhomogeneity is important. Here lies one big challenge for the future. To date, LbL structuring has predominantly only been possible perpendicular to the surface,

i.e., by variation of the compositions of the different layers. However, in order to create LbL-assembled membranes mimicking the function of biological membranes—for example, with integrated protein-based channels—lateral structuring would also be required. In the simplest case, “channels” in the form of holes could be introduced, for example, by nanoplasmonic heating.²⁰⁷ Another option lies in tethered membranes. In recent work, dense membranes with limited defects and high resistivity were assembled on top of multilayers.^{208–211} These membranes can contain channels with selective ion permeability.²¹² For electronic sensing, the multilayers provide a means to control the distance of the lipid bilayer from the electrodes, which is particularly useful for membranes incorporating channels and transmembrane proteins, avoiding undesired effects from the electrode on channel and protein behavior.²¹² Another method for lateral structuring might be based on the fusion of microcapsules.²¹³ Still, despite the numerous ideas outlined here, lateral structuring of LbL films remains a challenge.

LAYER-BY-LAYER-BASED ENCAPSULATION FOR DELIVERY VEHICLES

Layer-by-layer Assembly for Encapsulation. Layer-by-layer technology for micro- and nanoencapsulation was introduced ~20 years ago and initially looked extremely promising (see Figure 6).^{10,11,214–219} The key advantage was considered to be the simplicity with which one could construct multifunctional delivery systems. In fact, LbL capsules can combine multiple functions and external responsiveness. However, LbL-based encapsulation suffers from high permeability of small, water-soluble molecules (*i.e.*, leaching) and rather time-consuming processes for fabrication. Some of these problems have been solved, such as expanding the class of molecules that can be encapsulated (*e.g.*, doxorubicin, paclitaxel, liquid crystals, siRNA) without severe leaching,^{44,45,220–225} and inroads have been made into the problem of scale-up.^{61,226,227} This approach has also been made possible by extending the initial capsule geometries to more sophisticated structures, such as capso-somes, *etc.*^{228–235} The capsule shells can also be labeled with different types of nanoparticles, providing contrast for imaging^{118–120} or enabling magnetic targeting.^{236,237} Currently, the technology still has potential, particularly in areas where other technologies are not available. A number of studies on various cell types, including macrophages, dendritic cells, neurons, and stem cells, have




Figure 5. Retention of different endocrines by an uncoated poly(ether sulfone) membrane (red) and by a layer-by-layer (LbL)-coated (PDADMAC/PSS)₄ membrane (green). Unpublished data by the group of Lars Dähne.




Figure 6. Layer-by-layer (LbL) assembly can be used to fabricate encapsulation platforms for nanodelivery.

demonstrated that incubation with cells results in internalization of capsules by cells without significant effects on cell viability.^{238–240} The elastic properties facilitate their uptake as the capsules can easily be deformed during internalization.^{241–244} In other words, cells were found to tolerate capsule internalization, which is not always the case for other delivery systems. Detailed studies on the tissue response after subcutaneous²⁴⁵ and pulmonary²⁴⁶ administration of degradable LbL capsules composed of polypeptide and polysaccharide building blocks have also demonstrated that LbL capsules exhibit a moderate foreign body response and are easily internalized by immune cells, such as macrophages and dendritic cells. This advance should pave the way for further development of such carriers in advanced vaccine technologies. In summary, LbL offers a good platform for delivery of encapsulated cargo inside cells, which is discussed below in terms of drug delivery and imaging/sensing. Because the capsules remain in endosomes/lysosomes after internalization, endosomal escape and translocation of encapsulated compounds to the cytosol remains a significant hurdle.

Delivery of Therapeutic Agents. The LbL technique opens the possibility of assembling therapeutics in between layers of polyelectrolytes, on top of nano/microparticles that protect a certain cargo, while, at the same time, making multiple functional groups available in the polyelectrolyte, which can be engineered to generate stealth coatings for targeting delivery. For the delivery of encapsulated therapeutics in polyelectrolyte multilayers, the assemblies must degrade, liberating the material entrapped between the layers. However, as we noted above, LbL assemblies have intrinsically semipermeable properties that can be tuned by means of layer numbers and thicknesses as well as by the type of the interacting polyelectrolyte pairs, resulting in leaching even before intended degradation and subsequent release. Thus, the initial euphoria in scientific articles to encapsulate low molecular weight drugs and to release them in a controlled manner on demand has not yet translated into real-world applications. As previously noted, the most critical reason for this difficulty in translation is the high permeability of the films for small molecules (see Figure 7). Even for the very dense polyelectrolyte system poly(allylamine hydrochloride)/polystyrenesulfonate (PAH/PSS), researchers recorded release rates ranging from minutes to a few hours for water-soluble molecules having molecular weights below 5 kDa.²⁴⁷ In contrast, large molecules with molecular weights above 10 kDa can be permanently immobilized, either in the polyelectrolyte

layers or in capsules comprising polyelectrolyte walls. This same conclusion has been shown over the past decade for a variety of biomolecules, including proteins, such as antibodies;²⁴⁸ growth factors;²⁴⁹ hormones;²⁵⁰ enzymes;²⁵¹ nucleic acids, such as DNA plasmids;²³⁷ different types of RNA molecules, such as silencing RNAs;²⁵² and polysaccharides such as alginate, carrageenan, chitosan, and hyaluronic acid.²⁵³

In parallel, new therapeutic avenues based on the delivery of high molecular weight drugs, for instance, at the site of the implantation of LbL material.¹⁵⁹ Plasmids, specific antibodies, RNA, or DNA can be delivered by incorporation in LbL films and can be utilized as personalized medicines. However, due to the sensitive and specialized recognition of such molecules by our immune system, it is hard to deliver them efficiently *in vivo* to the intended targets. For this purpose, LbL assemblies could have a bright future in the form of capsule formulations, because the necessary multifunctionality can be delivered by LbL technology. For example, an ideal capsule should have an inner surface that is not interacting with the biomolecule in order to retain its functionality. The intermediate layers determine the release behavior, which could be controlled slow release, immediate release caused by an internal trigger (e.g., by




Figure 7. Permeability of layer-by-layer (LbL) membranes consisting of different polyelectrolyte combinations (8 layers) for small molecules (fluorescein). Unpublished data from the group of Lars Dähne.

the lower pH value in cancer cells or by specific enzymatic surroundings^{254,255}) or release activated by an external trigger (e.g., NIR light,^{22,237,256–258} X-ray radiation, ultrasound (US),^{259–261} or magnetic fields^{262,263}). Internal triggers can readily be created by combining polycations and polyanions in such a way that their degradation will be fast or slow. The sequential assembly of polyelectrolytes in LbL enables control over the composition of the layers in the vertical direction and could be used to deliver different therapeutics progressively. For example, two siRNA molecules with complementary actions could be assembled in different positions within the LbL film, so that they are released sequentially. Degradation of the multilayers in biological fluids or intracellularly can be selected because matrices can be programmed by varying the assembly conditions, the number of assembled layers and the combination of polycations and polyanions. The surface layer is also important: It should not be recognizable by the immune system in order to realize high circulation times, but it should nonetheless bind specifically to a defined target. In the case of systemic delivery, there is the problem of targeting, *i.e.*, to produce locally enhanced concentrations of the pharmaceutical agent at the desired target site. One interesting approach, which has not yet been fully exploited, is cell-mediated delivery, where cells are used as natural transporters to carry the encapsulated materials to a targeted site.²⁶⁴ Here, externally driven cell navigation could be used.²⁶⁵ *In vitro* studies have demonstrated that cell motion is possible in magnetic field gradients if the cell has internalized magnetic capsules.²⁶⁶ Magnetic capsules can bring genetic materials inside the cells and reprogram the cells in such a way that the follow-up sorting of altered and nonmodified cells can easily be done by magnetic sorting.²⁶⁷ Such magnetic targeting is biocompatible. The ability of mesenchymal stem cells (MSCs) to differentiate was not affected by magnetic manipulation.²⁶⁸ This is important, as MSCs impregnated with capsules could be used as natural cargo transporters. Also, whereas many applications focus on systemic delivery, local delivery may offer new approaches, which deliberately avoid the “targeting” issue. One interesting example is LbL particles that were designed for transdermal delivery of vaccine and adjuvant peptides *via* hair follicles. In contrast to dissolved molecules, particles in sizes ranging between 300 and 900 nm can be inserted in hair follicles by intense massage.²⁶⁹ The diffusion of vaccines to the Langerhans cells in the skin is much easier through the follicle membrane than through the epidermis. In order to transport the vaccine peptides into the hair follicle, 600 nm silica particles were coated with polymethacrylate with LbL assembly, with an outermost layer having a pK_a value of 6.2. The pH difference between skin (pH 5–5.5) and follicle center (pH 7.4) was selected for the delivery of the peptides, which were tagged with four glutamic amino acids bearing negative total charge. The vaccines were efficiently adsorbed at pH 4.5 onto the partly positively charged particles and kept stably attached during the skin massage. After arriving at the follicle center where the pH was 7.4, the zeta-potential of the particles switched and became highly negative and the vaccines were released due to electrostatic repulsion. In general, LbL capsules have made the step from *in vitro* demonstration to *in vivo* experiments. For example, these particle systems can induce bone formation *in vivo* (when loaded with growth factors),²⁴⁹ target atherosclerotic plaques *in vivo*,²⁷⁰ and generate a significant immune response *in vivo* (when loaded with immunogenic peptides).²⁷¹ Both peptide- and protein-antigen-loaded LbL capsules generate a significant immune response *in vitro* and

in vivo.²⁵⁴ It was demonstrated that ovalbumin (OVA) (a model vaccine)-specific CD4 and CD8 T cells were activated to proliferate *in vivo* following intravenous²⁷¹ and subcutaneous²⁷² vaccination of mice with OVA protein- and OVA peptide-loaded LbL capsules. The OVA encapsulated within the capsules resulted in greatly enhanced antigen presentation and proliferation of antigen-specific CD4 and CD8 T cells that provided enhanced protection against viral infection and tumor growth. Furthermore, LbL capsules could be further engineered on their surface with immune-stimulatory molecules to boost the antigen-specific immune responses against encapsulated antigen.²⁷³ The latter work was carried out with the idea of using LbL-coated microneedles for transdermal vaccination. Indeed, several groups have investigated codelivery of antigen and immune stimuli, both on colloidal and planar substrates.^{273–275}

Imaging and Sensing. In diagnostic imaging, highly developed methods/modalities are applied, such as ultrasound imaging (US), X-ray computed tomography (CT), magnetic resonance imaging (MRI), near-infrared imaging (NIR), photoacoustic imaging (PAI) and nuclear imaging methods such positron emission tomography (PET) or single photon emission computed tomography (SPECT). Each of these imaging methods has advantages, but also drawbacks, such as limited spatial or time resolution, sensitivity, impairment of the patient, *etc.* Therefore, several methods must be combined in order to optimize the images and information obtained.²⁷⁶ Instruments for this purpose are already under development, but suitable contrast agents providing contrast for different imaging modalities and methods are also necessary. These agents can be based on molecular materials or on particles. Solid particles should be in the nanometer range, whereas flexible particles could be used at the micron scale of erythrocytes. By means of LbL technology, such multifunctional contrast agents can be produced in a controlled way. One example was recently developed, which is simultaneously applicable for US, MRI, SPECT, and NIR imaging.²⁷⁷ The core of the flexible 3 μm particles consisted of an air bubble, which is stably encapsulated by cross-linked poly(vinyl alcohol) (PVA) for US imaging. Positive charges were introduced in the PVA matrix in order to achieve controlled LbL coating. Two double layers of PSS/PAH-1,4,7-triazacyclononane-1,4,7-triacetic acid (NOTA) were assembled. The NOTA label complexes technetium for SPECT imaging. On top, double layers of citrate-stabilized iron oxide nanoparticles (SPION)/PAH were assembled for dark contrast in MRI imaging.²⁷⁸ For NIR imaging, further fluorescent layers of PAH-Cy5/PSS were assembled. Finally, targeting was demonstrated by biotinylated antibodies coupled to an outermost PAH/streptavidin layer.^{279,280} Thus, LbL enables convenient integration of different contrast modalities in one single particle. Apart from simple imaging, where contrast depends on the local concentration of contrast agent, functional imaging, *i.e.*, sensing, is possible. In this case, the signal of the contrast agent also depends on the local environment. There are several examples of encapsulated, analyte-sensitive fluorophores,^{281–283} which enable the detection of local ion concentrations. The changes in environment must be taken into account when designing these multimodal particles. For example, many ion-sensitive fluorophores also respond to local pH, so one severe challenge concerning future *in vivo* applications is that particles will undergo massive local pH changes along their trajectories in the body, for example, upon endocytosis by macrophages. One solution might be to use more complex systems, such as sensors with distance-dependent




Figure 8. Glucose sensing in layer-by-layer (LbL) capsules, containing ConcanavalinA (ConA) and Dextran (Dex), labeled with fluorescence resonance energy transfer (FRET) pair. Unpublished data from the group of Lars Dähne.

quenching of optical or magnetic signals. In order to protect these systems from agglomeration, they could be encapsulated. The LbL shell around the sensors would then enable analytes to diffuse in and out, whereas it would retain and protect the actual sensor system. One developed glucose microsensor is depicted in Figure 8. Due to the possibility of multicompartment encapsulation of different molecules in different locations within one particle by LbL,²⁸⁴ even feedback-controlled systems might be developed. A drug could be encapsulated for delivery in one compartment, whereas a sensor monitoring the action of the drug could be placed in an adjacent compartment.^{285,286}

Challenges for Layer-by-Layer Coated Particles Intended for *in Vivo* Use. Following the above-outlined possibilities for applying LbL-based particles to *in vivo* delivery and imaging/sensing, one can summarize a number of key challenges for the future. (1) Highly biocompatible and biodegradable materials need to be developed and used. (2) Further fundamental studies need to be undertaken to understand the interactions of LbL particles and biological systems in order to probe parameters such as elasticity and shape and how these influence biological

By means of layer-by-layer technology, multifunctional contrast agents for diagnostic imaging can be produced in a controlled way.

responses. (3) Automation of the preparation of LbL particles should be further developed, as this capability is critical to reproducibility and streamlining preparation. (4) More focus should be placed on such particles for local delivery applications (e.g., their use as depots) and their interactions with the local cellular and protein environment, not only limiting their studies to systemic delivery applications. Thus, the development of LbL-based vehicles continues and important breakthroughs lie ahead.

AUTHOR INFORMATION

Corresponding Author

*E-mail: wolfgang.parak@uni-hamburg.de.

ORCID

Frank Caruso: 0000-0002-0197-497X

Gero Decher: 0000-0002-7976-8818

Bruno G. De Geest: 0000-0001-9826-6170

Jinchen Fan: 0000-0002-8905-1693

Neus Feliu: 0000-0002-7886-1711

Yury Gogotsi: 0000-0001-9423-4032

Paula T. Hammond: 0000-0002-9835-192X

Mark C. Hersam: 0000-0003-4120-1426

Ali Khademhosseini: 0000-0002-2692-1524

Nicholas Kotov: 0000-0002-6864-5804

Stefano Loporatti: 0000-0001-5912-7565

Yan Li: 0000-0002-3828-8340

Luis M. Liz-Marzán: 0000-0002-6647-1353

Sergio Moya: 0000-0002-7174-1960

Paul Mulvaney: 0000-0002-8007-3247

Andrey L. Rogach: 0000-0002-8263-8141

Sathi Roy: 0000-0002-0645-5386

Dmitry G. Shchukin: 0000-0002-2936-804X

Andre G. Skirtach: 0000-0002-4468-7620

Molly M. Stevens: 0000-0002-7335-266X

Gleb B. Sukhorukov: 0000-0001-6213-0562

Paul S. Weiss: 0000-0001-5527-6248

Wolfgang J. Parak: 0000-0003-1672-6650

Author Contributions

⊗ Authors are listed in alphabetic order.

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

S.Z. was supported by the Chinese Scholarship Council (CSC). F.C. acknowledges the award of a National Health and Medical Research Council (NHMRC) Senior Principal Research Fellowship (APP1135806) and support from the Australian Research Council Centre of Excellence in Convergent Bio-Nano Science and Technology (Project No. CE140100036). L.D. thanks the BMBF (topical vaccination) and the EU FP6 and FP7 (LbL Brane, 3M and Sight) for supporting the research. S.E.M. thanks the MAT2017-88752-R Retos project from the Ministerio de Economía, Industria y Competitividad, gobierno de España. M.C.H. acknowledges support from the Materials Research Science and Engineering Center (MRSEC) of Northwestern University (NSF DMR-1720139). N.A.K. acknowledges the Alexander von Humboldt Foundation for a visiting professorship to Hamburg University. S.L. is supported by Progetto FISIR-CNR "Tecnopolo di Nanotecnologia e Fotonica per la Medicina di Precisione"-CUP B83B17000010001. P.M. acknowledges support through ARC Grant CE170100026. A.L.R. was supported by a grant from the Germany/Hong Kong Joint Research Scheme sponsored by the Research Grants Council of Hong Kong and the Germany Academic Exchange Service of Germany (Reference No. G-CityU106/18). S.R. was supported by Fazit Stiftung. D.S. acknowledges an ERC Consolidator Grant No.

647969. A.G.S. acknowledges support of BOF-UGent (01IO3618, BAS094-18, BOF14/IOP/003) and FWO-Vlaanderen (G043219). W.J.P. received funding from the Deutsche Forschungsgemeinschaft (DFG PA 794/21-1). Z.Y. was supported by the National Natural Science Foundation of China (61871240).

DEDICATION

This article is dedicated to the memory of our beloved colleague and friend Prof. Dr. Helmuth Möhwald (19 January 1946–27 March 2018).

REFERENCES

- (1) Decher, G.; Hong, J. D.; Schmitt, J. Buildup of Ultrathin Multilayer Films by a Self-Assembly Process: III. Consecutively Alternating Adsorption of Anionic and Cationic Polyelectrolytes on Charged Surfaces. *Thin Solid Films* **1992**, *210*, 831–835.
- (2) Lvov, Y.; Decher, G.; Möhwald, H. Assembly, Structural Characterization, and Thermal-Behavior of Layer-by-Layer Deposited Ultrathin Films of Poly(vinyl sulfate) and Poly(allylamine). *Langmuir* **1993**, *9*, 481–486.
- (3) Schmitt, J.; Gruenewald, T.; Decher, G.; Pershan, P. S.; Kjaer, K.; Lösche, M. Internal Structure of Layer-by-Layer Adsorbed Polyelectrolyte Films: A Neutron and X-Ray Reflectivity Study. *Macromolecules* **1993**, *26*, 7058–7063.
- (4) Decher, G.; Lehr, B.; Lowack, K.; Lvov, Y.; Schmitt, J. New Nanocomposite Films for Biosensors: Layer-by-Layer Adsorbed Films of Polyelectrolytes, Proteins or DNA. *Biosens. Bioelectron.* **1994**, *9*, 677–684.
- (5) Lvov, Y.; Haas, H.; Decher, G.; Möhwald, H.; Mikhailov, A.; Mchedlishvili, B.; Morgunova, E.; Vainshtein, B. Successive Deposition of Alternate Layers of Polyelectrolytes and a Charged Virus. *Langmuir* **1994**, *10*, 4232–4236.
- (6) Sukhorukov, G. B.; Lvov, Y. M.; Möhwald, H.; Decher, G. Assembly of Polyelectrolyte Multilayer Films by Consecutively Alternating Adsorption of Polynucleotides and Polycations. *Thin Solid Films* **1996**, *284–285*, 220–223.
- (7) Decher, G. Fuzzy Nanoassemblies: Toward Layered Polymeric Multicomposites. *Science* **1997**, *277*, 1232–1237.
- (8) Caruso, F.; Caruso, R. A.; Möhwald, H. Nanoengineering of Inorganic and Hybrid Hollow Spheres by Colloidal Templating. *Science* **1998**, *282*, 1111–1114.
- (9) Caruso, F.; Lichtenfeld, H.; Giersig, M.; Möhwald, H. Electrostatic Self-Assembly of Silica Nanoparticle-Polyelectrolyte Multilayers on Polystyrene Latex Particles. *J. Am. Chem. Soc.* **1998**, *120*, 8523–8524.
- (10) Zhang, R.; Shang, J.; Xin, J.; Xie, B.; Li, Y.; Möhwald, H. Self-Assemblies of Luminescent Rare Earth Compounds in Capsules and Multilayers. *Adv. Colloid Interface Sci.* **2014**, *207*, 361–375.
- (11) Kolesnikova, T. A.; Skirtach, A. G.; Möhwald, H. Red Blood Cells and Polyelectrolyte Multilayer Capsules: Natural Carriers versus Polymer-Based Drug Delivery Vehicles. *Expert Opin. Drug Delivery* **2013**, *10*, 47–58.
- (12) Shchukin, D. G.; Möhwald, H. Multilayer Polyelectrolyte Assembly in Feedback Active Coatings and Films. In *Multilayer Thin Films: Sequential Assembly of Nanocomposite Materials*, 2nd ed.; Decher, G., Schlenoff, J. B., Eds.; Wiley-VCH: Weinheim, Germany, 2012; Vol. 2, pp 1039–1050.
- (13) Dronov, R.; Kurth, D. G.; Möhwald, H.; Scheller, F. W.; Lisdat, F. A Self-Assembled Cytochrome *c*/Xanthine Oxidase Multilayer Arrangement on Gold. *Electrochim. Acta* **2007**, *53*, 1107–1113.
- (14) Tang, F.; Cui, Q.; Wu, F.; Li, L.; Möhwald, H. Photoinduced Long-Range Charge Transfer in Polyelectrolyte Multilayers. *J. Photopolym. Sci. Technol.* **2008**, *21*, 729–731.
- (15) Li, Z.; Xu, F.; Li, Q.; Liu, S.; Wang, H.; Möhwald, H.; Cui, X. Synthesis of Multifunctional Bovine Serum Albumin Microcapsules by the Sonochemical Method for Targeted Drug Delivery and Controlled Drug Release. *Colloids Surf., B* **2015**, *136*, 470–478.
- (16) Malcher, M.; Volodkin, D.; Heurtault, B.; André, P.; Schaaf, P.; Möhwald, H.; Voegel, J. C.; Sokolowski, A.; Ball, V.; Boulmedais, F.; Frisch, B. Embedded Silver Ions-Containing Liposomes in Polyelectrolyte Multilayers: Cargos Films for Antibacterial Agents. *Langmuir* **2008**, *24*, 10209–10215.
- (17) Sezer, M.; Feng, J. J.; Khoa Ly, H.; Shen, Y.; akanishi, T.; Kuhlmann, U.; Hildebrandt, P.; Möhwald, H.; Weidinger, I. M. Multi-Layer Electron Transfer Across Nanostructured Ag-SAM-Au-SAM Junctions Probed by Surface Enhanced Raman Spectroscopy. *Phys. Chem. Chem. Phys.* **2010**, *12*, 9822–9829.
- (18) Shchukin, D. G.; Zheludkevich, M.; Yasakau, K.; Lamaka, S.; Ferreira, M. G. S.; Möhwald, H. Layer-by-Layer Assembled Nanocontainers for Self-Healing Corrosion Protection. *Adv. Mater.* **2006**, *18*, 1672–1678.
- (19) Tong, W. J.; Gao, C. Y.; Möhwald, H. Single Polyelectrolyte Microcapsules Fabricated by Glutaraldehyde-Mediated Covalent Layer-by-Layer Assembly. *Macromol. Rapid Commun.* **2006**, *27*, 2078–2083.
- (20) Volodkin, D.; Skirtach, A.; Möhwald, H. Bioapplications of Light-Sensitive Polymer Films and Capsules Assembled Using the Layer-by-Layer Technique. *Polym. Int.* **2012**, *61*, 673–679.
- (21) Ibarz, G.; Dähne, L.; Donath, E.; Möhwald, H. Smart Micro- and Nanocontainers for Storage, Transport, and Release. *Adv. Mater.* **2001**, *13*, 1324–1327.
- (22) Skirtach, A. G.; Munoz Javier, A.; Kreft, O.; Köhler, K.; Piera Alberola, A.; Möhwald, H.; Parak, W. J.; Sukhorukov, G. B. Laser-Induced Release of Encapsulated Materials Inside Living Cells. *Angew. Chem., Int. Ed.* **2006**, *45*, 4612–4617.
- (23) Skirtach, A. G.; Dejumat, C.; Braun, D.; Susa, A. S.; Rogach, A. L.; Parak, W. J.; Möhwald, H.; Sukhorukov, G. B. The Role of Metal Nanoparticles in Remote Release of Encapsulated Materials. *Nano Lett.* **2005**, *5*, 1371–1377.
- (24) Beissenhirtz, M. K.; Scheller, F. W.; Stocklein, W. F. M.; Kurth, D. G.; Möhwald, H.; Lisdat, F. Electroactive Cytochrome *c* Multilayers within a Polyelectrolyte Assembly. *Angew. Chem., Int. Ed.* **2004**, *43*, 4357–4360.
- (25) Sukhorukov, G.; Dähne, L.; Hartmann, J.; Donath, E.; Möhwald, H. Controlled Precipitation of Dyes into Hollow Polyelectrolyte Capsules Based on Colloids and Biocolloids. *Adv. Mater.* **2000**, *12*, 112–115.
- (26) Ibarz, G.; Dähne, L.; Donath, E.; Möhwald, H. Controlled Permeability of Polyelectrolyte Capsules via Defined Annealing. *Chem. Mater.* **2002**, *14*, 4059–4062.
- (27) Dähne, L.; Leporatti, S.; Donath, E.; Möhwald, H. Fabrication of Micro Reaction Cages with Tailored Properties. *J. Am. Chem. Soc.* **2001**, *123*, 5431–5436.
- (28) Dai, Z.; Voigt, A.; Leporatti, S.; Donath, E.; Dähne, L.; Möhwald, H. Layer-by-Layer Self-Assembly of Polyelectrolyte and Low Molecular Weight Species into Capsules. *Adv. Mater.* **2001**, *13*, 1339–1342.
- (29) Dai, Z. F.; Dähne, L.; Donath, E.; Möhwald, H. Mimicking Photosynthetic Two-Step Energy Transfer in Cyanine Triads Assembled into Capsules. *Langmuir* **2002**, *18*, 4553–4555.
- (30) Dai, Z.; Dähne, L.; Donath, E.; Möhwald, H. Downhill Energy Transfer via Ordered Multichromophores in Light-Harvesting Capsules. *J. Phys. Chem. B* **2002**, *106*, 11501–11508.
- (31) Dai, Z. F.; Möhwald, H.; Tiersch, B.; Dähne, L. Nano-engineering of Polymeric Capsules with a Shell-in-Shell Structure. *Langmuir* **2002**, *18*, 9533–9538.
- (32) Dai, Z.; Dähne, L.; Möhwald, H.; Tiersch, B. Novel Capsules with High Stability and Controlled Permeability by Hierarchic Templating. *Angew. Chem., Int. Ed.* **2002**, *41*, 4019–4022.
- (33) Donath, E.; Sukhorukov, G. B.; Caruso, F.; Davis, S. A.; Möhwald, H. Novel Hollow Polymer Shells by Colloid-Templated Assembly of Polyelectrolytes. *Angew. Chem., Int. Ed.* **1998**, *37*, 2201–2205.

- (34) Möbius, D.; Möhwald, H. Structural Characterization of Monolayers at the Air-Water Interface. *Adv. Mater.* **1991**, *3*, 19–24.
- (35) Kotov, N. A.; Dekany, I.; Fendler, J. H. Ultrathin Graphite Oxide-Polyelectrolyte Composites Prepared by Self-Assembly: Transition Between Conductive and Non-Conductive States. *Adv. Mater.* **1996**, *8*, 637–641.
- (36) Tang, Z.; Kotov, N. A.; Magonov, S.; Ozturk, B. Nanostructured Artificial Nacre. *Nat. Mater.* **2003**, *2*, 413–418.
- (37) Kotov, N. A.; Putyera, K.; Fendler, J. H.; Tombácz, E.; Dékány, I. Cadmium Sulfide Particles in Organomontmorillonite Complexes. *Colloids Surf., A* **1993**, *71*, 317–326.
- (38) Kotov, N. A.; Meldrum, F. C.; Fendler, J. H. Monoparticulate Layers of Titanium Dioxide Nanocrystallites with Controllable Interparticle Distances. *J. Phys. Chem.* **1994**, *98*, 8827–8830.
- (39) Kotov, N. A.; Meldrum, F. C.; Wu, C.; Fendler, J. H. Monoparticulate Layer and Langmuir-Blodgett-Type Multiparticulate Layers of Size-Quantized Cadmium Sulfide Clusters: A Colloid-Chemical Approach to Superlattice Construction. *J. Phys. Chem.* **1994**, *98*, 2735–2738.
- (40) Motte, L.; Billoudet, F.; Lacaze, E.; Pileni, M. P. Self-Organization of Size-Selected, Nanoparticles into Three-Dimensional Superlattices. *Adv. Mater.* **1996**, *8*, 1018–1020.
- (41) Yonezawa, T.; Matsune, H.; Kunitake, T. Layered Nanocomposite of Close-Packed Gold Nanoparticles and TiO₂ Gel Layers. *Chem. Mater.* **1999**, *11*, 33–35.
- (42) Berndt, P.; Kurihara, K.; Kunitake, T. Adsorption of Poly(styrenesulfonate) onto an Ammonium Monolayer on Mica: A Surface Forces Study. *Langmuir* **1992**, *8*, 2486–2490.
- (43) Kilper, S.; Facey, S. J.; Burghard, Z.; Hauer, B.; Rothenstein, D.; Bill, J. Macroscopic Properties of Biomimetic Ceramics Are Governed by the Molecular Recognition at the Bioorganic-Inorganic Interface. *Adv. Funct. Mater.* **2018**, *28*, 1705842.
- (44) Cui, J.; Richardson, J. J.; Björnalm, M.; Faria, M.; Caruso, F. Nanoengineered Templated Polymer Particles: Navigating the Biological Realm. *Acc. Chem. Res.* **2016**, *49*, 1139–1148.
- (45) Richardson, J. J.; Björnalm, M.; Caruso, F. Technology-Driven Layer-by-Layer Assembly of Nanofilms. *Science* **2015**, *348*, No. aaa2491.
- (46) Peyratout, C. S.; Dähne, L. Tailor-Made Polyelectrolyte Microcapsules: From Multilayers to Smart Containers. *Angew. Chem., Int. Ed.* **2004**, *43*, 3762–3783.
- (47) Dähne, L.; Peyratout, C. Nanoengineered Capsules with Specific Layer Structures. *Dekker Encyclopedia of Nanoscience and Nanotechnology*, 2nd ed. six volume set (print version); CRC Press: Boca Raton, FL, 2004; pp 2355–2367.
- (48) Möhwald, H.; Lichtenfeld, H.; Moya, S.; Voigt, A.; Sukhorukov, G.; Leporatti, S.; Dähne, L.; Antipov, A.; Gao, C. Y.; Donath, E. From Polymeric Films to Nanocapsules. In *Adsorption and Aggregation of Surfactants in Solution*; Mittal, K. L., Shah, D. O., Eds.; Marcel Dekker: New York, 2002; Vol. 132, pp 485–490.
- (49) Lisdat, F. Trends in the Layer-by-Layer Assembly of Redox Proteins and Enzymes in Bioelectrochemistry. *Curr. Opin. Electrochem.* **2017**, *5*, 165–172.
- (50) De Geest, B. G.; Sukhorukov, G. B.; Möhwald, H. The Pros and Cons of Polyelectrolyte Capsules in Drug Delivery. *Expert Opin. Drug Delivery* **2009**, *6*, 613–624.
- (51) Delcea, M.; Möhwald, H.; Skirtach, A. G. Stimuli-Responsive LbL Capsules and Nanoshells for Drug Delivery. *Adv. Drug Delivery Rev.* **2011**, *63*, 730–747.
- (52) Zhuk, A.; Sukhishvili, S. A. Stimuli-Responsive Layer-by-Layer Nanocomposites. *Soft Matter* **2013**, *9*, 5149–5154.
- (53) Hua, F.; Cui, T.; Lvov, Y. M. Ultrathin Cantilevers Based on Polymer-Ceramic Nanocomposite Assembled through Layer-by-Layer Adsorption. *Nano Lett.* **2004**, *4*, 823–825.
- (54) Kang, S.; Wang, L.; Zhang, J.; Du, J.; Li, M.; Chen, Q. Electroreductive Coupling Layer-by-Layer Assembly. *ACS Appl. Mater. Interfaces* **2017**, *9*, 32179–32183.
- (55) Ma, Y.; Zhang, Y.; Wu, B.; Sun, W.; Li, Z.; Sun, J. Polyelectrolyte Multilayer Films for Building Energetic Walking Devices. *Angew. Chem.* **2011**, *123*, 6378–6381.
- (56) Podsiadlo, P.; Kaushik, A. K.; Shim, B. S.; Agarwal, A.; Tang, Z.; Waas, A. M.; Arruda, E. M.; Kotov, N. A. Can Nature's Design be Improved Upon? High Strength, Transparent Nacre-Like Nanocomposites with Double Network of Sacrificial Cross Links. *J. Phys. Chem. B* **2008**, *112*, 14359–14363.
- (57) Schlenoff, J. B.; Dubas, S. T.; Farhat, T. Sprayed Polyelectrolyte Multilayers. *Langmuir* **2000**, *16*, 9968–9969.
- (58) Krogman, K. C.; Zacharia, N. S.; Schroeder, S.; Hammond, P. T. Automated Process for Improved Uniformity and Versatility of Layer-by-Layer Deposition. *Langmuir* **2007**, *23*, 3137–3141.
- (59) Krogman, K. C.; Lowery, J. L.; Zacharia, N. S.; Rutledge, G. C.; Hammond, P. T. Spraying Asymmetry into Functional Membranes Layer-by-Layer. *Nat. Mater.* **2009**, *8*, 512–518.
- (60) Lefort, M.; Popa, G.; Seyrek, E.; Szamocki, R.; Felix, O.; Hemmerlé, J.; Vidal, L.; Voegel, J. C.; Boulmedais, F.; Decher, G.; Schaaf, P. Spray-on Organic/Inorganic Films: a General Method for the Formation of Functional Nano- to Microscale Coatings. *Angew. Chem., Int. Ed.* **2010**, *49*, 10110–10113.
- (61) Richardson, J. J.; Ejima, H.; Lorcher, S. L.; Liang, K.; Senn, P.; Cui, J.; Caruso, F. Preparation of Nano- and Microcapsules by Electrophoretic Polymer Assembly. *Angew. Chem., Int. Ed.* **2013**, *52*, 6455–6458.
- (62) Ejima, H.; Richardson, J. J.; Liang, K.; Best, J. P.; Van Koeveerden, M. P.; Such, G. K.; Cui, J.; Caruso, F. One-Step Assembly of Coordination Complexes for Versatile Film and Particle Engineering. *Science* **2013**, *341*, 154–157.
- (63) Dierendonck, M.; De Koker, S.; Cuvelier, C.; Grooten, J.; Vervae, C.; Remon, J. P.; De Geest, B. G. Facile Two-Step Synthesis of Porous Antigen-Loaded Degradable Polyelectrolyte Microspheres. *Angew. Chem., Int. Ed.* **2010**, *49*, 8620–8624.
- (64) Porcel, C. H.; Izquierdo, A.; Ball, V.; Decher, G.; Voegel, J. C.; Schaaf, P. Ultrathin Coatings and (Poly(glutamic acid)/Polyallylamine) Films Deposited by Continuous and Simultaneous Spraying. *Langmuir* **2005**, *21*, 800–802.
- (65) Muzzio, N. E.; Pasquale, M. A.; Gregurec, D.; Diamanti, E.; Kosutic, M.; Azzaroni, O.; Moya, S. E. Polyelectrolytes Multilayers To Modulate Cell Adhesion: A Study of the Influence of Film Composition and Polyelectrolyte Interdigitation on the Adhesion of the A549 Cell Line. *Macromol. Biosci.* **2016**, *16*, 482–495.
- (66) Liao, W. C.; Sohn, Y. S.; Riutin, M.; Ceconello, A.; Parak, W. J.; Nechushtai, R.; Willner, I. The Application of Stimuli-Responsive VEGF- and ATP-Aptamer-Based Microcapsules for the Controlled Release of an Anticancer Drug, and the Selective Targeted Cytotoxicity toward Cancer Cells. *Adv. Funct. Mater.* **2016**, *26*, 4262–4273.
- (67) Liao, W.; Lu, C.; Hartmann, R.; Wang, F.; Sohn, Y. S.; Parak, W. J.; Willner, I. Adenosine Triphosphate-Triggered Release of Macromolecular and Nanoparticle Loads from Aptamer/DNA-Cross-Linked Microcapsules. *ACS Nano* **2015**, *9*, 9078–9086.
- (68) Seyrek, E.; Decher, G. Layer-by-Layer Assembly of Multifunctional Hybrid Materials and Nanoscale Devices. In *Polymer Science: A Comprehensive Reference*; Matyjaszewski, K., Müller, M., Eds.; Elsevier: Amsterdam, 2012; Vol. 7, pp 159–185.
- (69) Kotov, N. A.; Magonov, S.; Tropsha, E. Layer-by-Layer Self-Assembly of Aluminosilicate-Polyelectrolyte Composites: Mechanism of Deposition, Crack Resistance, and Perspectives for Novel Membrane Materials. *Chem. Mater.* **1998**, *10*, 886–895.
- (70) Kotov, N. A. Ordered Layered Assemblies of Nanoparticles. *MRS Bull.* **2001**, *26*, 992–997.
- (71) Yashchenok, A. M.; Gorin, D. A.; Badylevich, M.; Serdobintsev, A. A.; Bedard, M.; Fedorenko, Y. G.; Khomutov, G. B.; Grigoriev, D. O.; Möhwald, H. Impact of Magnetite Nanoparticle Incorporation on Optical and Electrical Properties of Nanocomposite LbL Assemblies. *Phys. Chem. Chem. Phys.* **2010**, *12*, 10469–10475.
- (72) Malikova, N.; Pastoriza-Santos, I.; Schierhorn, M.; Kotov, N. A.; Liz-Marzán, L. M. Layer-by-Layer Assembled Mixed Spherical and

Planar Gold Nanoparticles: Control of Interparticle Interactions. *Langmuir* **2002**, *18*, 3694–3697.

(73) Salgueirino-Maceira, V.; Caruso, F.; Liz-Marzan, L. M. Coated Colloids with Tailored Optical Properties. *J. Phys. Chem. B* **2003**, *107*, 10990–10994.

(74) Schneider, G.; Decher, G.; Nerambourg, N.; Praho, R.; Werts, M. H.; Blanchard-Desce, M. Distance-Dependent Fluorescence Quenching on Gold Nanoparticles Ensheathed with Layer-by-Layer Assembled Polyelectrolytes. *Nano Lett.* **2006**, *6*, 530–536.

(75) Dykman, L.; Khlebtsov, N. Gold Nanoparticles in Biomedical Applications: Recent Advances and Perspectives. *Chem. Soc. Rev.* **2012**, *41*, 2256–2282.

(76) Del Pino, P.; Pelaz, B.; Zhang, Q.; Maffre, P.; Nienhaus, G. U.; Parak, W. J. Protein Corona Formation around Nanoparticles—From the Past to the Future. *Mater. Horiz.* **2014**, *1*, 301–313.

(77) Ariga, K.; Hill, J. P.; Ji, Q. Layer-by-Layer Assembly as a Versatile Bottom-Up Nanofabrication Technique for Exploratory Research and Realistic Application. *Phys. Chem. Chem. Phys.* **2007**, *9*, 2319–2340.

(78) Ung, T.; Liz-Marzán, L. M.; Mulvaney, P. Optical Properties of Thin Films of Au@SiO₂ Particles. *J. Phys. Chem. B* **2001**, *105*, 3441–3452.

(79) Vial, S.; Pastoriza-Santos, I.; Perez-Juste, J.; Liz-Marzan, L. M. Plasmon Coupling in Layer-by-Layer Assembled Gold Nanorod Films. *Langmuir* **2007**, *23*, 4606–4611.

(80) Abalde-Cela, S.; Ho, S.; Rodriguez-Gonzalez, B.; Correa-Duarte, M. A.; Alvarez-Puebla, R. A.; Liz-Marzan, L. M.; Kotov, N. A. Loading of Exponentially Grown LbL Films with Silver Nanoparticles and Their Application to Generalized SERS Detection. *Angew. Chem., Int. Ed.* **2009**, *48*, 5326–5329.

(81) Stankovich, S.; Dikin, D. A.; Dommett, G. H. B.; Kohlhaas, K. M.; Zimney, E. J.; Stach, E. A.; Piner, R. D.; Nguyen, S. T.; Ruoff, R. S. Graphene-Based Composite Materials. *Nature* **2006**, *442*, 282–286.

(82) Wan, S.; Li, Y.; Mu, J.; Aliev, A. E.; Fang, S.; Kotov, N. A.; Jiang, L.; Cheng, Q.; Baughman, R. H. Sequentially Bridged Graphene Sheets with High Strength, Toughness, and Electrical Conductivity. *Proc. Natl. Acad. Sci. U. S. A.* **2018**, *115*, 5359–5364.

(83) Mao, L. B.; Gao, H. L.; Yao, H. B.; Liu, L.; Cölfen, H.; Liu, G.; Chen, S. M.; Li, S. K.; Yan, Y. X.; Liu, Y. Y.; Yu, S. H. Synthetic Nacre by Predesigned Matrix-Directed Mineralization. *Science* **2016**, *354*, 107–110.

(84) Jiang, C.; Markutsya, S.; Pikus, Y.; Tsukruk, V. V. Freely Suspended Nanocomposite Membranes as Highly Sensitive Sensors. *Nat. Mater.* **2004**, *3*, 721–728.

(85) Li, Y.; Wang, X.; Sun, J. Layer-by-Layer Assembly for Rapid Fabrication of Thick Polymeric Films. *Chem. Soc. Rev.* **2012**, *41*, 5998–6009.

(86) Mannarino, M. M.; Liu, D. S.; Hammond, P. T.; Rutledge, G. C. Mechanical and Transport Properties of Layer-by-Layer Electrospun Composite Proton Exchange Membranes for Fuel Cell Applications. *ACS Appl. Mater. Interfaces* **2013**, *5*, 8155–8164.

(87) Jiang, C.; Tsukruk, V. V. Freestanding Nanostructures via Layer-by-Layer Assembly. *Adv. Mater.* **2006**, *18*, 829–840.

(88) Zhang, X.; Chen, H.; Zhang, H. Layer-by-Layer Assembly: From Conventional to Unconventional Methods. *Chem. Commun.* **2007**, *0*, 1395–1405.

(89) Weng, G. M.; Li, J.; Alhabebe, M.; Karpovich, C.; Wang, H.; Lipton, J.; Maleski, K.; Kong, J.; Shaulsky, E.; Elimelech, M.; Gogotsi, Y.; Taylor, A. D. Layer-by-Layer Assembly of Cross-Functional Semi-Transparent MXene-Carbon Nanotubes Composite Films for Next-Generation Electromagnetic Interference Shielding. *Adv. Funct. Mater.* **2018**, *28*, 1803360.

(90) Feifel, S. C.; Lisdat, F. Silica Nanoparticles for the Layer-by-Layer Assembly of Fully Electro-Active Cytochrome c Multilayers. *J. Nanobiotechnol.* **2011**, *9*, 59.

(91) Irigoyen, J.; Laakso, T.; Politakos, N.; Dahne, L.; Pihlajamäki, A.; Mänttari, M.; Moya, S. E. Design and Performance Evaluation of Hybrid Nanofiltration Membranes Based on Multiwalled Carbon

Nanotubes and Polyelectrolyte Multilayers for Larger Ion Rejection and Separation. *Macromol. Chem. Phys.* **2016**, *217*, 804–811.

(92) Kaushik, A. K.; Podsiadlo, P.; Qin, M.; Shaw, C. M.; Waas, A. M.; Kotov, N. A.; Arruda, E. M. The Role of Nanoparticle Layer Separation in the Finite Deformation Response of Layered Polyurethane-Clay Nanocomposites. *Macromolecules* **2009**, *42*, 6588–6595.

(93) Shahzad, F.; Alhabebe, M.; Hatter, C. B.; Anasori, B.; Hong, S. M.; Koo, C. M.; Gogotsi, Y. Electromagnetic Interference Shielding with 2D Transition Metal Carbides (MXenes). *Science* **2016**, *353*, 1137–1140.

(94) Zhou, Z.; Panatdasirisuk, W.; Mathis, T. S.; Anasori, B.; Lu, C.; Zhang, X.; Liao, Z.; Gogotsi, Y.; Yang, S. Layer-by-Layer Assembly of MXene and Carbon Nanotubes on Electrospun Polymer Films for Flexible Energy Storage. *Nanoscale* **2018**, *10*, 6005–6013.

(95) Hoda, N.; Larson, R. G. Explicit- and Implicit-Solvent Molecular Dynamics Simulations of Complex Formation between Polycations and Polyanions. *Macromolecules* **2009**, *42*, 8851–8863.

(96) Patel, P. A.; Jeon, J.; Mather, P. T.; Dobrynin, A. V. Molecular Dynamics Simulations of Layer-by-Layer Assembly of Polyelectrolytes at Charged Surfaces: Effects of Chain Degree of Polymerization and Fraction of Charged Monomers. *Langmuir* **2005**, *21*, 6113–6122.

(97) Lacevic, N. M.; Joshi, S. P. Energy Dissipation Mechanism in Nanocomposites Studied via Molecular Dynamics Simulation. In *Challenges in Mechanics of Time-Dependent Materials and Processes in Conventional and Multifunctional Materials*. In *Conference Proceedings of the Society for Experimental Mechanics Series*; Antoun, B., Qi, H., Hall, R., Randon, G., Lu, H., Lu, C., Eds.; Springer: New York, 2013; Vol. 2, pp 23–27.

(98) Blell, R.; Lin, X.; Lindström, T.; Ankerfors, M.; Pauly, M.; Felix, O.; Decher, G. Generating In-Plane Orientational Order in Multilayer Films Prepared by Spray-Assisted Layer-by-Layer Assembly. *ACS Nano* **2017**, *11*, 84–94.

(99) Sekar, S.; Lemaire, V.; Hu, H.; Decher, G.; Pauly, M. Anisotropic Optical and Conductive Properties of Oriented 1D-Nanoparticle Thin Films Made by Spray-Assisted Self-Assembly. *Faraday Discuss.* **2016**, *191*, 373–389.

(100) Hu, H.; Pauly, M.; Felix, O.; Decher, G. Spray-Assisted Alignment of Layer-by-Layer Assembled Silver Nanowires: A General Approach for the Preparation of Highly Anisotropic Nano-Composite Films. *Nanoscale* **2017**, *9*, 1307–1314.

(101) Shchukin, D.; Möhwald, H. A Coat of Many Functions. *Science* **2013**, *341*, 1458–1459.

(102) Andreeva, D. V.; Fix, D.; Möhwald, H.; Shchukin, D. G. Buffering Polyelectrolyte Multilayers for Active Corrosion Protection. *J. Mater. Chem.* **2008**, *18*, 1738–1740.

(103) Zheludkevich, M. L.; Shchukin, D. G.; Yasakau, K. A.; Möhwald, H.; Ferreira, M. G. S. Anticorrosion Coatings with Self-Healing Effect Based on Nanocontainers Impregnated with Corrosion Inhibitor. *Chem. Mater.* **2007**, *19*, 402–411.

(104) Andreeva, D. V.; Skorb, E. V.; Shchukin, D. G. Layer-by-Layer Polyelectrolyte/Inhibitor Nanostructures for Metal Corrosion Protection. *ACS Appl. Mater. Interfaces* **2010**, *2*, 1954–1962.

(105) Shchukin, D. G.; Lamaka, S. V.; Yasakau, K. A.; Zheludkevich, M. L.; Ferreira, M. G. S.; Möhwald, H. Active Anticorrosion Coatings with Halloysite Nanocontainers. *J. Phys. Chem. C* **2008**, *112*, 958–964.

(106) Li, G. L.; Zheng, Z.; Möhwald, H.; Shchukin, D. G. Silica/Polymer Double-Walled Hybrid Nanotubes: Synthesis and Application as Stimuli-Responsive Nanocontainers in Self-Healing Coatings. *ACS Nano* **2013**, *7*, 2470–2478.

(107) Shchukin, D. G.; Shchukina, E. Capsules with External Navigation and Triggered Release. *Curr. Opin. Pharmacol.* **2014**, *18*, 42–46.

(108) Pomerantseva, E.; Gogotsi, Y. Two-Dimensional Heterostructures for Energy Storage. *Nat. Energy* **2017**, *2*, 17089.

(109) Fendler, J. H. Colloid Chemical Approach to the Construction of High Energy Density Rechargeable, Lithium-Ion Batteries. *J. Dispersion Sci. Technol.* **1999**, *20*, 13–25.

- (110) Xiao, F. X.; Pagliaro, M.; Xu, Y. J.; Liu, B. Layer-by-Layer Assembly of Versatile Nanoarchitectures with Diverse Dimensionality: A New Perspective for Rational Construction of Multilayer Assemblies. *Chem. Soc. Rev.* **2016**, *45*, 3088–3121.
- (111) Liu, L.; Choi, B. G.; Tung, S. O.; Lyu, J.; Li, T.; Zhao, T.; Kotov, N. A. Materials Engineering of High-Performance Anodes as Layered Composites with Self-Assembled Conductive Networks. *J. Phys. Chem. C* **2018**, *122*, 14014–14028.
- (112) Tung, S. O.; Ho, S.; Yang, M.; Zhang, R.; Kotov, N. A. A Dendrite-Suppressing Composite Ion Conductor from Aramid Nanofibres. *Nat. Commun.* **2015**, *6*, 6152.
- (113) Wang, M.; Emre, A.; Tung, S.; Gerber, A.; Wang, D.; Huang, Y.; Cecen, V.; Kotov, N. A. Biomimetic Solid-State Zn^{2+} Electrolyte for Corrugated Structural Batteries. *ACS Nano* **2019**, *13*, 1107–1115.
- (114) Gao, M.; Lesser, C.; Kirstein, S.; Möhwald, H.; Rogach, A. L.; Weller, H. Electroluminescence of Different Colors from Polycation/CdTe Nanocrystal Self-Assembled Films. *J. Appl. Phys.* **2000**, *87*, 2297–2302.
- (115) Franzl, T.; Koktysh, D. S.; Klar, T. A.; Rogach, A. L.; Feldmann, J.; Gaponik, N. Fast Energy Transfer in Layer-by-Layer Assembled CdTe Nanocrystal Bilayers. *Appl. Phys. Lett.* **2004**, *84*, 2904–2906.
- (116) Franzl, T.; Klar, T. A.; Schietinger, S.; Rogach, A. L.; Feldmann, J. Exciton Recycling in Graded Gap Nanocrystal Structures. *Nano Lett.* **2004**, *4*, 1599–1603.
- (117) Klar, T. A.; Franzl, T.; Rogach, A. L.; Feldmann, J. Super-Efficient Exciton Funneling in Layer-by-Layer Semiconductor Nanocrystal Structures. *Adv. Mater.* **2005**, *17*, 769–773.
- (118) Susa, A. S.; Caruso, F.; Rogach, A. L.; Sukhorukov, G. B.; Kornowski, A.; Möhwald, H.; Giersig, M.; Eychmüller, A.; Weller, H. Formation of Luminescent Spherical Core-Shell Particles by the Consecutive Adsorption of Polyelectrolyte and CdTe(S) Nanocrystals on Latex Colloids. *Colloids Surf., A* **2000**, *163*, 39–44.
- (119) Gaponik, N.; Radtchenko, I. L.; Gerstenberger, M. R.; Fedutik, Y. A.; Sukhorukov, G. B.; Rogach, A. L. Labeling of Biocompatible Polymer Microcapsules with Near-Infrared Emitting Nanocrystals. *Nano Lett.* **2003**, *3*, 369–372.
- (120) Gaponik, N.; Radtchenko, I. L.; Sukhorukov, G. B.; Rogach, A. L. Luminescent Polymer Microcapsules Addressable by a Magnetic Field. *Langmuir* **2004**, *20*, 1449–1452.
- (121) Kotov, N. A.; Dekany, I.; Fendler, J. H. Layer-by-Layer Self-Assembly of Polyelectrolyte-Semiconductor Nanoparticle Composite Films. *J. Phys. Chem.* **1995**, *99*, 13065–13069.
- (122) Rogach, A. L.; Koktysh, D. S.; Harrison, M.; Kotov, N. A. Layer-by-Layer Assembled Films of HgTe Nanocrystals with Strong Infrared Emission. *Chem. Mater.* **2000**, *12*, 1526–1528.
- (123) Mamedov, A. A.; Belov, A.; Giersig, M.; Mamedova, N. N.; Kotov, N. A. Nanorainbows: Graded Semiconductor Films from Quantum Dots. *J. Am. Chem. Soc.* **2001**, *123*, 7738–7739.
- (124) Zhu, J.; Kang, J.; Kang, J.; Jariwala, D.; Wood, J. D.; Seo, J. W. T.; Chen, K. S.; Marks, T. J.; Hersam, M. C. Solution-Processed Dielectrics Based on Thickness-Sorted Two-Dimensional Hexagonal Boron Nitride Nanosheets. *Nano Lett.* **2015**, *15*, 7029–7036.
- (125) Feifel, S. C.; Kapp, A.; Lisdat, F. Protein Multilayer Architectures on Electrodes for Analyte Detection. In *Biosensors Based on Aptamers and Enzymes*; Gu, M. B., Kim, H. S., Eds.; Springer: Berlin, 2013; Vol. 140, pp 253–298.
- (126) Heath, G. R.; Li, M.; Rong, H.; Radu, V.; Frielingsdorf, S.; Lenz, O.; Butt, J. N.; Jeuken, L. J. C. Multilayered Lipid Membrane Stacks for Biocatalysis Using Membrane Enzymes. *Adv. Funct. Mater.* **2017**, *27*, 1606265.
- (127) Dronov, R.; Kurth, D. G.; Möhwald, H.; Scheller, F. W.; Lisdat, F. Communication in a Protein Stack: Electron Transfer between Cytochrome c and Bilirubin Oxidase within a Polyelectrolyte Multilayer. *Angew. Chem., Int. Ed.* **2008**, *47*, 3000–3003.
- (128) Grant, G. G. S.; Koktysh, D. S.; Yun, B.; Matts, R. L.; Kotov, N. A. Layer-by-Layer Assembly of Collagen Thin Films: Controlled Thickness and Biocompatibility. *Biomed. Microdevices* **2001**, *3*, 301–306.
- (129) Dronov, R.; Kurth, D. G.; Möhwald, H.; Spricigo, R.; Leimkuehler, S.; Wollenberger, U.; Rajagopalan, K. V.; Scheller, F. W.; Lisdat, F. Layer-by-Layer Arrangement by Protein-Protein Interaction of Sulfite Oxidase and Cytochrome c Catalyzing Oxidation of Sulfite. *J. Am. Chem. Soc.* **2008**, *130*, 1122–1123.
- (130) Feifel, S. C.; Kapp, A.; Ludwig, R.; Lisdat, F. Nano-biomolecular Multiprotein Clusters on Electrodes for the Formation of a Switchable Cascadic Reaction Scheme. *Angew. Chem., Int. Ed.* **2014**, *53*, 5676–5679.
- (131) Gheith, M. K.; Sinani, V. A.; Wicksted, J. P.; Matts, R. L.; Kotov, N. A. Single-Walled Carbon Nanotube Polyelectrolyte Multilayers and Freestanding Films as a Biocompatible Platform for Neuroprosthetic Implants. *Adv. Mater.* **2005**, *17*, 2663–2670.
- (132) Pappas, T. C.; Wickramanyake, W. M. S.; Jan, E.; Motamedi, M.; Brodwick, M.; Kotov, N. A. Nanoscale Engineering of a Cellular Interface with Semiconductor Nanoparticle Films for Photoelectric Stimulation of Neurons. *Nano Lett.* **2007**, *7*, 513–519.
- (133) Rabe, K. S.; Müller, J.; Skoupi, M.; Niemeyer, C. M. Cascades in Compartments: En Route to Machine-Assisted Biotechnology. *Angew. Chem., Int. Ed.* **2017**, *56*, 13574–13589.
- (134) Kreft, O.; Skirtach, A. G.; Sukhorukov, G. B.; Möhwald, H. Remote Control of Bioreactions in Multicompartment Capsules. *Adv. Mater.* **2007**, *19*, 3142–3145.
- (135) Bäumler, H.; Georgieva, R. Coupled Enzyme Reactions in Multicompartment Microparticles. *Biomacromolecules* **2010**, *11*, 1480–1487.
- (136) Stoll, C.; Kudera, S.; Parak, W. J.; Lisdat, F. Quantum Dots on Gold: Electrodes For Photoswitchable Cytochrome c Electrochemistry. *Small* **2006**, *2*, 741–743.
- (137) Katz, E.; Zayats, M.; Willner, I.; Lisdat, F. Controlling the Direction of Photocurrents by Means of CdS Nanoparticles and Cytochrome c-Mediated Biocatalytic Cascades. *Chem. Commun.* **2006**, *0*, 1395–1397.
- (138) Rajendran, V.; Lehnig, M.; Niemeyer, C. M. Photocatalytic Activity of Colloidal CdS Nanoparticles with Different Capping Ligands. *J. Mater. Chem.* **2009**, *19*, 6348–6353.
- (139) Ipe, B. I.; Niemeyer, C. M. Nanohybrids Composed of Quantum Dots and Cytochrome P450 as Photocatalysts. *Angew. Chem., Int. Ed.* **2006**, *45*, 504–507.
- (140) Yue, Z.; Lisdat, F.; Parak, W. J.; Hickey, S. G.; Tu, L. P.; Sabir, N.; Dorfs, D.; Bigall, N. C. Quantum-Dot-Based Photoelectrochemical Sensors for Chemical and Biological Detection. *ACS Appl. Mater. Interfaces* **2013**, *5*, 2800–2814.
- (141) Friebe, V. M.; Frese, R. N. Photosynthetic Reaction Center-Based Biophotovoltaics. *Curr. Opin. Electrochem.* **2017**, *5*, 126–134.
- (142) Stieger, K. R.; Ciornii, D.; Kölsch, A.; Hejazi, M.; Lokstein, H.; Feifel, S. C.; Zouni, A.; Lisdat, F. Engineering of Supramolecular Photoactive Protein Architectures: the Defined Co-Assembly of Photosystem I and Cytochrome c Using a Nanoscaled DNA-Matrix. *Nanoscale* **2016**, *8*, 10695–10705.
- (143) Carregal-Romero, S.; Rinklin, P.; Schulze, S.; Schäfer, M.; Ott, A.; Hühn, D.; Yu, X.; Wolfrum, B.; Weitzel, K. M.; Parak, W. J. Ion Transport through Polyelectrolyte Multilayers. *Macromol. Rapid Commun.* **2013**, *34*, 1820–1826.
- (144) Wesp, V.; Hermann, M.; Schäfer, M.; Hühn, J.; Parak, W. J.; Weitzel, K. M. Bombardment Induced Ion Transport-Part IV: Ionic Conductivity of Ultra-Thin Polyelectrolyte Multilayer Films. *Phys. Chem. Chem. Phys.* **2016**, *18*, 4345–4351.
- (145) v. Klitzing, R. Internal Structure of Polyelectrolyte Multilayer Assemblies. *Phys. Chem. Chem. Phys.* **2006**, *8*, 5012–5033.
- (146) Zhao, S.; Zhang, J.; Li, Z.; Zhang, P.; Li, Y.; Liu, G.; Wang, Y.; Yue, Z. Photoelectrochemical Determination of Hydrogen Peroxide Using a Gold Electrode Modified with Fluorescent Gold Nanoclusters and Graphene Oxide. *Microchim. Acta* **2017**, *184*, 677–686.
- (147) Zhao, S.; Li, Z.; Li, Y.; Yu, J.; Liu, G.; Liu, R.; Yue, Z. BSA-AuNCs Based Enhanced Photoelectrochemical Biosensors and Its Potential Use in Multichannel Detections. *J. Photochem. Photobiol., A* **2017**, *342*, 15–24.

- (148) Khalid, W.; El Helou, M.; Murböck, T.; Yue, Z.; Montenegro, J. M.; Schubert, K.; Göbel, G.; Lisdat, F.; Witte, G.; Parak, W. J. Immobilization of Quantum Dots *via* Conjugated Self-Assembled Monolayers and Their Application as a Light-Controlled Sensor for the Detection of Hydrogen Peroxide. *ACS Nano* **2011**, *5*, 9870–9876.
- (149) Sabir, N.; Khan, N.; Völkner, J.; Widdascheck, F.; del Pino, P.; Witte, G.; Riedel, M.; Lisdat, F.; Konrad, M.; Parak, W. J. Photo-Electrochemical Bioanalysis of Guanosine Monophosphate Using Coupled Enzymatic Reactions at a CdS/ZnS Quantum Dot Electrode. *Small* **2015**, *11*, 5844–5850.
- (150) Tanne, J.; Schafer, D.; Khalid, W.; Parak, W. J.; Lisdat, F. Light-Controlled Bioelectrochemical Sensor Based on CdSe/ZnS Quantum Dots. *Anal. Chem.* **2011**, *83*, 7778–7785.
- (151) Meyer, R.; Sacca, B.; Niemeyer, C. M. Site-Directed, On-Surface Assembly of DNA Nanostructures. *Angew. Chem.* **2015**, *127*, 12207–12211.
- (152) Chen, X.; Venkatachalapathy, M.; Kamps, D.; Weigel, S.; Kumar, R.; Orlich, M.; Garrecht, R.; Hirtz, M.; Niemeyer, C. M.; Wu, Y. W.; Dehmelt, L. Molecular Activity Painting: Switch-Like, Light-Controlled Perturbations inside Living Cells. *Angew. Chem., Int. Ed.* **2017**, *56*, 5916–5920.
- (153) Salles, P.; Pinto, D.; Hantanasirisakul, K.; Maleski, K.; Shuck, C. E.; Gogotsi, Y. Electrochromic Effect in Titanium Carbide MXene Thin Films Produced by Dip-Coating. *Adv. Funct. Mater.* **2019**, *29*, 1809223.
- (154) Liu, S.; Kurth, D. G.; Möhwald, H.; Volkmer, D. A Thin-Film Electrochromic Device Based on a Polyoxometalate Cluster. *Adv. Mater.* **2002**, *14*, 225–228.
- (155) Liu, S.; Möhwald, H.; Volkmer, D.; Kurth, D. G. Polyoxometalate-Based Electro- and Photochromic Dual-Mode Devices. *Langmuir* **2006**, *22*, 1949–1951.
- (156) Sergeeva, Y. N.; Huang, T.; Felix, O.; Jung, L.; Tropel, P.; Viville, S.; Decher, G. What is Really Driving Cell-Surface Interactions? Layer-by-Layer Assembled Films May Help To Answer Questions Concerning Cell Attachment and Response to Biomaterials. *Biointerphases* **2016**, *11*, 019009.
- (157) Muzzio, N. E.; Pasquale, M. A.; Rios, X.; Azzaroni, O.; Llop, J.; Moya, S. E. Adsorption and Exchangeability of Fibronectin and Serum Albumin Protein Corona on Annealed Polyelectrolyte Multilayers and Their Consequences on Cell Adhesion. *Adv. Mater. Interfaces* **2019**, *6*, 1900008.
- (158) El-Khouri, R. J.; Szamocki, R.; Sergeeva, Y.; Felix, O.; Decher, G. Multifunctional Layer-by-Layer Architectures for Biological Applications. In *Functional Polymer Films*; Knoll, W., Advincula, R. C., Eds.; Wiley-VCH: Weinheim, Germany, 2011; Vol. 2, pp 11–58.
- (159) Jan, E.; Pereira, F. N.; Turner, D. L.; Kotov, N. A. In Situ Gene Transfection and Neuronal Programming on Electroconductive Nanocomposite to Reduce Inflammatory Response. *J. Mater. Chem.* **2011**, *21*, 1109–1114.
- (160) Crouzier, T.; Boudou, T.; Picart, C. Polysaccharide-Based Polyelectrolyte Multilayers. *Curr. Opin. Colloid Interface Sci.* **2010**, *15*, 417–426.
- (161) Romero, G.; Ochoteco, O.; Sanz, D. J.; Estrela-Lopis, I.; Donath, E.; Moya, S. E. Poly(lactide-co-glycolide) Nanoparticles, Layer-by-Layer Engineered for the Sustainable Delivery of AntiTNF- α . *Macromol. Biosci.* **2013**, *13*, 903–912.
- (162) Naves, A. F.; Motay, M.; Merindol, R.; Davi, C. P.; Felix, O.; Catalani, L. H.; Decher, G. Layer-by-Layer Assembled Growth Factor Reservoirs for Steering the Response of 3T3-cells. *Colloids Surf., B* **2016**, *139*, 79–86.
- (163) Muzzio, N. E.; Gregurec, D.; Diamanti, E.; Irigoyen, J.; Pasquale, M. A.; Azzaroni, O.; Moya, S. E. Thermal Annealing of Polyelectrolyte Multilayers: An Effective Approach for the Enhancement of Cell Adhesion. *Adv. Mater. Interfaces* **2017**, *4*, 1600126.
- (164) Skirtach, A. G.; Volodkin, D. V.; Möhwald, H. Bio-Interfaces-Interaction of PLL/HA Thick Films with Nanoparticles and Microcapsules. *ChemPhysChem* **2010**, *11*, 822–829.
- (165) Kohler, D.; Madaboosi, N.; Delcea, M.; Schmidt, S.; De Geest, B. G.; Volodkin, D. V.; Möhwald, H.; Skirtach, A. G. Patchiness of Embedded Particles and Film Stiffness Control through Concentration of Gold Nanoparticles. *Adv. Mater.* **2012**, *24*, 1095–1100.
- (166) Merindol, R.; Diabang, S.; Felix, O.; Roland, T.; Gauthier, C.; Decher, G. Bio-Inspired Multiproperty Materials: Strong, Self-Healing, and Transparent Artificial Wood Nanostructures. *ACS Nano* **2015**, *9*, 1127–1136.
- (167) Khademhosseini, A.; Suh, Y. K.; Yang, M. J.; Eng, G.; Yeh, J.; Levenberg, S.; Langer, R. Layer-by-Layer Deposition of Hyaluronic Acid and Poly-L-lysine for Patterned Cell Co-Cultures. *Biomaterials* **2004**, *25*, 3583–3592.
- (168) Fukuda, J.; Khademhosseini, A.; Yeh, J.; Eng, G.; Cheng, J.; Farokhzad, O. C.; Langer, R. Micropatterned Cell Co-Cultures Using Layer-by-Layer Deposition of Extracellular Matrix Components. *Biomaterials* **2006**, *27*, 1479–1486.
- (169) Tamada, Y.; Ikada, Y. Effect of Preadsorbed Proteins on Cell Adhesion to Polymer Surfaces. *J. Colloid Interface Sci.* **1993**, *155*, 334–339.
- (170) Yeom, B.; Sain, T.; Lacevic, N.; Bukharina, D.; Cha, S. H.; Waas, A. M.; Arruda, E. M.; Kotov, N. A. Abiotic Tooth Enamel. *Nature* **2017**, *543*, 95–98.
- (171) Vendamme, R.; Onoue, S. Y.; Nakao, A.; Kunitake, T. Robust Free-Standing Nanomembranes of Organic/Inorganic Interpenetrating Networks. *Nat. Mater.* **2006**, *5*, 494–501.
- (172) Ariga, K.; Yamauchi, Y.; Rydzek, G.; Ji, Q.; Yonamine, Y.; Wu, K. C. W.; Hill, J. P. Layer-by-Layer Nanoarchitectonics: Invention, Innovation, and Evolution. *Chem. Lett.* **2014**, *43*, 36–68.
- (173) Tang, Z.; Wang, Y.; Podsiadlo, P.; Kotov, N. A. Biomedical Applications of Layer-by-Layer Assembly: From Biomimetics to Tissue Engineering. *Adv. Mater.* **2006**, *18*, 3203–3224.
- (174) Sinani, V. A.; Koktysh, D. S.; Yun, B. G.; Matts, R. L.; Pappas, T. C.; Motamedi, M.; Thomas, S. N.; Kotov, N. A. Collagen Coating Promotes Biocompatibility of Semiconductor Nanoparticles in Stratified LbL Films. *Nano Lett.* **2003**, *3*, 1177–1182.
- (175) Zhang, Y.; Sun, J. Multilevel and Multicomponent Layer-by-Layer Assembly for the Fabrication of Nanofibrillar Films. *ACS Nano* **2015**, *9*, 7124–7132.
- (176) Volodkin, D.; von Klitzing, R.; Möhwald, H. Polyelectrolyte Multilayers: Towards Single Cell Studies. *Polymers* **2014**, *6*, 1502–1527.
- (177) Johnston, A. P. R.; Cortez, C.; Angelatos, A. S.; Caruso, F. Layer-by-Layer Engineered Capsules and Their Applications. *Curr. Opin. Colloid Interface Sci.* **2006**, *11*, 203–209.
- (178) Sukhorukov, G. B.; Donath, E.; Lichtenfeld, H.; Knippel, E.; Knippel, M.; Budde, A.; Möhwald, H. Layer-by-Layer Self Assembly of Polyelectrolytes on Colloidal Particles. *Colloids Surf., A* **1998**, *137*, 253–266.
- (179) Kotov, N. A.; Liu, Y. F.; Wang, S. P.; Cumming, C.; Eghtedari, M.; Vargas, G.; Motamedi, M.; Nichols, J.; Cortiella, J. Inverted Colloidal Crystals as Three-Dimensional Cell Scaffolds. *Langmuir* **2004**, *20*, 7887–7892.
- (180) Nichols, J. E.; Cortiella, J. Q.; Lee, J.; Niles, J. A.; Cuddihy, M.; Wang, S. P.; Bielitzki, J.; Cantu, A.; Mlcak, R.; Valdivia, E.; Yancy, R.; McClure, M. L.; Kotov, N. A. In Vitro Analog of Human Bone Marrow from 3D Scaffolds with Biomimetic Inverted Colloidal Crystal Geometry. *Biomaterials* **2009**, *30*, 1071–1079.
- (181) Kozai, T. D. Y.; Langhals, N. B.; Patel, P. R.; Deng, X.; Zhang, H.; Smith, K. L.; Lahann, J.; Kotov, N. A.; Kipke, D. R. Ultrasmall Implantable Composite Microelectrodes with Bioactive Surfaces for Chronic Neural Interfaces. *Nat. Mater.* **2012**, *11*, 1065–1073.
- (182) Kotov, N. A.; Winter, J. O.; Clements, I. P.; Jan, E.; Timko, B. P.; Campidelli, S.; Pathak, S.; Mazzatenta, A.; Lieber, C. M.; Prato, M.; Bellamkonda, R. V.; Silva, G. A.; Kam, N. W. S.; Patolsky, F.; Ballerini, L. Nanomaterials for Neural Interfaces. *Adv. Mater.* **2009**, *21*, 3970–4004.
- (183) Montjoy, D. G.; Bahng, J. H.; Eskafi, A.; Hou, H.; Kotov, N. A. Omnidispersible Hedgehog Particles with Multilayer Coatings for Multiplexed Biosensing. *J. Am. Chem. Soc.* **2018**, *140*, 7835–7845.
- (184) Lvov, Y. M.; Lu, Z.; Schenkman, J. B.; Zu, X.; Rusling, J. F. Direct Electrochemistry of Myoglobin and Cytochrome P450_{cam} in

Alternate Layer-by-Layer Films with DNA and Other Polyions. *J. Am. Chem. Soc.* **1998**, *120*, 4073–4080.

(185) Tong, W.; Song, X.; Gao, C. Layer-by-Layer Assembly of Microcapsules and Their Biomedical Applications. *Chem. Soc. Rev.* **2012**, *41*, 6103–6124.

(186) Yashchenok, A. M.; Bratashov, D. N.; Gorin, D. A.; Lomova, M. V.; Pavlov, A. M.; Sapelkin, A. V.; Shim, B. S.; Khomutov, G. B.; Kotov, N. A.; Sukhorukov, G. B.; Möhwald, H.; Skirtach, A. G. Carbon Nanotubes on Polymeric Microcapsules: Free-Standing Structures and Point-Wise Laser Openings. *Adv. Funct. Mater.* **2010**, *20*, 3136–3142.

(187) Shyu, T. C.; Damasceno, P. F.; Dodd, P. M.; Lamoureux, A.; Xu, L.; Shlian, M.; Shtein, M.; Glotzer, S. C.; Kotov, N. A. A Kirigami Approach to Engineering Elasticity in Nanocomposites Through Patterned Defects. *Nat. Mater.* **2015**, *14*, 785–789.

(188) Kim, Y.; Yeom, B.; Arteaga, O.; Yoo, S. J.; Lee, S. G.; Kim, J. G.; Kotov, N. A. Reconfigurable Chiroptical Nanocomposites with Chirality Transfer From the Macro- to the Nanoscale. *Nat. Mater.* **2016**, *15*, 461–468.

(189) Muzzio, N. E.; Pasquale, M. A.; Diamanti, E.; Gregurec, D.; Moro, M. M.; Azzaroni, O.; Moya, S. E. Enhanced Antiadhesive Properties of Chitosan/Hyaluronic Acid Polyelectrolyte Multilayers Driven by Thermal Annealing: Low Adherence for Mammalian Cells and Selective Decrease in Adhesion for Gram-Positive Bacteria. *Mater. Sci. Eng., C* **2017**, *80*, 677–687.

(190) Dubas, S. T.; Kumlangdudsana, P.; Potiyaraj, P. Layer-by-Layer Deposition of Antimicrobial Silver Nanoparticles on Textile Fibers. *Colloids Surf., A* **2006**, *289*, 105–109.

(191) Moskowitz, J. S.; Blaisse, M. R.; Samuel, R. E.; Hsu, H. P.; Harris, M. B.; Martin, S. D.; Lee, J. C.; Spector, M.; Hammond, P. T. The Effectiveness of the Controlled Release of Gentamicin from Polyelectrolyte Multilayers in the Treatment of *Staphylococcus aureus* Infection in a Rabbit Bone Model. *Biomaterials* **2010**, *31*, 6019–6030.

(192) Shah, N. J.; Macdonald, M. L.; Beben, M. Y.; Padera, R. F.; Samuel, R. E.; Hammond, P. T. Tunable Dual Growth Factor Delivery from Polyelectrolyte Multilayer Films. *Biomaterials* **2011**, *32*, 6183–6193.

(193) Hammond, P. T. Building Biomedical Materials Layer-by-Layer. *Mater. Today* **2012**, *15*, 196–206.

(194) Macdonald, M. L.; Samuel, R. E.; Shah, N. J.; Padera, R. F.; Beben, Y. M.; Hammond, P. T. Tissue Integration of Growth Factor-Emitting Layer-by-Layer Polyelectrolyte Multilayer Coated Implants. *Biomaterials* **2011**, *32*, 1446–1453.

(195) Joseph, N.; Ahmadiannamini, P.; Hoogenboom, R.; Vankelecom, I. F. J. Layer-by-Layer Preparation of Polyelectrolyte Multilayer Membranes for Separation. *Polym. Chem.* **2014**, *5*, 1817–1831.

(196) Miller, M. D.; Bruening, M. L. Controlling the Nanofiltration Properties of Multilayer Polyelectrolyte Membranes through Variation of Film Composition. *Langmuir* **2004**, *20*, 11545–11551.

(197) Krasemann, L.; Tieke, B. Composite Membranes with Ultrathin Separation Layer Prepared by Self-Assembly of Polyelectrolytes. *Mater. Sci. Eng., C* **1999**, *8–9*, 513–518.

(198) van Ackern, F.; Krasemann, L.; Tieke, B. Ultrathin Membranes for Gas Separation and Pervaporation Prepared upon Electrostatic Self-Assembly of Polyelectrolytes. *Thin Solid Films* **1998**, *327–329*, 762–766.

(199) White, N.; Misovich, M.; Alemayehu, E.; Yaroshchuk, A.; Bruening, M. L. Highly Selective Separations of Multivalent and Monovalent Cations in Electrodialysis through Nafion Membranes Coated with Polyelectrolyte Multilayers. *Polymer* **2016**, *103*, 478–485.

(200) Krasemann, L.; Tieke, B. Selective Ion Transport Across Self-Assembled Alternating Multilayers of Cationic and Anionic Polyelectrolytes. *Langmuir* **2000**, *16*, 287–290.

(201) Liu, G.; Dotzauer, M. D.; Bruening, M. L. Ion-Exchange Membranes Prepared Using Layer-by-Layer Polyelectrolyte Deposition. *J. Membr. Sci.* **2010**, *354*, 198–205.

(202) de Grooth, J.; Oborný, R.; Potreck, J.; Nijmeijer, K.; de Vos, W. M. The Role of Ionic Strength and Odd-Even Effects on the Properties of Polyelectrolyte Multilayer Nanofiltration Membranes. *J. Membr. Sci.* **2015**, *475*, 311–319.

(203) Menne, D.; Üzüüm, C.; Koppelman, A.; Wong, J. E.; Foeken, C. V.; Borre, F.; Dähne, L.; Laakso, T.; Pihlajamäki, A.; Wessling, M. Regenerable Polymer/Ceramic Hybrid Nanofiltration Membrane Based on Polyelectrolyte Assembly by Layer-by-Layer Technique. *J. Membr. Sci.* **2016**, *520*, 924–932.

(204) Cho, K. L.; Hill, A. J.; Caruso, F.; Kentish, S. E. Chlorine Resistant Glutaraldehyde Crosslinked Polyelectrolyte Multilayer Membranes for Desalination. *Adv. Mater.* **2015**, *27*, 2791–2796.

(205) Irigoyen, J.; Politakos, N.; Murray, R.; Moya, S. E. Design and Fabrication of Regenerable Polyelectrolyte Multilayers for Applications in Foulant Removal. *Macromol. Chem. Phys.* **2014**, *215*, 1543–1550.

(206) Singer, S. J.; Nicolson, G. L. The Fluid Mosaic of the Structure of Cell Membranes. *Science* **1972**, *175*, 720–731.

(207) Palankar, R.; Pinchasik, B. E.; Khlebtsov, B. N.; Kolesnikova, T. A.; Möhwald, H.; Winterhalter, M.; Skirtach, A. G. Nanoplasmonically-Induced Defects in Lipid Membrane Monitored by Ion Current: Transient Nanopores versus Membrane Rupture. *Nano Lett.* **2014**, *14*, 4273–4279.

(208) Diamanti, E.; Andreozzi, P.; Anguiano, R.; Yate, L.; Gregurec, D.; Politakos, N.; Ziolo, R. F.; Donath, E.; Moya, S. E. The Effect of Top-Layer Chemistry on the Formation of Supported Lipid Bilayers on Polyelectrolyte Multilayers: Primary versus Quaternary Amines. *Phys. Chem. Chem. Phys.* **2016**, *18*, 32396–32405.

(209) Diamanti, E.; Gregurec, D.; Rodríguez-Presa, M. J.; Gervasi, C. A.; Azzaroni, O.; Moya, S. E. High Resistivity Lipid Bilayers Assembled on Polyelectrolyte Multilayer Cushions: An Impedance Study. *Langmuir* **2016**, *32*, 6263–6271.

(210) Diamanti, E.; Cuellar, L.; Gregurec, D.; Moya, S. E.; Donath, E. Role of Hydrogen Bonding and Polyanion Composition in the Formation of Lipid Bilayers on Top of Polyelectrolyte Multilayers. *Langmuir* **2015**, *31*, 8623–8632.

(211) Diamanti, E.; Andreozzi, P.; Kirby, C.; Anguiano, R.; Yate, L.; Heinz, H.; Ziolo, R. F.; Donath, E.; Moya, S. E. Study of the Impact of Polyanions on the Formation of Lipid Bilayers on Top of Polyelectrolyte Multilayers with Poly(allylamine hydrochloride) as the Top Layer. *J. Phys. Chem. B* **2017**, *121*, 1158–1167.

(212) Diamanti, E.; Gutiérrez-Pineda, E.; Politakos, N.; Andreozzi, P.; Rodríguez-Presa, M. J.; Knoll, W.; Azzaroni, O.; Gervasi, C. A.; Moya, S. E. Gramicidin Ion Channels in a Lipid Bilayer Supported on Polyelectrolyte Multilayer Films: An Electrochemical Impedance Study. *Soft Matter* **2017**, *13*, 8922–8929.

(213) Zhang, R. J.; Kohler, K.; Kreft, O.; Skirtach, A.; Möhwald, H.; Sukhorukov, G. Salt-Induced Fusion of Microcapsules of Polyelectrolytes. *Soft Matter* **2010**, *6*, 4742–4747.

(214) Skorb, E. V.; Möhwald, H. Smart Surface Capsules for Delivery Devices. *Adv. Mater. Interfaces* **2014**, *1*, 1400237.

(215) Skirtach, A.; Yashchenok, A.; Möhwald, H. Encapsulation, Release and Applications of LbL Polyelectrolyte Multilayer Capsules. *Chem. Commun.* **2011**, *47*, 12736–12746.

(216) Liu, X. Y.; Gao, C. Y.; Shen, J. C.; Möhwald, H. Multilayer Microcapsules as Anti-Cancer Drug Delivery Vehicle: Deposition, Sustained Release, and *in Vitro* Bioactivity. *Macromol. Biosci.* **2005**, *5*, 1209–1219.

(217) De Geest, B. G.; Sanders, N. N.; Sukhorukov, G. B.; Demeester, J.; De Smedt, S. C. Release Mechanisms for Polyelectrolyte Capsules. *Chem. Soc. Rev.* **2007**, *36*, 636–649.

(218) Donath, E.; Moya, S.; Neu, B.; Sukhorukov, G. B.; Georgieva, R.; Voigt, A.; Baumler, H.; Kiesewetter, H.; Möhwald, H. Hollow Polymer Shells from Biological Templates: Fabrication and Potential Applications. *Chem. - Eur. J.* **2002**, *8*, 5481–5485.

(219) Sukhorukov, G. B.; Donath, E.; Moya, S.; Susa, A. S.; Voigt, A.; Hartmann, J.; Möhwald, H. Microencapsulation by Means of Step-Wise Adsorption of Polyelectrolytes. *J. Microencapsulation* **2000**, *17*, 177–185.

- (220) Dai, Q.; Bertleff-Zieschang, N.; Braunger, J. A.; Björnalm, M.; Cortez-Jugo, C.; Caruso, F. Particle Targeting in Complex Biological Media. *Adv. Healthcare Mater.* **2018**, *7*, 1700575.
- (221) Richardson, J. J.; Cui, J.; Björnalm, M.; Braunger, J. A.; Ejima, H.; Caruso, F. Innovation in Layer-by-Layer Assembly. *Chem. Rev.* **2016**, *116*, 14828–14867.
- (222) Such, G. K.; Yan, Y.; Johnston, A. P. R.; Gunawan, S. T.; Caruso, F. Interfacing Materials Science and Biology for Drug Carrier Design. *Adv. Mater.* **2015**, *27*, 2278–2297.
- (223) Sivakumar, S.; Gupta, J. K.; Abbott, N. L.; Caruso, F. Monodisperse Emulsions through Templating Polyelectrolyte Multilayer Capsules. *Chem. Mater.* **2008**, *20*, 2063–2065.
- (224) Becker, A. L.; Orlotti, N. I.; Folini, M.; Cavalieri, F.; Zelikin, A. N.; Johnston, A. P. R.; Zaffaroni, N.; Caruso, F. Redox-Active Polymer Microcapsules for the Delivery of a Survivin-Specific siRNA in Prostate Cancer Cells. *ACS Nano* **2011**, *5*, 1335–1344.
- (225) Björnalm, M.; Cui, J.; Bertleff-Zieschang, N.; Song, D.; Caruso, F. Nanoengineering Particles through Template Assembly. *Chem. Mater.* **2017**, *29*, 289–306.
- (226) Noi, K. F.; Roozmand, A.; Björnalm, M.; Richardson, J. J.; Franks, G. V.; Caruso, F. Assembly-Controlled Permeability of Layer-by-Layer Polymeric Microcapsules Using a Tapered Fluidized Bed. *ACS Appl. Mater. Interfaces* **2015**, *7*, 27940–27947.
- (227) Richardson, J. J.; Teng, D.; Björnalm, M.; Gunawan, S. T.; Guo, J.; Cui, J.; Franks, G. V.; Caruso, F. Fluidized Bed Layer-by-Layer Microcapsule Formation. *Langmuir* **2014**, *30*, 10028–10034.
- (228) Chandrawati, R.; Hosta-Rigau, L.; Vanderstraaten, D.; Lokuliyana, S. A.; Stadler, B.; Albericio, F.; Caruso, F. Engineering Advanced Capsosomes: Maximizing the Number of Subcompartments, Cargo Retention, and Temperature-Triggered Reaction. *ACS Nano* **2010**, *4*, 1351–1361.
- (229) Hosta-Rigau, L.; Stadler, B.; Yan, Y.; Nice, E. C.; Heath, J. K.; Albericio, F.; Caruso, F. Capsosomes with Multilayered Subcompartments: Assembly and Loading with Hydrophobic Cargo. *Adv. Funct. Mater.* **2010**, *20*, 59–66.
- (230) Stadler, B.; Chandrawati, R.; Goldie, K.; Caruso, F. Capsosomes: Subcompartmentalizing Polyelectrolyte Capsules Using Liposomes. *Langmuir* **2009**, *25*, 6725–6732.
- (231) Hosta-Rigau, L.; Chung, S. F.; Postma, A.; Chandrawati, R.; Stadler, B.; Caruso, F. Capsosomes with “Free-Floating” Liposomal Subcompartments. *Adv. Mater.* **2011**, *23*, 4082–4087.
- (232) Maina, J. W.; Richardson, J. J.; Chandrawati, R.; Kempe, K.; van Koeven, M. P.; Caruso, F. Capsosomes as Long-Term Delivery Vehicles for Protein Therapeutics. *Langmuir* **2015**, *31*, 7776–7781.
- (233) Chandrawati, R.; Odermatt, P. D.; Chong, S. F.; Price, A. D.; Städler, B.; Caruso, F. Triggered Cargo Release by Encapsulated Enzymatic Catalysis in Capsosomes. *Nano Lett.* **2011**, *11*, 4958–4963.
- (234) Chandrawati, R.; Chong, S. F.; Zelikin, A. N.; Hosta-Rigau, L.; Städler, B.; Caruso, F. Degradation of Liposomal Subcompartments in PEGylated Capsosomes. *Soft Matter* **2011**, *7*, 9638–9646.
- (235) Hosta-Rigau, L.; Chandrawati, R.; Saveriades, E.; Odermatt, P. D.; Postma, A.; Ercole, F.; Breheney, K.; Wark, K. L.; Städler, B.; Caruso, F. Noncovalent Liposome Linkage and Miniaturization of Capsosomes for Drug Delivery. *Biomacromolecules* **2010**, *11*, 3548–3555.
- (236) Zebli, B.; Susha, A. S.; Sukhorukov, G. B.; Rogach, A. L.; Parak, W. J. Magnetic Targeting and Cellular Uptake of Polymer Microcapsules Simultaneously Functionalized with Magnetic and Luminescent Nanocrystals. *Langmuir* **2005**, *21*, 4262–4265.
- (237) Ochs, M.; Carregal Romero, S.; Rejman, J.; Braeckmans, K.; De Smedt, S. C.; Parak, W. J. Light-Addressable Capsules as Caged Compound Matrix for Controlled *in Vitro* Release. *Angew. Chem., Int. Ed.* **2013**, *52*, 695–699.
- (238) Kirchner, C.; Javier, A. M.; Susha, A. S.; Rogach, A. L.; Kreft, O.; Sukhorukov, G. B.; Parak, W. J. Cytotoxicity of Nanoparticle-Loaded Polymer Capsules. *Talanta* **2005**, *67*, 486–491.
- (239) Kastl, L.; Sasse, D.; Wulf, V.; Hartmann, R.; Mircheski, J.; Ranke, C.; Carregal-Romero, S.; Martínez-López, J. A.; Fernández-Chacón, R.; Parak, W. J.; Elsaesser, H. P.; Rivera Gil, P. Multiple Internalization Pathways of Polyelectrolyte Multilayer Capsules into Mammalian Cells. *ACS Nano* **2013**, *7*, 6605–6618.
- (240) Zyuzin, M. V.; Díez, P.; Goldsmith, M.; Carregal-Romero, S.; Teodosio, C.; Rejman, J.; Feliu, N.; Escudero, A.; Almendral, M. J. S.; Linne, U.; Peer, D.; Fuentes, M.; Parak, W. J. Comprehensive and Systematic Analysis of the Immunocompatibility of Polyelectrolyte Capsules. *Bioconjugate Chem.* **2017**, *28*, 556–564.
- (241) Delcea, M.; Schmidt, S.; Palankar, R.; Fernandes, P. A. L.; Fery, A.; Möhwald, H.; Skirtach, A. G. P. Mechanobiology: Correlation between Mechanical Stability of Microcapsules Studied by AFM and Impact of Cell-Induced Stresses. *Small* **2010**, *6*, 2858–2862.
- (242) Hartmann, R.; Weidenbach, M.; Neubauer, M.; Fery, A.; Parak, W. J. Stiffness-Dependent *in Vitro* Uptake and Lysosomal Acidification of Colloidal Particles. *Angew. Chem., Int. Ed.* **2015**, *54*, 1365–1368.
- (243) Sun, H. L.; Wong, E. H. H.; Yan, Y.; Cui, J. W.; Dai, Q.; Guo, J. L.; Qiao, G. G.; Caruso, F. The Role of Capsule Stiffness on Cellular Processing. *Chem. Sci.* **2015**, *6*, 3505–3514.
- (244) Shimoni, O.; Yan, Y.; Wang, Y.; Caruso, F. Shape-Dependent Cellular Processing of Polyelectrolyte Capsules. *ACS Nano* **2013**, *7*, 522–530.
- (245) De Koker, S.; De Geest, B. G.; Cuvelier, C.; Ferdinande, L.; Deckers, W.; Hennink, W. E.; De Smedt, S.; Mertens, N. *In Vivo* Cellular Uptake, Degradation, and Biocompatibility of Polyelectrolyte Microcapsules. *Adv. Funct. Mater.* **2007**, *17*, 3754–3763.
- (246) De Koker, S.; Naessens, T.; De Geest, B. G.; Bogaert, P.; Demeester, J.; De Smedt, S.; Grooten, J. Biodegradable Polyelectrolyte Microcapsules: Antigen Delivery Tools with Th17 Skewing Activity after Pulmonary Delivery. *J. Immunol.* **2010**, *184*, 203–211.
- (247) Antipov, A. A.; Sukhorukov, G. B.; Leporatti, S.; Radtchenko, I. L.; Donath, E.; Möhwald, H. Polyelectrolyte Multilayer Capsule Permeability Control. *Colloids Surf., A* **2002**, *198*, 535–541.
- (248) Kamphuis, M. M. J.; Johnston, A. P. R.; Such, G. K.; Dam, H. H.; Evans, R. A.; Scott, A. M.; Nice, E. C.; Heath, J. K.; Caruso, F. Targeting of Cancer Cells Using Click-Functionalized Polymer Capsules. *J. Am. Chem. Soc.* **2010**, *132*, 15881–15883.
- (249) Facca, S.; Cortez, C.; Mendoza-Palomares, C.; Messadeq, N.; Dierich, A.; Johnston, A. P.; Mainard, D.; Voegel, J. C.; Caruso, F.; Benkirane-Jessel, N. Active Multilayered Capsules for *in Vivo* Bone Formation. *Proc. Natl. Acad. Sci. U. S. A.* **2010**, *107*, 3406–3411.
- (250) Chluba, J.; Voegel, J. C.; Decher, G.; Erbacher, P.; Schaaf, P.; Ogier, J. Peptide Hormone Covalently Bound to Polyelectrolytes and Embedded into Multilayer Architectures Conserving Full Biological Activity. *Biomacromolecules* **2001**, *2*, 800–805.
- (251) Yu, A. M.; Wang, Y. J.; Barlow, E.; Caruso, F. Mesoporous Silica Particles as Templates for Preparing Enzyme-Loaded Biocompatible Microcapsules. *Adv. Mater.* **2005**, *17*, 1737–1741.
- (252) Ganas, C.; Weiß, A.; Nazarenus, M.; Rösler, S.; Kissel, T.; Rivera Gil, P.; Parak, W. J. Biodegradable Capsules as Non-Viral Vectors for *in Vitro* Delivery of PEI/siRNA Polyplexes for Efficient Gene Silencing. *J. Controlled Release* **2014**, *196*, 132–138.
- (253) Wood, K. C.; Boedicker, J. Q.; Lynn, D. M.; Hammond, P. T. Tunable Drug Release from Hydrolytically Degradable Layer-by-Layer Thin Films. *Langmuir* **2005**, *21*, 1603–1609.
- (254) De Koker, S.; De Geest, B. G.; Singh, S. K.; De Rycke, R.; Naessens, T.; Van Kooyk, Y.; Demeester, J.; De Smedt, S. C.; Grooten, J. Polyelectrolyte Microcapsules as Antigen Delivery Vehicles to Dendritic Cells: Uptake, Processing, and Cross-Presentation of Encapsulated Antigens. *Angew. Chem., Int. Ed.* **2009**, *48*, 8485–8489.
- (255) Rivera Gil, P.; De Koker, S.; De Geest, B. G.; Parak, W. J. Intracellular Processing of Proteins Mediated by Biodegradable Polyelectrolyte Capsules. *Nano Lett.* **2009**, *9*, 4398–4402.
- (256) Radt, B.; Smith, T. A.; Caruso, F. Optically Addressable Nanostructured Capsules. *Adv. Mater.* **2004**, *16*, 2184–2189.
- (257) Ambrosone, A.; Marchesano, V.; Carregal-Romero, S.; Intartaglia, D.; Parak, W. J.; Tortiglione, C. Control of Wnt/ β -

Catenin Signaling Pathway *in Vivo* via Light Responsive Capsules. *ACS Nano* **2016**, *10*, 4828–4834.

(258) Lengert, E.; Parakhonskiy, B.; Khalkenow, D.; Zečić, A.; Vangheel, M.; Monje Moreno, J. M.; Braeckman, B. P.; Skirtach, A. G. Laser-Induced Remote Release *in Vivo* in *C. elegans* from Novel Silver Nanoparticles-Alginate Hydrogel Shells. *Nanoscale* **2018**, *10*, 17249–17256.

(259) Kolesnikova, T. A.; Gorin, D. A.; Fernandes, P.; Kessel, S.; Khomutov, G. B.; Fery, A.; Shchukin, D. G.; Möhwald, H. Nanocomposite Microcontainers with High Ultrasound Sensitivity. *Adv. Funct. Mater.* **2010**, *20*, 1189–1195.

(260) De Geest, B. G.; Skirtach, A. G.; Mamedov, A. A.; Antipov, A. A.; Kotov, N. A.; De Smedt, S. C.; Sukhorukov, G. B. Ultrasound-Triggered Release from Multilayered Capsules. *Small* **2007**, *3*, 804–808.

(261) Shchukin, D. G.; Gorin, D. A.; Möhwald, H. Ultrasonically Induced Opening of Polyelectrolyte Microcontainers. *Langmuir* **2006**, *22*, 7400–7404.

(262) Cui, X.; Li, Z.; Zhong, S.; Wang, B.; Han, Y.; Wang, H.; Möhwald, H. A Facile Sonochemical Route for the Fabrication of Magnetic Protein Microcapsules for Targeted Delivery. *Chem. - Eur. J.* **2013**, *19*, 9485–9488.

(263) Lu, Z.; Prouty, M. D.; Guo, Z.; Golub, V. O.; Kumar, C. S.; Lvov, Y. M. Magnetic Switch of Permeability for Polyelectrolyte Microcapsules Embedded with Co@Au Nanoparticles. *Langmuir* **2005**, *21*, 2042–2050.

(264) Timin, A. S.; Litvak, M. M.; Gorin, D. A.; Atochina-Vasserman, E. N.; Atochin, D. N.; Sukhorukov, G. B. Drug Delivery: Cell-Based Drug Delivery and Use of Nano- and Microcarriers for Cell Functionalization. *Adv. Healthcare Mater.* **2018**, *7*, 1700818.

(265) Vidiyasheva, I. V.; Abalymov, A. A.; Kurochkin, M. A.; Mayorova, O. A.; Lomova, M. V.; German, S. V.; Khalkenow, D. N.; Zharkov, M. N.; Gorin, D. A.; Skirtach, A. G.; Tuchin, V. V.; Sukhorukov, G. B. Transfer of Cells with Uptaken Nanocomposite, Magnetite-Nanoparticle Functionalized Capsules with Electromagnetic Tweezers. *Biomater. Sci.* **2018**, *6*, 2219–2229.

(266) Pavlov, A. M.; DeGeest, B. G.; Louage, B.; Lybaert, L.; DeKoker, S.; Koudelka, Z.; Sapelkin, A. V.; Sukhorukov, G. B. Magnetically Engineered Microcapsules as Intracellular Anchors for Remote Control over Cellular Mobility. *Adv. Mater.* **2013**, *25*, 6945–6950.

(267) Muslimov, A.; Timin, A. S.; Petrova, A.; Epifanovskaya, O.; Shakirova, A. I.; Lepik, K. V.; Gorshkov, A.; Il'inskaja, E. V.; Vasin, A. V.; Afanasyev, B. V.; Fehse, B.; Sukhorukov, G. B. Mesenchymal Stem Cells Engineering: Microcapsules-Assisted Gene Transfection and Magnetic Cell Separation. *ACS Biomater. Sci. Eng.* **2017**, *3*, 2314–2324.

(268) Lepik, K. V.; Muslimov, A. R.; Timin, A. S.; Sergeev, V. S.; Romanyuk, D. S.; Moiseev, I. S.; Popova, E. V.; Radchenko, I. L.; Vilesov, A. D.; Galibin, O. V.; Sukhorukov, G. B.; Afanasyev, B. V. Mesenchymal Stem Cell Magnetization: Magnetic Multilayer Microcapsule Uptake, Toxicity, Impact on Functional Properties, and Perspectives for Magnetic Delivery. *Adv. Healthcare Mater.* **2016**, *5*, 3182–3190.

(269) Baleeiro, R. B.; Wiesmüller, K. H.; Reiter, Y.; Baude, B.; Dähne, L.; Patzelt, A.; Lademann, J.; Barbutto, J. A.; Walden, P. Topical Vaccination with Functionalized Particles Targeting Dendritic Cells. *J. Invest. Dermatol.* **2013**, *133*, 1933–1941.

(270) Richardson, J. J.; Choy, M. Y.; Guo, J.; Liang, K.; Alt, K.; Ping, Y.; Cui, J.; Law, L. S.; Hagemeyer, C. E.; Caruso, F. Polymer Capsules for Plaque-Targeted *in Vivo* Delivery. *Adv. Mater.* **2016**, *28*, 7703–7707.

(271) Sexton, A.; Whitney, P. G.; Chong, S. F.; Zelikin, A. N.; Johnston, A. P. R.; De Rose, R.; Brooks, A. G.; Caruso, F.; Kent, S. J. A Protective Vaccine Delivery System for *in Vivo* T Cell Stimulation Using Nanoengineered Polymer Hydrogel Capsules. *ACS Nano* **2009**, *3*, 3391–3400.

(272) De Geest, B. G.; Willart, M. A.; Hammad, H.; Lambrecht, B. N.; Pollard, C.; Bogaert, P.; De Filette, M.; Saelens, X.; Vervaet, C.;

Remon, J. P.; Grooten, J.; De Koker, S. Polymeric Multilayer Capsule-Mediated Vaccination Induces Protective Immunity against Cancer and Viral Infection. *ACS Nano* **2012**, *6*, 2136–2149.

(273) De Geest, B. G.; Willart, M. A.; Lambrecht, B. N.; Pollard, C.; Vervaet, C.; Remon, J. P.; Grooten, J.; De Koker, S. Surface-Engineered Polyelectrolyte Multilayer Capsules-Synthetic Vaccines Mimicking Microbial Structure and Function. *Angew. Chem., Int. Ed.* **2012**, *51*, 3862–3866.

(274) DeMuth, P. C.; Min, Y.; Huang, B.; Kramer, J. A.; Miller, A. D.; Barouch, D. H.; Hammond, P. T.; Irvine, D. J. Polymer Multilayer Tattooing for Enhanced DNA Vaccination. *Nat. Mater.* **2013**, *12*, 367–376.

(275) Tostanoski, L. H.; Chiu, Y. C.; Andorko, J. I.; Guo, M.; Zeng, X.; Zhang, P.; Royal, W.; Jewell, C. M. Design of Polyelectrolyte Multilayers to Promote Immunological Tolerance. *ACS Nano* **2016**, *10*, 9334–9345.

(276) Khalkenow, D.; Donche, S.; Braeckman, K.; Vanhove, C.; Skirtach, A. G. Added Value of Microscale Raman Chemical Analysis in Mild Traumatic Brain Injury (TBI): A Comparison with Macroscopic MRI. *ACS Omega* **2018**, *3*, 16806–16811.

(277) Barrefelt, Å. A.; Brismar, T. B.; Egri, G.; Aspelin, P.; Olsson, A.; Oddo, L.; Margheritelli, S.; Caidahl, K.; Paradossi, G.; Dähne, L.; Axelsson, R.; Hassan, M. Multimodality Imaging Using SPECT/CT and MRI and Ligand Functionalized ^{99m}Tc-Labeled Magnetic Microbubbles. *EJNMMI Res.* **2013**, *3*, 12.

(278) Barrefelt, Å.; Saghaian, M.; Kuiper, R.; Ye, F.; Egri, G.; Klickermann, M.; Brismar, T. B.; Aspelin, P.; Muhammed, M.; Dähne, L.; Hassan, M. Biodistribution, Kinetics, and Biological Fate of SPION Microbubbles in the Rat. *Int. J. Nanomed.* **2013**, *8*, 3241–3254.

(279) Ahmed, M.; Gustafsson, B.; Aldi, S.; Dusart, P.; Egri, G.; Butler, L. M.; Bone, D.; Dähne, L.; Hedin, U.; Caidahl, K. Molecular Imaging of a New Multimodal Microbubble for Adhesion Molecule Targeting. *Cell. Mol. Bioeng.* **2019**, *12*, 15–32.

(280) Barrefelt, A.; Zhao, Y.; Larsson, M. K.; Egri, G.; Kuiper, R. V.; Hamm, J.; Saghaian, M.; Caidahl, K.; Brismar, T. B.; Aspelin, P.; Heuchel, R.; Muhammed, M.; Dähne, L.; Hassan, M. Fluorescence Labeled Microbubbles for Multimodal Imaging. *Biochem. Biophys. Res. Commun.* **2015**, *464*, 737–742.

(281) Del Mercato, L. L.; Abbasi, A. Z.; Parak, W. J. Synthesis and Characterization of Ratiometric Ion-Sensitive Polyelectrolyte Capsules. *Small* **2011**, *7*, 351–363.

(282) Del Mercato, L. L.; Abbasi, A. Z.; Ochs, M.; Parak, W. J. Multiplexed Sensing of Ions with Barcoded Polyelectrolyte Capsules. *ACS Nano* **2011**, *5*, 9668–9674.

(283) Rivera Gil, P.; Nazarenus, M.; Ashraf, S.; Parak, W. J. pH Sensitive Capsules as Intracellular Optical Reporters for Monitoring Lysosomal pH Changes upon Stimulation. *Small* **2012**, *8*, 943–948.

(284) Delcea, M.; Yashchenok, A.; Videnova, K.; Kreft, O.; Möhwald, H.; Skirtach, A. G. Multicompartmental Micro- and Nanocapsules: Hierarchy and Applications in Biosciences. *Macromol. Biosci.* **2010**, *10*, 465–474.

(285) Harimech, P. K.; Hartmann, R.; Rejman, J.; Del Pino, P.; Rivera Gil, P.; Parak, W. J. Encapsulated Enzymes with Integrated Fluorescence-Control of Enzymatic Activity. *J. Mater. Chem. B* **2015**, *3*, 2801–2807.

(286) Xiong, R.; Soenen, S. J.; Braeckmans, K.; Skirtach, A. G. Towards Theranostic Multicompartment Microcapsules: *In-Situ* Diagnostics and Laser-Induced Treatment. *Theranostics* **2013**, *3*, 141–151.